



Chemical Compatibility Guide for: North Butyl® Gloves

NOTICE:

The guide on the following page(s) was provided by the supplier. New Pig Corporation assumes no responsibility, obligation, or liability in conjunction with the use or misuse of the information.

**For additional assistance, please contact New Pig Technical Services at
1-800-HOT-HOGS® (468-4647).**

100% Money-Back Guarantee

If you're not happy with a product, for any reason, we'll refund every penny of your purchase price. That means we'll refund all sales taxes, shipping costs, and any other incidentals - without tacking on a restocking fee or any other surprise charges. You get ALL your money back. Period.

One Pork Avenue, Tipton, PA 16684-0304 • 1-800-HOT HOGS® (468-4647) • Fax: 1-800-621-PIGS (7447)
Email: hothogs@newpig.com • Web: newpig.com

© New Pig Corporation. All rights reserved.



NORTH

*Chemical
Resistance
Guide*

CHEMICAL RESISTANCE GUIDE

This Chemical Resistance Guide incorporates three types of information:

- **Degradation (D)** is a deleterious change in one or more of the glove's physical properties. The most obvious forms of degradation are the loss of the glove's strength and excessive swelling. Several published degradation lists (primarily "The General Chemical Resistance of Various Elastomers" by the Los Angeles Rubber Group, Inc.) were used to determine degradation.
- **Breakthrough time (BT)** is defined as the elapsed time between initial contact of the liquid chemical with the outside surface of the glove and the time at which the permeation rate reaches 0.1 mg/m²/sec. WHEN BREAKTHROUGH OCCURS, THE GLOVE IS NO LONGER PROVIDING ADEQUATE PROTECTION.
- **Permeation rate (PR)**, measured in milligrams per square meter per second (mg/m²/sec) is the measured steady state flow of the permeating chemical through the glove elastomer. Glove thickness plays an important role in resistance to permeation.

The glove styles tested for permeation were the SSG, F101, B174, CS113B, LA102G and PNLB1815. The permeation data in this guide are based on permeation tests performed in accordance with ASTM Standard F 739 under laboratory conditions by North Safety Products or independent AIHA accredited laboratories. Neither North Safety Products nor the independent laboratory assumes any responsibility for the suitability of an end user's selection of gloves based on this guide.

General Recommendation:

The Guide also provides a color-coded general recommendation on which gloves should be evaluated and tested first, based on data from multiple sources. (See general recommendation color key).

Technical Assistance:

Data on chemicals not listed here can be obtained by calling the North Technical Service Department at

(800) 430-4110. North also offers **ezGuide™**, an interactive software program which is designed to electronically help you select the proper glove for use against specific chemicals. This "user friendly" guide walks you step-by-step through the process to determine what type of glove to wear and its permeation resistance to the selected contaminant. Product features, benefits and ordering information of the suggested products also are included in the program. **ezGuide** can be accessed from the North web site, www.northsafety.com or ordered by e-mailing us at marketing@northsafety.com.

The finest chemical handling gloves deserve to be used with the finest respiratory products. Please consult the current North Safety Products Respiratory Protection Catalog and **ezGuide™** for proper respiratory selection.

Warning:

Protective gloves and other protective apparel selection must be based on the user's assessment of the workplace hazards. Glove and Apparel materials do not provide unlimited protection against all chemicals. It is the users responsibility to determine before use that the Glove and Apparel will resist permeation and degradation by the chemicals (including chemical mixtures) in the environment of intended use.

Failure by the user to select the correct protective gloves can result in injury, sickness or death




To obtain maximum life, protective gloves and other protective apparel should have chemicals removed from the surface by washing or other appropriate methods after each use. Protective apparel should be stored away from the contaminating atmosphere.

Punctured, torn or otherwise ruptured apparel must be removed from service; unservicable apparel may be disposed of only in accordance with applicable waste disposal regulations.

Key to Degradation and Permeation Ratings

- E - Excellent Exposure has little or no effect. The glove retains its properties after extended exposure
- G - Good Exposure has minor effect with long term exposure. Short term exposure has little or no effect
- F - Fair Exposure causes moderate degradation of the glove. Glove is still useful after short term exposure but caution should be exercised with extended exposure
- P - Poor Short term exposure will result in moderate degradation to complete destruction
- N/D Permeation was not detected during the test
- I/D Insufficient data to make a recommendation

General Recommendation Color Key

-  Good for total immersion
-  Good for accidental splash protection and intermittent contact
-  Only use with extreme caution. Glove will fail with only short exposure

Physical Performance Chart

Physical Characteristics	Silver Shield®	Viton†	Butyl	Chemsoft®	Nitrile	Natural Rubber
Abrasion Resistance	F	G	G	E	E	E
Cut Resistance	P	G	G	E	E	E
Puncture (Snag) Resistance	P	G	G	E	E	E
Flexibility	E	G	G	E	E	E
Heat Resistance	F	G	G	G	G	G
Ozone Resistance	E	E	E	G	G	P
Tensile Strength	E	G	G	E	E	E
Low Gas Permeability	E	E	E	F	F	P

Note: Products in these categories vary in capabilities. Laboratory tests are necessary for specific recommendations.




† Viton is a Registered Trademark of DuPont Company.

		Silver Shield			Viton			Butyl			Chemsoft			Nitrile			Natural Rubber		
Chemical Name	CAS No.	D	BT	PR	D	BT	PR	D	BT	PR	D	BT	PR	D	BT	PR	D	BT	PR
Acetaldehyde	75-07-0	E	>8 hrs	N/D	P	0 min	281.9	E	>8 hrs	0.066	I/D	I/D	I/D	P	0 min	161	I/D	I/D	I/D
Acetic Acid (100%) (Glacial)	64-19-7	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	F	37 min	13.3	F	38 min	1.9	F	1.3 hrs	0.39
Acetic Aldehyde	75-07-0	E	>8 hrs	N/D	P	0 min	281.9	E	>8 hrs	0.066	I/D	I/D	I/D	P	0 min	161	I/D	I/D	I/D
Acetic Ester	141-78-6	E	>8 hrs	N/D	I/D	I/D	I/D	E	7.6 hrs	3.4	I/D	I/D	I/D	P	8 min	145	I/D	I/D	I/D
Acetone	67-64-1	E	>8 hrs	N/D	P	2 min	383	E	>8 hrs	N/D	P	1 min	42.3	P	3 min	291	P	8 min	93.2
Acrylic Acid	79-10-7	E	>8 hrs	N/D	G	5.9 hrs	0.23	E	>8 hrs	N/D	I/D	I/D	I/D	F	I/D	I/D	G	54 min	1.6
Acrylonitrile	107-13-1	E	>8 hrs	N/D	F	14 min	28	E	>8 hrs	N/D	P	4 min	42	P	6 min	29.8	P	16 min	0.11
Ammonia (99%)	7664-41-7	E	>8 hrs	N/D	E	>8 hrs	N/D	E	>8 hrs	N/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D
Ammonium Hydroxide (29%)	1336-21-6	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	F	2 hrs	0.115	F	2.2 hrs	0.05	G	60 min	28.7
Aniline	62-53-3	E	>8 hrs	N/D	P	6 min	18.7	E	>8 hrs	N/D	I/D	I/D	I/D	F	1.1 hrs	45	I/D	I/D	I/D
Aniline Oil	62-53-3	E	>8 hrs	N/D	P	6 min	18.7	E	>8 hrs	N/D	I/D	I/D	I/D	F	1.1 hrs	45	I/D	I/D	I/D
Benzaldehyde	100-52-7	I/D	I/D	I/D	E	>8 hrs	4	E	>8 hrs	N/D	I/D	I/D	I/D	P	I/D	I/D	I/D	I/D	I/D
Benzene	71-43-2	E	>8 hrs	N/D	E	5.9 hrs	0.012	P	31 min	32.3	P	I/D	I/D	P	<6 min	>29	I/D	I/D	I/D
Bromoacetonitrile	590-17-0	I/D	I/D	I/D	E	>8 hrs	N/D	E	>8 hrs	N/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D
Bromobenzene	108-86-1	E	I/D	I/D	E	>8 hrs	N/D	P	32 min	39.8	I/D	I/D	I/D	P	13 min	9.1	I/D	I/D	I/D
1,3-Butadiene	106-99-0	E	>8 hrs	N/D	E	>8 hrs	N/D	E	>8 hrs	N/D	E	>8 hrs	N/D	I/D	I/D	I/D	I/D	I/D	I/D
Butyl Acetate	123-86-4	E	>8 hrs	N/D	P	I/D	I/D	G	1.8 hrs	7.61	I/D	I/D	I/D	P	29 min	54.4	F	18 min	47
Butyraldehyde	123-72-8	I/D	I/D	I/D	P	54 min	9	E	>8 hrs	N/D	I/D	I/D	I/D	P	I/D	I/D	I/D	I/D	I/D
Carbon Bisulfide	75-15-0	E	>8 hrs	N/D	E	>8 hrs	N/D	P	3 min	98.4	I/D	I/D	I/D	P	9 min	51	I/D	I/D	I/D
Carbon Disulfide	75-15-0	E	>8 hrs	N/D	E	>8 hrs	N/D	P	3 min	98.4	I/D	I/D	I/D	P	9 min	51	I/D	I/D	I/D
Carbon Tetrachloride	56-23-5	E	>8 hrs	N/D	E	>13 hrs	N/D	P	I/D	I/D	F	1.3 hrs	3.45	G	3.4 hrs	5	I/D	I/D	I/D
Caustic Soda (50%)	1310-73-2	E	>8 hrs	N/D	E	>8 hrs	N/D	E	>8 hrs	N/D	E	>8 hrs	N/D	E	>8 hrs	N/D	E	>8 hrs	N/D
Chlorine	7782-50-5	E	>8 hrs	N/D	E	>8 hrs	N/D	E	>8 hrs	N/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D
2-Chloroethanol	107-07-3	I/D	I/D	I/D	E	>8 hrs	N/D	E	>8 hrs	N/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D
Chloroform	67-66-3	E	>8 hrs	N/D	E	9.5 hrs	0.46	P	I/D	I/D	I/D	I/D	I/D	P	4 min	352	I/D	I/D	I/D
3-Chloroprene	107-05-1	E	>4 hrs	N/D	F	31 min	16	P	50 min	281	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D
Curing Agent Z	N/A	E	>8 hrs	N/D	E	>8 hrs	N/D	E	>8 hrs	N/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D
Cyclohexane	110-82-7	E	>4hrs	N/D	E	>7 hrs	N/D	P	50 min	103.8	E	>8 hrs	N/D	G	I/D	I/D	I/D	I/D	I/D
Cyclohexanol	108-93-0	E	>8 hrs	N/D	E	>8 hrs	N/D	E	>11 hrs	N/D	E	>6 hrs	N/D	E	>16 hrs	N/D	I/D	I/D	I/D
Cyclohexanone	108-94-1	E	>8 hrs	N/D	P	29 min	86.3	E	>16 hrs	N/D	I/D	I/D	I/D	P	I/D	I/D	F	15 min	46.9
Di(2-ethylhexyl)phthalate	117-81-7	I/D	I/D	I/D	E	>8 hrs	N/D	E	>8 hrs	N/D	E	>8 hrs	N/D	E	>8 hrs	N/D	I/D	I/D	I/D
Dibutylphthalate	84-74-2	E	>8 hrs	N/D	E	>8 hrs	N/D	E	>16 hrs	N/D	E	>8 hrs	N/D	E	>16 hrs	N/D	I/D	I/D	I/D
1,2-Dichloroethane	107-06-2	E	>8 hrs	N/D	E	>8 hrs	N/D	P	2.9 hrs	53	I/D	I/D	I/D	P	8 min	82.7	I/D	I/D	I/D
Dichloromethane	75-09-2	E	>8 hrs	N/D	F	1 hr	7.32	I/D	I/D	I/D	I/D	I/D	I/D	P	4 min	766	I/D	I/D	I/D
Diethyl Ether	60-29-7	E	>8 hrs	N/D	P	12 min	21.5	P	8 min	92.2	I/D	I/D	I/D	P	14 min	21.8	I/D	I/D	I/D

D = Degradation
BT = Breakthrough Time
PR = Permeation Rate

E = Excellent
G = Good
F = Fair
P = Poor

N/D = None Detected
I/D = Insufficient Data

 Good for total immersion
 Good for accidental splash protection and intermittent contact
 Only use with extreme caution. Glove will fail with only short exposure




		Silver Shield			Viton			Butyl			Chemsoft			Nitrile			Natural Rubber		
Chemical Name	CAS No.	D	BT	PR	D	BT	PR	D	BT	PR	D	BT	PR	D	BT	PR	D	BT	PR
Diethyl Oxide	60-29-7	E	>8 hrs	N/D	P	12 min	21.5	P	8 min	92.2	I/D	I/D	I/D	P	14 min	21.8	I/D	I/D	I/D
Diethylamine	109-89-7	E	>8 hrs	N/D	P	35 min	852	P	47 min	46	I/D	I/D	I/D	F	I/D	I/D	I/D	I/D	I/D
Diethylaminoethanol	100-37-8	I/D	I/D	I/D	E	>8 hrs	N/D	E	>8 hrs	N/D	E	>7.8 hrs	0.02	E	>8 hrs	N/D	I/D	I/D	I/D
1,4-Diethylene Dioxide	123-91-1	I/D	I/D	I/D	P	23 min	26.8	E	>20 hrs	N/D	I/D	I/D	I/D	P	28 min	77.1	I/D	I/D	I/D
Diethylene Ether	123-91-1	I/D	I/D	I/D	P	23 min	26.8	E	>20 hrs	N/D	I/D	I/D	I/D	P	28 min	77.1	I/D	I/D	I/D
Diethylene Oxide	123-91-1	I/D	I/D	I/D	P	23 min	26.8	E	>20 hrs	N/D	I/D	I/D	I/D	P	28 min	77.1	I/D	I/D	I/D
Diethylenetriamine	111-40-0	I/D	I/D	I/D	E	>8 hrs	N/D	E	>8 hrs	N/D	I/D	I/D	I/D	P	I/D	I/D	I/D	I/D	I/D
Diisobutyl Ketone (80%)	108-83-8	E	>8 hrs	N/D	F	1.1 hrs	90.6	G	3.3 hrs	41.2	I/D	I/D	I/D	F	2.9 hrs	49	I/D	I/D	I/D
Dimethyl Acetamide	127-19-5	F	1.5 hrs	0.728	P	25 min	3	E	>8 hrs	N/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D
Dimethyl Formamide	68-12-2	E	>8 hrs	N/D	P	8 min	6.5	E	>8 hrs	N/D	I/D	I/D	I/D	F	9 min	15	I/D	I/D	I/D
Dimethyl Mercury	593-74-8	E	>4 hrs	<0.017	P	<15 min	3.1	P	<15 min	46.7	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D
Dimethyl Sulfoxide	67-68-5	G	I/D	I/D	F	1.5 hrs	5	E	>8 hrs	N/D	F	41 min	3.7	F	40 min	5.2	I/D	I/D	I/D
Dimethylketone	67-64-1	E	>8 hrs	N/D	P	2 min	383	E	>8 hrs	N/D	P	1 min	42.3	P	3 min	291	P	10 min	12.2
Diethyl Phthalate	117-81-7	I/D	I/D	I/D	E	>8 hrs	N/D	E	>8 hrs	N/D	E	>8 hrs	N/D	E	>8 hrs	N/D	I/D	I/D	I/D
1,4-Dioxane	123-91-1	I/D	I/D	I/D	P	23 min	26.8	E	>20 hrs	N/D	I/D	I/D	I/D	P	28 min	77.1	I/D	I/D	I/D
Dioxyethylene Ether	123-91-1	I/D	I/D	I/D	P	23 min	26.8	E	>20 hrs	N/D	I/D	I/D	I/D	P	28 min	77.1	I/D	I/D	I/D
Divinyl Benzene	1321-74-0	E	>8 hrs	N/D	E	>17 hrs	N/D	F	2.2 hrs	238	I/D	I/D	I/D	P	I/D	I/D	I/D	I/D	I/D
Epichlorohydrin	106-89-8	I/D	I/D	I/D	P	2 hrs	4	E	>8 hrs	N/D	I/D	I/D	I/D	P	I/D	I/D	I/D	I/D	I/D
1,2-Epoxypropane	75-56-9	I/D	I/D	I/D	P	1 min	1790	F	2.2 hrs	7	I/D	I/D	I/D	P	<6 min	>3.9	I/D	I/D	I/D
Ethanal	75-7-0	E	>8 hrs	N/D	P	0 min	281.9	E	>8 hrs	0.066	I/D	I/D	I/D	P	0 min	161	I/D	I/D	I/D
Ethanol	64-17-5	E	>8 hrs	N/D	I/D	I/D	I/D	E	>8 hrs	N/D	F	1.2 hrs	3.3	I/D	I/D	I/D	I/D	I/D	I/D
Ether	60-29-7	E	>8 hrs	N/D	P	12 min	21.5	P	8 min	92.2	I/D	I/D	I/D	P	14 min	21.8	I/D	I/D	I/D
Ethyl Acetate	141-78-6	E	>8 hrs	N/D	P	I/D	I/D	G	7.6 hrs	3.4	I/D	I/D	I/D	P	8 min	145	I/D	I/D	I/D
Ethyl Alcohol	64-17-5	E	>8 hrs	N/D	I/D	I/D	I/D	E	>8 hrs	N/D	F	1.2 hrs	3.3	I/D	I/D	I/D	G	31 min	2.4
Ethyl Aldehyde	75-07-0	E	>8 hrs	N/D	P	0 min	281.9	E	>8 hrs	0.066	I/D	I/D	I/D	P	0 min	161	I/D	I/D	I/D
Ethyl Ether	60-29-7	E	>8 hrs	N/D	P	12 min	21.5	P	8 min	92.2	I/D	I/D	I/D	P	14 min	21.8	I/D	I/D	I/D
Ethylamine (70% in water)	75-04-7	F	51 min	0.65	P	I/D	I/D	E	>12 hrs	N/D	I/D	I/D	I/D	F	1.1 hrs	30.1	I/D	I/D	I/D
Ethylene Dichloride	107-06-2	E	>8 hrs	N/D	E	>8 hrs	N/D	F	2.9 hrs	53	I/D	I/D	I/D	P	8 min	82.7	I/D	I/D	I/D
Ethylene Glycol	107-21-1	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	E	>8 hrs	N/D	I/D	I/D	I/D	E	>8hrs	N/D
Ethylene Oxide	75-21-8	E	>8 hrs	N/D	E	>8 hrs	N/D	E	>8 hrs	N/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D
Formaldehyde (37% in water)	50-00-0	E	>8 hrs	N/D	E	>16 hrs	N/D	E	>16 hrs	N/D	E	>8hrs	0.007	E	>21 hrs	N/D	I/D	I/D	I/D
Furfural	98-01-1	E	>8 hrs	N/D	F	3.5 hrs	14.8	E	>16 hrs	N/D	I/D	I/D	I/D	P	24 min	265	I/D	I/D	I/D
Glutaraldehyde (25%)	111-30-8	I/D	I/D	I/D	E	>8 hrs	N/D	E	>8 hrs	N/D	I/D	I/D	I/D	P	I/D	I/D	E	>6 hrs	N/D
Heptane	142-82-5	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	E	>6 hrs	N/D	I/D	I/D	I/D	I/D	I/D	I/D
Hexahydrobenzene	110-82-7	E	>4hrs	N/D	E	>7 hrs	N/D	F	50 min	103.8	E	>8 hrs	N/D	F	I/D	I/D	I/D	I/D	I/D

		Silver Shield			Viton			Butyl			Chemsoft			Nitrile			Natural Rubber		
Chemical Name	CAS No.	D	BT	PR	D	BT	PR	D	BT	PR	D	BT	PR	D	BT	PR	D	BT	PR
Hexahydrophenol	108-93-0	E	>8 hrs	N/D	E	>8 hrs	N/D	E	>11 hrs	N/D	E	>6 hrs	N/D	E	>16 hrs	N/D	I/D	I/D	I/D
Hexamethylene	110-82-7	E	>4hrs	N/D	E	>7 hrs	N/D	F	50 min	103.8	E	>8 hrs	N/D	F	I/D	I/D	I/D	I/D	I/D
Hexanaphthene	110-82-7	E	>4hrs	N/D	E	>7 hrs	N/D	F	50 min	103.8	E	>8 hrs	N/D	F	I/D	I/D	I/D	I/D	I/D
Hexane	110-54-3	E	>8 hrs	N/D	E	>8 hrs	N/D	P	I/D	I/D	E	>6 hrs	N/D	E	I/D	I/D	I/D	I/D	I/D
Hydrochloric Acid (37%)	7647-01-0	E	>8 hrs	N/D	E	I/D	I/D	E	I/D	I/D	E	>6 hrs	N/D	E	>6 hrs	N/D	E	>6 hrs	N/D
Hydrofluoric Acid (48%)	7664-39-3	E	>8 hrs	0.013	G	I/D	I/D	F	I/D	I/D	I/D	I/D	I/D	G	1 hr	0.49	E	7 hrs	0.18
Hydrogen Chloride (gas)	7647-01-0	E	>8 hrs	N/D	E	>8 hrs	N/D	E	>8 hrs	N/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D
Iodomethane	74-88-4	P	4 min	0.026	E	6.3 hrs	0.7	F	55 min	82	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D
Isobutyl Alcohol	78-83-1	E	I/D	I/D	E	>8 hrs	N/D	E	>8 hrs	N/D	E	>8 hrs	N/D	E	>8 hrs	N/D	I/D	I/D	I/D
Isopropyl Alcohol	67-63-0	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	E	>6 hrs	N/D	E	>6 hrs	N/D	G	1.7 hrs	0.42
Ketohexamethylene	108-94-1	E	>8 hrs	N/D	P	29 min	86.3	E	>16 hrs	N/D	I/D	I/D	I/D	P	I/D	I/D	F	2.1 hrs	0.07
Methacrylic Acid	79-41-4	I/D	I/D	I/D	E	>8 hrs	N/D	E	>8 hrs	N/D	I/D	I/D	I/D	F	1.7 hrs	23	I/D	I/D	I/D
Methacrylonitrile	126-98-7	E	I/D	I/D	F	4 min	462	E	>8 hrs	N/D	I/D	I/D	I/D	P	7 min	560	I/D	I/D	I/D
Methanol	67-56-1	E	6 hrs	0.02	F	3 hrs	1	E	>8 hrs	N/D	I/D	I/D	I/D	F	32 min	11.8	F	19 min	1.97
Methenyl Trichloride	67-66-3	E	>8 hrs	N/D	E	9.5 hrs	0.46	I/D	I/D	I/D	I/D	I/D	I/D	P	4 min	352	I/D	I/D	I/D
Methyl Alcohol	67-56-1	E	6 hrs	0.02	F	3 hrs	1	E	>8 hrs	N/D	I/D	I/D	I/D	F	32 min	11.8	F	19 min	1.97
1-Methyl-4-tert-butylbenzene	98-51-1	E	>8 hrs	N/D	E	>8 hrs	N/D	F	1.78 hrs	8	I/D	I/D	I/D	P	I/D	I/D	I/D	I/D	I/D
Methyl Cellosolve	109-86-4	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	F	55 min	13.2	F	45 min	0.56
Methyl Chloride	74-87-3	E	>8 hrs	N/D	E	>8 hrs	N/D	E	>8 hrs	N/D	E	>8 hrs	0.0013	I/D	I/D	I/D	I/D	I/D	I/D
Methyl Chloroform	71-55-6	E	>8 hrs	N/D	E	>15 hrs	N/D	P	I/D	I/D	I/D	I/D	I/D	P	37 min	76.4	I/D	I/D	I/D
Methyl Iodide	74-88-4	P	4 min	0.026	E	6.3 hrs	0.7	F	55 min	82	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D
Methylamine (40% in water)	74-89-5	F	46 min	1.28	E	>16 hrs	N/D	E	>15 hrs	N/D	F	1.7 hr	7	E	>8 hrs	N/D	I/D	I/D	I/D
Methylbenzene	108-88-3	E	>8 hrs	N/D	E	>16 hrs	N/D	P	6 min	511	I/D	I/D	I/D	P	11 min	68.1	P	3 min	82.2
Methylene Chloride	75-09-2	E	>8 hrs	N/D	F	1 hr	7.32	P	I/D	I/D	P	I/D	I/D	P	4 min	766	I/D	I/D	I/D
4,4-Methylene Dianiline	101-77-9	E	>8 hrs	N/D	E	>8 hrs	N/D	E	>8 hrs	N/D	I/D	I/D	I/D	F	I/D	I/D	I/D	I/D	I/D
Monoethanolamine	141-43-5	I/D	I/D	I/D	E	>8 hrs	N/D	E	>8 hrs	N/D	E	>8 hrs	N/D	I/D	I/D	I/D	I/D	I/D	I/D
Morpholine	110-91-8	E	>8 hrs	N/D	G	1.9 hrs	97	E	>16 hrs	N/D	I/D	I/D	I/D	P	48 min	206	I/D	I/D	I/D
Naphtha	8052-41-3	E	>8 hrs	N/D	I/D	I/D	I/D	I/D	I/D	I/D	E	>8 hrs	N/D	E	>6 hrs	N/D	I/D	I/D	I/D
n-Hexane	110-54-3	E	>8 hrs	N/D	E	>8 hrs	N/D	I/D	I/D	I/D	E	>6 hrs	N/D	I/D	I/D	I/D	I/D	I/D	I/D
Nitrobenzene	98-95-3	E	>8 hrs	N/D	E	>8 hrs	N/D	E	>8 hrs	N/D	I/D	I/D	I/D	F	29 min	1.7	P	7 min	8.4
Nitromethane	75-52-5	I/D	I/D	I/D	I/D	I/D	I/D	E	>8 hrs	N/D	I/D	I/D	I/D	I/D	I/D	I/D	P	7 min	2.83
1-Nitropropane	108-03-2	E	>8 hrs	N/D	P	17 min	26.1	E	>8 hrs	N/D	I/D	I/D	I/D	P	12 min	29.5	I/D	I/D	I/D
n-Methyl-2-Pyrrolidone	872-50-4	I/D	I/D	I/D	I/D	I/D	I/D	E	8 hrs	N/D	I/D	I/D	I/D	F	1.45 hrs	0.388	F	1.26 hrs	3.14
n-Propyl Acetate	109-60-4	E	>8 hrs	N/D	I/D	I/D	I/D	F	2.7 hrs	2.86	I/D	I/D	I/D	P	17 min	72.5	I/D	I/D	I/D
Oxalic Acid	144-62-7	E	>8 hrs	N/D	E	>8 hrs	N/D	E	>8 hrs	N/D	I/D	I/D	I/D	G	I/D	I/D	I/D	I/D	I/D

D = Degradation
BT = Breakthrough Time
PR = Permeation Rate

E = Excellent
G = Good
F = Fair
P = Poor

N/D = None Detected
I/D = Insufficient Data




 Good for total immersion
 Good for accidental splash protection and intermittent contact
 Only use with extreme caution. Glove will fail with only short exposure

		Silver Shield			Viton			Butyl			Chemsoft			Nitrile			Natural Rubber		
Chemical Name	CAS No.	D	BT	PR	D	BT	PR	D	BT	PR	D	BT	PR	D	BT	PR	D	BT	PR
p-Dioxane	123-91-1	I/D	I/D	I/D	P	23 min	26.8	E	>20 hrs	N/D	I/D	I/D	I/D	P	28 min	77.1	I/D	I/D	I/D
Perchloric Acid (70%)	7601-90-3	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	E	>8 hrs	N/D	E	>8 hrs	N/D	I/D	I/D	I/D
Perchloroethylene	127-18-4	E	>8 hrs	N/D	E	>17 hrs	N/D	P	I/D	I/D	F	1 hr	3.8	F	1.3 hrs	5.5	I/D	I/D	I/D
Perchloromethane	56-23-5	E	>8 hrs	N/D	E	>13 hrs	N/D	I/D	I/D	I/D	F	1.3 hrs	3.45	F	3.4 hrs	5	I/D	I/D	I/D
Phenol (85% in water)	108-95-2	E	>8 hrs	N/D	E	>15 hrs	N/D	E	>20 hrs	N/D	I/D	I/D	I/D	P	39 min	>1500	F	2.2 hrs	4.64
Phenylamine	62-53-3	E	>8 hrs	N/D	P	6 min	18.7	E	>8 hrs	N/D	I/D	I/D	I/D	F	1.1 hrs	45	I/D	I/D	I/D
Phosphoric Acid (85%)	7664-38-2	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	E	>8 hrs	N/D	E	>8 hrs	N/D	E	>8 hrs	N/D
Pimelic Ketone	108-94-1	E	>8 hrs	N/D	P	29 min	86.3	E	>16 hrs	N/D	I/D	I/D	I/D	I/D	I/D	I/D	F	2.1 hrs	0.07
2-Propanone	67-64-1	E	>8 hrs	N/D	P	2 min	383	E	>8 hrs	N/D	P	1 min	42.3	P	3 min	291	P	10 min	12.2
Propyl Acetate	109-60-4	E	>8 hrs	N/D	P	I/D	I/D	G	2.7 hrs	2.86	I/D	I/D	I/D	P	17 min	72.5	I/D	I/D	I/D
Propyl Alcohol	71-23-8	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	G	3.8 hrs	0.35	E	4.4 hrs	1.1	I/D	I/D	I/D
Propylene Oxide	75-56-9	I/D	I/D	I/D	P	1 min	1790	F	2.2 hrs	7	I/D	I/D	I/D	P	<6 min	>3.9	I/D	I/D	I/D
p-tert-Butyltoluene	98-51-1	E	>8 hrs	N/D	E	>8 hrs	N/D	F	1.78 hrs	8	I/D	I/D	I/D	P	I/D	I/D	I/D	I/D	I/D
Pyridine	110-86-1	I/D	I/D	I/D	P	38 min	74	E	>8 hrs	N/D	I/D	I/D	I/D	P	I/D	I/D	I/D	I/D	I/D
Sodium Hydroxide 50%	1310-73-2	E	>8 hrs	N/D	E	>8 hrs	N/D	E	>8 hrs	N/D	E	>8 hrs	N/D	E	>8 hrs	N/D	E	>8 hrs	N/D
Stoddard Solvent	8052-41-3	E	>8 hrs	N/D	I/D	I/D	I/D	I/D	I/D	I/D	E	>8 hrs	N/D	E	>6 hrs	N/D	I/D	I/D	I/D
Styrene	100-42-5	E	>6 hrs	N/D	E	>6 hrs	N/D	F	35 Mins	0.19	P	16 min	39	P	11 min	>3.35	I/D	I/D	I/D
Sulfuric Acid (50%)	7664-93-9	E	>6 hrs	N/D	E	I/D	I/D	E	I/D	I/D	G	>8 hrs	N/D	G	>6 hrs	N/D	G	>6 hrs	N/D
Sulfuric Acid (93%)	7664-93-9	E	>8 hrs	N/D	E	>8 hrs	N/D	E	>8 hrs	N/D	P	2 min	N/D	F	1.9 hrs	11.4	G	5.1 hrs	N/D
Tetrachloroethylene	127-18-4	E	>8 hrs	N/D	E	>17 hrs	N/D	P	I/D	I/D	F	1 hr	3.8	F	1.3 hrs	5.5	I/D	I/D	I/D
Tetrachloromethane	56-23-5	E	>8 hrs	N/D	E	>13 hrs	N/D	I/D	I/D	I/D	F	1.3 hrs	3.45	F	3.4 hrs	5	I/D	I/D	I/D
Tetrahydrofuran	109-99-9	E	>8 hrs	N/D	P	0 min	327	F	27 min	112	P	I/D	I/D	P	0 min	167	P	5 min	360
Thioglycolic Acid	68-11-1	I/D	I/D	I/D	E	>8 hrs	N/D	E	>8 hrs	N/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D	I/D
Toluene	108-88-3	E	>8 hrs	N/D	E	>16 hrs	N/D	P	6 min	511	P	I/D	I/D	P	11 min	68.1	P	3 min	82.2
Toluene Diisocyanate	584-84-9	E	>8 hrs	N/D	I/D	I/D	I/D	E	I/D	I/D	F	1 hr	2.52	G	I/D	I/D	I/D	I/D	I/D
1,1,1-Trichloroethane	71-55-6	E	>8 hrs	N/D	E	>15 hrs	N/D	P	I/D	I/D	I/D	I/D	I/D	F	37 min	76.4	I/D	I/D	I/D
Trichloroethylene	79-01-6	E	>8 hrs	N/D	E	7.4 hrs	0.24	P	14 min	550	I/D	I/D	I/D	P	4 min	283	P	<5 min	894
Trichloromethane	67-66-3	E	>8 hrs	N/D	E	9.5 hrs	0.46	I/D	I/D	I/D	I/D	I/D	I/D	P	4 min	352	I/D	I/D	I/D
Triethanolamine	102-71-6	I/D	I/D	I/D	I/D	I/D	I/D	E	>8 hrs	N/D	E	>8 hrs	N/D	I/D	I/D	I/D	E	>8 hrs	N/D
Triethylamine	121-44-8	I/D	I/D	I/D	E	>8 hrs	N/D	P	I/D	I/D	E	5.8 hrs	0.18	E	>8 hrs	N/D	I/D	I/D	I/D
Vinegar Naphtha	141-78-6	E	>8 hrs	N/D	P	I/D	I/D	E	7.6 hrs	3.4	I/D	I/D	I/D	P	8 min	145	I/D	I/D	I/D
Vinylstyrene	1321-74-0	E	>8 hrs	N/D	E	>17 hrs	N/D	F	2.2 hrs	238	I/D	I/D	I/D	P	I/D	I/D	I/D	I/D	I/D
Xylene	1330-20-7	E	>8 hrs	N/D	E	>8 hrs	N/D	P	I/D	I/D	P	I/D	I/D	P	21 min	18.5	I/D	I/D	I/D

D = Degradation
BT = Breakthrough Time
PR = Permeation Rate

E = Excellent
G = Good
F = Fair
P = Poor

N/D = None Detected
I/D = Insufficient Data

 Good for total immersion
 Good for accidental splash protection and intermittent contact
 Only use with extreme caution. Glove will fail with only short exposure