## CITY OF LOS ANGELES

**CALIFORNIA** 

ST LOS ANG

ERIC GARCETTI MAYOR DEPARTMENT OF BUILDING AND SAFETY 201 NORTH FIGUEROA STREET LOS ANGELES, CA 90012

OSAMA YOUNAN, P.E.

GENERAL MANAGER SUPERINTENDENT OF BUILDING

JOHN WEIGHT EXECUTIVE OFFICER

GEORGE HOVAGUIMIAN ELVIN W. MOON

JOSELYN GEAGA-ROSENTHAL

BOARD OF

**BUILDING AND SAFETY** 

**COMMISSIONERS** 

VAN AMBATIELOS

JAVIER NUNEZ

Headed Reinforcement Corp. 11200 Condor Avenue Fountain Valley, CA 92708

Attn: Robbie Hall (678) 333-4450

RESEARCH REPORT: RR 25815 (CSI # 03 21 00)

BASED UPON IAPMO EVALUATION REPORT NO. ER-0177

REEVALUATION DUE

DATE: March 01, 2022 Issued date: March 01, 2021 Code: 2020 LABC

**GENERAL APPROVAL** – Technical Modification - HRC 555 Series Headed Reinforcing Bars and 670 Series T-Head (HEADLOCK<sup>TM</sup>) Headed Ends of Concrete Reinforcement

#### **DETAILS**

The above assemblies and/or products are approved when in compliance with the use, description, design, installation, conditions of approval, and identification of Evaluation Report No. ER- 0177, originally issued November 24, 2010, revised November 25, 2020 of the IAPMO-UES Evaluation Services, Incorporated. The report, in its entirety, is attached and made part of this general approval.

The parts of the UES Report, ER-0177, which are stricken out on the attached copy have been removed by the Los Angeles Building Department as not being included in this approval.

#### The approval is subject to the following conditions:

1. Continuous inspection by Deputy Inspectors shall be provided during installations of the headed steel reinforcing bars.

RR 25815 Page **1** of **3** 

- 2. The fabricator, in processing steel for the headed steel reinforcing bars through his works, shall maintain identity of the material and shall maintain suitable procedures and records attesting that the specified grade has been furnished in conformity with the applicable ASTM Standard. The ASTM or other specification designation shall be included near the erection mark on each shipping assembly or important construction component over any shop coat of paint prior to shipment from the fabricator's plant. The fabricator's identification mark system shall be established and on record prior to fabrication. Steel which is not readily identifiable as to grade from marking and test records shall be tested to determine conformity to such standard. The fabricator shall, when requested, furnish an affidavit of compliance with such standard. Test data shall be provided upon request.
- 3. Except as specified herein, installation of the headed steel reinforcing bars shall be in accordance with the manufacturer's specifications. A copy of the specifications shall be provided at the job site and be made available to all Deputy Inspectors on the job.
- 4. Headed steel reinforcing bars locations shall be fully detailed on the plans and approved by the Structural Plan Check Section. The calculations for headed steel reinforcing bars shall be prepared by a Civil or Structural Engineer registered in the State of California.
- 5. Requirements for concrete cover, space between bars or sleeves, and minimum anchor length shall be applicable to headed steel reinforcing bars.
- 6. Headed steel reinforcing bars shall not be used on compression reinforcement and epoxy and other coated bars.
- 7. The design of anchorage to concrete shall comply with section 4.1.2 of attached IAPMO-UES Evaluation Report, ER-0177.
- 7. For use as reinforcement resisting earthquake-induced flexural and axial forces in frame members and boundary elements of special structural walls, the reinforcing bar component of the headed bars shall comply with Section 20.2 of ACI 318-14.
- 8. The use of headed and mechanical anchored deformed reinforcement for lap splices is outside the scope of this approval.
- 9. Special inspections shall be as required per Sections 1704.4 and 1705.3 of the 2020 Los Angeles Building Code. The special inspector is responsible for verifying identification of the headed deformed reinforcing bars, grade and size of reinforcing bars, installation of reinforcing bar splices to the headed deformed reinforcing bars, as well as placement of the headed bars.

Headed Reinforcement Corporation RE: HRC 555 Headed Reinforcing Bars and 670 T-Head Headed Ends of Concrete Reinforcement

#### **DISCUSSION**

The technical modification is to add the HRC® 670 T-Headed Grade 80 bars with diameters #7-18 to the approval, to update the contact person and phone number and to update the report to the 2020 City of Los Angeles Building Code.

This report is in compliance with the 2020 City of Los Angeles Building Code.

This general approval will remain effective provided the Evaluation Report is maintained valid and unrevised with the issuing organization. Any revision to the report must be submitted to this Department for review with appropriate fee to continue the approval of the revised report.

Addressee to whom this Research Report is issued is responsible for providing copies of it, <u>complete with any attachments indicated</u>, to architects, engineers and builders using items approved herein in design or construction which must be approved by Department of Building and Safety Engineers and Inspectors.

This general approval of an equivalent alternate to the Code is only valid where an engineer and/or inspector of this Department has determined that all conditions of this Approval have been met in the project in which it is to be used.

QUAN NGHIEM Chief Engineering Research Section 201 N. Figueroa St., Room 880 Los Angeles, CA 90012 Phone - 213-202-9812 Fax - 213-202-9943

DE RR 25815 TLB2000060 R03/06/2021 ACI 318-14. Section 25.4

Attachment: IAPMO-UES Report No. ER-0177 (5 Pages)

Revised: 11/25/2020

177

Valid Through: 11/30/2021

HEADED REINFORCEMENT CORP. 11200 Condor Avenue

Originally Issued: 11/24/2010

Fountain Valley, CA 92708 800-HRC-6775

www.hrc-usa.com engineer@hrc-usa.com

HRC® 555 SERIES AND HRC® 670 SERIES T-HEAD (HEADLOCK<sup>TM</sup>) HEADED ENDS OF CONCRETE REINFORCEMENT

**CSI DIVISION:** 

03 CONCRETE

**CSI Section:** 

03210 Reinforcing Steel

#### 1.0 SCOPE OF EVALUATION

#### 1.1 Compliance to the following codes:

- 2018, 2015 and 2012 International Building Code<sup>®</sup> (IBC)
- 2018, 2015 and 2012 International Residential Code® (IRC)

#### 1.2 Evaluated in accordance with:

IAPMO ES EC 006

#### 1.3 Properties assessed:

Structural

#### 2.0 PRODUCT USE

The HRC® 555 Series headed reinforcing bars are Class HA headed deformed steel reinforcing bars for concrete reinforcement. The HRC® 670 HeadLock<sup>TM</sup> is an attachable head for deformed steel reinforcing bars for concrete reinforcement. Both products comply with Section 25.4.4 and 25.4.5 of ACI 318-14 and Section 12.6 of ACI 318-11 with Class HA heads for use in developing headed and anchored deformed bars in tension in normal-weight concrete as an alternative to standard hooks or development lengths of straight deformed reinforcing bars.

#### 3.0 PRODUCT DESCRIPTION

#### 3.1 Product information:

**3.1.1 HRC**<sup>®</sup> **555:** The HRC<sup>®</sup> 555 Series are Class HA headed deformed bars complying with the requirements of ASTM A970. HRC<sup>®</sup> 555 Series are integrally factory-forged where the heads are produced by deforming the bar end(s) in a hot forging process. The headed reinforcing steel bars are available in No. 4 (13 mm) through No. 11

(35 mm) sizes. The net head bearing area,  $A_{brg}$ , of the HRC® 555 headed devices exceed four times the nominal cross-sectional area,  $A_b$ , of the reinforcing bar, in conformance with the Class HA Head requirements in Annex A1 of ASTM A970. The HRC® 555 Series is recognized for use with the material, grade, and reinforcing bar sizes listed in Table 1 of this report. The dimensions of the HRC® 555 headed reinforcing bars are shown in Table 2 and Figure 1 of this report.

**3.1.2 HRC**® **670:** The HRC® 670 HeadLock<sup>TM</sup> Series are Class HA heads complying with the requirements of ASTM A970 Annex 1A. The HRC® 670 HeadLock<sup>TM</sup> Series. The HRC® 670 HeadLock<sup>TM</sup> Series are field installed T-Heads used mainly for retrofits and field repairs. The HRC® 670 HeadLock<sup>TM</sup> Series, when connected to the specified reinforcing bars, comply as Class HA in accordance with ASTM A970. HRC® 670 uses a wedged grip system with a spring and tension bolt that is installed on the end of a torch cut, sheared, or saw cut reinforcing bar. The product is available in sizes for use with No. 5 (16 mm) through No. 18 (57 mm) reinforcing bar.

The net head bearing area,  $A_{brg}$ , of the HRC® 670 HeadLock® devices exceed four times the nominal cross-sectional area,  $A_b$ , of the reinforcing bar. The HRC® 670 HeadLock® Series is recognized for use with the material, grade, and reinforcing bar sizes listed in Table 1 of this report. The dimensions of the HRC® 670 HeadLock<sup>TM</sup> headed reinforcing bars are shown in Table 3 and Figure 2 of this report.

**3.2. Material information:** HRC<sup>®</sup> 555 headed ends are manufactured from ASTM A615 or ASTM A706 steel reinforcing bars. HRC<sup>®</sup> 670 HeadLock<sup>TM</sup> T-Heads are manufactured from AISI 1141 and AISI 8620 steel and include a steel spring and a rubber O-ring.

#### 4.0 DESIGN AND INSTALLATION

#### 4.1 Design

**4.1.1 Development Length:** Development lengths shall be determined in accordance with Section 25.4.4 of ACI 318-14 or Section 12.6 of ACI 318-11 for bar sizes No. 4 through No. 11, ASTM A615 and A706 Grade 60 only.

The development length,  $\ell_{dl}$ , in inches, (including modification factors) shall not be less than the larger of  $8d_b$  or 6-inches. The development lengths, in inches, of Class HA headed deformed bars for uncoated ASTM A706 and A615 Grade 60 reinforcing bar are as follows:



The product described in this Uniform Evaluation Service (UES) Report has been evaluated as an alternative material, design or method of construction in order to satisfy and comply with the intent of the provision of the code, as noted in this report, and for at least equivalence to that prescribed in the code in quality, strength, effectiveness, fire resistance, durability and safely, as applicable, in accordance with IBC Section 104.11. This document shall only be reproduced in its entirety.



# **EVALUATION REPORT**

Number:

177

Originally Issued: 11/24/2010 Revised: 11/25/2020 Valid Through: 11/30/2021

Bar Size	f´c (normal-weight concrete), psi							
No.	4,000	5,000	6,000					
4	7.6	6.8	6.2					
5	9.5	8.5	7.7					
6	11.4	10.2	9.3					
7	13.3	11.9	10.8					
8	15.2	13.6	12.4					
9	17.1	15.3	14.0					
10	19.3	17.2	15.7					
11	21.4	19.1	17.5					

The concrete cover for the reinforcement shall be at least  $2d_b$ , and the clear spacing between bars shall be at least  $4d_b$ , in accordance with Section 25.4.4.1 of ACI 318-14 or Section 12.6 of ACI 318-11.

The use of No. 14, No. 18, Grade 75, and Grade 80 bars for development length is outside the scope of this report. The anchorage of No. 14, No. 18, Grade 75 and Grade 80 bars shall be designed in accordance with ACI 318-14 Chapter 17 or ACI 318-11 Appendix D, or otherwise to the satisfaction of the registered design professional and approved by the building official.

The development length,  $\ell_{dt}$ , shall be measured from the critical section as shown in Figure R25.4.4.2a of ACI 318-14 or Figure R12.6(a) of ACI 318-11.

Development lengths specified for the development and splices of reinforcement shall not be subject to a strength reduction factor in accordance with Section 25.4.1.3 of ACI 318-14 or Section 9.3.3 of ACI 318-11.

**4.1.2 Termination of Headed Bars:** When designed in accordance with Section 25.4.4.2 of ACI 318-14 or Section 12.6.2 of ACI 318-11, longitudinal headed deformed bars extending from a beam or a slab terminating at a support member, such as a column, shall extend through the joint to the far face of the confined supporting member in accordance with Figure R25.4.4.2b of ACI 318-14 and Figure R12.6 (b) of ACI 318-11.

Splices of reinforcement to headed deformed reinforcing bars in tension shall comply with Sections 25.5.1 and 25.5.2 of ACI 318-14 or Sections 12.14 and 12.15 of ACI 318-11.

**4.1.3 Design for Anchorage to Concrete:** Where headed reinforcing bars are used as anchorage to concrete, concrete breakout failure shall be considered. For compliance with Section 1909 of the IBC, ACI 318-14 Chapter 17 and ACI 318-11 Appendix D as anchorage to concrete, additional data needs to be prepared by a registered design professional and approved by the building official to justify how the headed bars are substantiated in accordance with Section 17.1.3 of ACI 318-14 or Section D.2.3 of ACI 318-11 or comply with ANSI/ASME B1.1, B18.2.1 and B18.2.6.

**4.2 Installation:** The HRC® 555 and HRC® 670 HeadLock<sup>TM</sup> shall be installed in accordance with HRC's installation instructions, applicable code sections of ACI 318, this evaluation report, and the approved plans. The HRC® 555's forged head is fixed and requires no field assembly.

The HRC® 670 HeadLock<sup>TM</sup> shall be installed by first cutting the reinforcing bar square to the desired length (desired elevation minus the value "X" noted in Table 3) and removing any debris and concrete from the bar end. Any burrs or other imperfections shall be grounded down. With the bolt removed, push the HRC® 670 HeadLock<sup>TM</sup> onto the bar. The bar end shall be against the bolt hole. Reinsert the bolt and apply a torque until the bolt head breaks off.

**4.3 Special Inspection:** Special inspection of the headed bars shall be provided at the jobsite as required by Sections 1704.2 and 1705.3 of the IBC. The special inspector is responsible for verifying identification of the headed deformed reinforcing bars, grade and size of reinforcing bars, installation of reinforcing bar splices to the headed deformed reinforcing bars, as well as placement of the headed bars.

#### **5.0 LIMITATIONS**

The HRC® 555 and HRC® 670 HeadLock<sup>TM</sup> headed bars described in this report comply with, or are suitable alternatives to what is specified in, the codes listed in Section 1.0 of this report, subject to the following limitations:

- **5.1.** The headed bars shall be installed in accordance with the applicable code, manufacturer's installation instructions, and this report. In the event of a conflict, the more restrictive governs.
- **5.2** Anchorage system calculations and installation details shall be designed in conformance with the IBC and ACI 318 by the registered design professional and approved by the building official.
- **5.3** Special inspections shall be provided in accordance with Section 4.3 of this report.
- **5.4** Minimum concrete cover for development shall be in accordance with Sections 20.6 and 25.4.4.1 of ACI 318-14 or Sections 7.7 and 12.6 of ACI 318-11 and shall be measured from the outer surface of the HRC® 555 or HRC® 670 HeadLockTM reinforcing bar's head, as applicable.
- **5.5** Fabricators and fabrication facilities of the HRC<sup>®</sup> 555 Series shall be qualified by HRC and approved by the building official.

177

Originally Issued: 11/24/2010 Revised: 11/25/2020 Valid Through: 11/30/2021

**5.6** For structures regulated by ACI 318-14 Chapter 18 (2018 and 2015 IBC), ACI 318-11 Chapter 21 (2012 IBC), where the HRC® 555 or HRC® 670 HeadLock<sup>TM</sup> headed reinforcing bars resisting earthquake-induced flexure, axial force, or both, in special moment frames, special structural walls, and all components of special structural walls including coupling beams and wall piers, mill certificates shall be submitted to the building official as evidence that the steel reinforcing bars comply with Section 20.2.2.5 of ACI 318-14 or Section 21.1.5.2 of ACI 318-11.


**5.7** The use of headed and mechanical anchored deformed reinforcement for lap splices is outside the scope of this criteria.

#### 6.0 SUBSTANTIATING DATA

Data in accordance with IAPMO UES Evaluation Criteria for Headed and Mechanically Anchored Deformed Reinforcement Bars in Tension (EC 006-2018), approved June 2018. Test reports are from laboratories in compliance with ISO/IEC 17025.

#### 7.0 IDENTIFICATION

HRC® 555 headed ends are packaged with a label bearing the manufacture's name (Headed Reinforcement Corporation), model and size. HRC® 670 HeadLock<sup>TM</sup> T-Heads shall include a marking etched on the top of the product that includes the product name, lot number, and the size of the reinforcing bar the head is to be used with. Both products shall include the unique heat code identification the letter "H" to indicate that the product has been produced to the ASTM A970 Annex A1 specification one of the IAPMO Uniform ES Mark of Conformities shown below and the Uniform Evaluation Report Number (ER-177). Products prepared by officially licensed fabricators, may have additional unique identifiers that corresponds to the fabricator. Either Mark of Conformity may be used as shown below:



IAPMO UES ER-177

Brian Darler

Brian Gerber, P.E., S.E.
Vice President, Technical Operations
Uniform Evaluation Service

Richard Beck, PE, CBO, MCP Vice President, Uniform Evaluation Service

> GP Russ Chaney CEO, The IAPMO Group

For additional information about this evaluation report please visit www.uniform-es.org or email at info@uniform-es.org

177

Originally Issued: 11/24/2010

Revised: 11/25/2020

Valid Through: 11/30/2021

TABLE 1 – EVALUATED PRODUCTS: SIZE AND MATERIAL GRADE<sup>1</sup>

	Compatible Reinforcing bar Sizes (No.)				
Reinforcement Material	HRC® 555 Series	HRC® 670 Series HeadLock <sup>TM</sup>			
ASTM A706/A615 Grade 60	4 - 11	5 - 11			
ASTM A615 Grade 75 <sup>2</sup>	8 - 11				
ASTM A706/615 Grade 80 <sup>2</sup>	8 - 11	7 – 18			

<sup>&</sup>lt;sup>1</sup> Note: For compliance with the IBC and ACI 318-14 Chapter 17 or ACI 318-11 Appendix D as anchorage, additional data needs to be prepared by the registered design professional and approved by the building official to justify how the headed bars are substantiated in accordance with Section 17.1.3 of ACI 318-14 or Section D.2.3 of ACI 318-11. See Section 4.1.3 of this report.


<sup>2</sup> Note: In accordance with Section 25.4.4.1 of ACI 318-14 and Section 12.6 of ACI 318-11 the use of Grade 75 and 80 bars for development length is outside the scope of this report.

TABLE 2 - DIMENSIONS OF HRC 555 HEADED REINFORCING BARS

Dimensions	Bar size	#4	#5	#6	#7	#8	#9	#10	#11
Reinforcing bar	Diameter [in]	0.500	0.625	0.750	0.875	1.000	1.128	1.270	1.410
	Area [in <sup>2</sup> ]	0.20	0.31	0.44	0.60	0.79	1.00	1.27	1.56
Head	*T <sub>min</sub> [in]	0.25	0.31	0.38	0.44	0.50	0.56	0.64	0.70
	D [in]	1.14	1.42	1.69	1.97	2.25	2.56	2.87	3.19
	A <sub>brg</sub> [in <sup>2</sup> ]	0.82	1.27	1.80	2.45	3.18	4.14	5.20	6.43

For SI: 1 inch = 25.4 mm, 1 sq.in. = 645 mm<sup>2</sup>, 1 foot = 305 mm. \* Head thickness shall be no larger than bar diameter

#### FIGURE 1 – HRC® 555 HEADED REINFORCING BARS



177

Originally Issued: 11/24/2010 Revised: 11/25/2020 Valid Through: 11/30/2021

TABLE 3 – DIMENSIONS OF HRC 670 T-HEAD FOR USE WITH REINFORCING BARS

Dimensions	Bar Size	#5	#6	#7	#8	#9	#10	#11	#14	#18
Reinforcing	Diameter	0.625	0.75	0.875	1.0	1.128	1.27	1.41	1.69	2.26
bar	(in)									
	Area	0.31	0.44	0.60	0.79	1.00	1.27	1.56	2.25	4.00
	$(in^2)$									
Head	D <sub>1</sub> (in)	1.5	1.75	2.08	2.375	2.625	3.0	3.5	4.0	5.25
	$D_2(in)$	1.75	1.875	2.25	2.5	2.75	3.25	3.625	4.0	5.25
	D <sub>L</sub> (in)	2.0	2.5	2.875	3.25	3.625	4.0	4.5	5.5	7.25
	L (in)	2.22	2.48	2.8	3.3	3.35	3.7	4.2	4.9	6.25
	X (in)	0.5	0.5	0.625	0.625	0.75	0.875	1.0	1.07	1.07
	<b>Bolt</b> Socket	3/4	3/4	3/4	1	1	$1^{1}/_{4}$	$1^{1}/_{2}$	$1^{1}/_{2}$	$1^{1}/_{2}$
	Size (in)									

For SI: 1 inch = 25.4 mm, 1 sq.in. = 645 mm<sup>2</sup>, 1 foot = 305 mm.


Clean debris and concrete off

bar end. Grind down burrs and

imperfections if necessary.

### FIGURE 2 - HRC® 670 HeadLock<sup>TM</sup> T-HEAD

## No Special Equipment Needed



without bolt, until it bottoms

out. Verify bar end is up

against bolt hole. Hammer

down if necessary.

torque until bolt head

breaks off.\*\*