

**IN SITU ENZYMATIC SYNTHESIS
OF COLLAGEN-CHITOSAN HYDROGEL
USING ULTRASONIC PRETREATED
COLLAGEN**

LAU SIN MUN

UNIVERSITI SAINS MALAYSIA

2019

**IN SITU ENZYMATIC SYNTHESIS OF
COLLAGEN-CHITOSAN HYDROGEL USING ULTRASONIC
PRETREATED COLLAGEN**

by

LAU SIN MUN

**Thesis submitted in fulfilment of the
requirements for the degree of
Master of Science**

February 2019

ACKNOWLEDGEMENT

First of all, I would like to express my gratitude to my supervisor, Dr. Masrina Mohd Nadzir, who has guided, supported and inspired me to accomplish this Master research study. I appreciate her efforts on spending time to guide and share knowledge with me in completing this research work. My appreciation also goes to my co-supervisor, Prof. Dr. Azlina bt. Harun @ Kamaruddin, for her guidance and advice throughout my studies. Sincere gratitude to my field supervisor, Dr. Shiplu Roy Chowdhury, who has provided me continuous supports and helps during my attachment in Universiti Kebangsaan Malaysia. To my family and friends, thanks for their love, encouragement and understandings that motivate me to complete the experimental work successfully. Special thanks to my mother, Leow Kooi Leng, who always give me spiritual support and willing to share my difficulties in my research study.

In addition, I would like to thank all technicians and office staffs from School of Chemical Engineering, Universiti Sains Malaysia (USM), who have helped me throughout the progress of this work. I am also very much indebted to technicians from School of Biological Sciences, USM and Science Engineering Research Center (SERC), USM who assisted me in conducting characterization analysis. Last but not least, the financial support provided by the Ministry of Higher Education Malaysia and USM under the Fundamental Research Grant Scheme and Research University Grant respectively are acknowledged.

Lau Sin Mun

February 2019

TABLE OF CONTENTS

	Page
ACKNOWLEDGEMENT	ii
TABLE OF CONTENTS	iii
LIST OF TABLES	viii
LIST OF FIGURES	ix
LIST OF PLATES	xiii
LIST OF ABBREVIATIONS	xiv
LIST OF SYMBOLS	xvi
ABSTRAK	xvii
ASBTRACT	xix
CHAPTER ONE: INTRODUCTION	
1.1 Development of injectable hydrogels	1
1.2 Problem statement	3
1.3 Objectives	4
1.4 Scope of study	5
1.5 Thesis organization	6
CHAPTER TWO: LITERATURE REVIEW	
2.1 Biomaterials for biomedical applications	8
2.1.1 Collagen	10
2.1.2 Chitosan	11
2.2 Hydrogels	13
2.2.1 Composite hydrogels	14

2.3	<i>In situ</i> forming hydrogels	16
2.3.1	Characteristic of <i>in situ</i> forming hydrogels	17
2.4	Crosslinking methods	20
2.4.1	Physical crosslinking	20
2.4.2	Chemical crosslinking	24
2.4.3	Limitation of physical and chemical crosslinking	28
2.4.4	Enzymatic crosslinking	29
2.5	Synthesis of <i>in situ</i> forming conjugate hydrogels	32
2.5.1	Conjugation of phenolic hydroxyl groups	32
2.5.2	HRP-catalyzed crosslinking reaction	35

CHAPTER THREE: MATERIALS AND METHODS

3.1	Materials and Chemicals	47
3.2	Experimental flow chart	50
3.3	Experimental procedure	51
3.3.1	Pre-treatment of collagen solution	51
3.3.2	Preparation of collagen-chitosan composite	51
3.3.3	Preparation of composite with Ph moieties	52
3.4	Analytical techniques	53
3.4.1	Transmission Electron Microscope (TEM) analysis of collagen fibrils	53
3.4.2	Gelation time of Col-Chit-Ph	54
3.4.3	<i>In vitro</i> cytotoxicity evaluation of conjugate hydrogels	55
3.4.3.1	Collagen-chitosan-Ph hydrogel preparation	55
3.4.3.2	Preparation of F12: Dulbecco's Modified	56

	Eagles's Medium (F12: DMEM) with supplements	
3.4.3.3	Preparation of Dulbecco's Phosphate Buffered Saline (DPBS)	56
3.4.3.4	Cell trypsinization	57
3.4.3.5	Cell counting	58
3.4.3.6	Cell culture on hydrogel	58
3.4.3.7	MTT- based cytotoxicity assay	59
3.4.4	Mechanical properties of conjugate hydrogels	60
3.4.5	Porosity of conjugate hydrogels	61
3.4.6	Morphology analysis of conjugate hydrogels	61
3.4.7	Swelling properties of conjugate hydrogels	62
3.4.8	Degradation of conjugate hydrogels	62
3.5	Statistical analysis	63

CHAPTER FOUR: RESULTS AND DISCUSSIONS

4.1	Ultrasonic effect on collagen fibrils	64
4.2	Physical characterization	67
4.2.1	Gelation of conjugate hydrogels	67
4.2.2	Influence of HRP on gelation time	72
4.2.3	Influence of H ₂ O ₂ on gelation time	74
4.2.4	Influence of temperature on gelation time	75
4.2.5	Influence of Col:Chit ratio on gelation time	77
4.3	<i>In vitro</i> cytotoxicity evaluation	79
4.3.1	Influence of Col:Chit ratio on efficiency of cell attachment	79

	to conjugate hydrogels	
4.3.2	Influence of Col:Chit ratio on cell growth rate	81
4.4	Mechanical characterization	83
4.4.1	Influence of Col:Chit ratio on bloom strength of conjugate hydrogels	84
4.5	Porosity comparisons among conjugate hydrogels with different Col:Chit ratios	86
4.6	Surface morphological analysis of conjugate hydrogels with different Col:Chit ratios	88
4.7	Swelling properties of injectable hydrogels	92
4.8	Degradation properties of injectable hydrogels	95
4.8.1	Influence of Col:Chit ratio on degradation of conjugate hydrogels	95
4.9	Potential of Col-Chit-Ph hydrogels in biomedical fields	100
 CHAPTER FIVE: CONCLUSIONS AND RECOMMENDATIONS		
5.1	Conclusions	102
5.2	Recommendations	104
 REFERENCES		106
 APPENDICES		
Appendix A: The reaction scheme of hydrolysis of <i>o</i> -acylisourea and intramolecular rearrangement of <i>o</i> -acylisourea		

Appendix B: Calculation of total number of cells and volume of culture
medium needed to suspend cells

Appendix C: Preparation of Simulated Body Fluid (SBF) for degradation
studies

LIST OF PUBLICATIONS

LIST OF TABLES

		Page
Table 2.1	Comparison between natural and synthetic biomaterials	9
Table 2.2	Physically crosslinked hydrogels	21
Table 2.3	Chemically crosslinked hydrogels	25
Table 2.4	Type of enzymes used for enzymatic crosslinking reactions	30
Table 2.5	HRP-catalysed crosslinking hydrogels	39
Table 3.1	List of chemicals	48
Table 3.2	List of equipment used for research work	49
Table 3.3	Preparation of F12: DMEM with supplements	56

LIST OF FIGURES

		Page
Figure 2.1	The triple helical structure of collagen (Samal et al., 2012).	10
Figure 2.2	The chemical structure of chitosan (Sakai et al., 2009d).	12
Figure 2.3	EDC reacts with 3-(<i>p</i> -hydroxyphenyl) propionic acid to form an active α -acylisourea intermediate (Hermanson, 2008).	33
Figure 2.4	The sulfo-NHS (i) reacts with <i>o</i> -acylisourea intermediate (ii) to form sulfo-NHS ester (iii) and isourea by-product (iv) (Hermanson, 2008).	34
Figure 2.5	The amines on polymer chain (i) make nucleophilic attack on carbonyl group of sulfo-HNS ester (ii), generating a stable amide linkage on polymer chain (iii) and the sulfo-NHS group leaves (iv) (Hermanson, 2008, Darr & Calabro, 2009). This result in conjugation of phenolic hydroxyl groups on polymer.	35
Figure 2.6	Radical transfers from the active sites of HRP to hydroxyl group in the phenol to initiate the phenol polymerization (Kawakita, 2012).	36
Figure 2.7	The numbers of hydroxyl groups and alkyl groups in the aromatic ring of polymer chains influence the receipt of radicals, resulting in producing different kinds of polyphenols (Kawakita, 2012).	37
Figure 2.8	The phenolic hydroxyl groups on polymer chain linked at the aromatic ring by C-C and C-O bonds via HRP-catalyzed crosslinking reaction in the presence of H ₂ O ₂ (Lee <i>et al.</i> , 2008).	37
Figure 3.1	Flowchart of the overall experimental studies.	50
Figure 3.2	Schematic diagram of experimental setup for conjugation of Ph groups to Col-Chit composite and Chit solution: (1) magnetic stirrer; (2) stir bar; (3) cooling jacket; (4) beaker; (5) insulated recirculating fluid connection hose; (6) recirculating chiller.	52

Figure 4.1	The effect of ultrasonication on collagen fibrils at collagen concentration (w/v) of 0.15% (a, b) and 0.4% (c, d). The collagen fibrils as shown in (a, c) were without ultrasonic treatment and (b, d) were treated with ultrasonic. The scale bar shows 2 μm .	65
Figure 4.2	The structure of collagen-chitosan composite adapted from Sakai et al. (2009) and Samal et al. (2012). Tangsadthakun et al. (2007) speculated that collagen-chitosan composite is formed by electrostatic interactions. Findings of Wang et al. (2011) further supported this evidence.	69
Figure 4.3	The simplified structure of collagen-chitosan (Col-Chit) composite adapted from Wang et al. (2011).	69
Figure 4.4	The Col-Chit composite (a) reacted with ρHP (b) to form Col-Chit conjugate (Col-Chit-Ph) (c) via carbodiimide-mediated condensation (Sakai <i>et al.</i> , 2009).	70
Figure 4.5	In the presence of HRP and H_2O_2 , the conjugates (a) were crosslinked between each other either through carbon-carbon bond (b) or carbon oxygen bond (c). This oxidative coupling reactions of phenol groups resulted in hydrogel formation (Lee <i>et al.</i> , 2008).	71
Figure 4.6	The gelation time of conjugate hydrogels with Col:Chit ratio of 4:1, 3:2, 1:1 and Chit at different concentration of HRP. The data represent the mean values with standard deviation from triplicate experiments. The boxed region on the figure (A) is highlighted by the magnifications (A-1).	72
Figure 4.7	The higher concentration of HRP provided increased number of radicals to phenolic hydroxyl group (b) from its active site (a), hence enhanced the efficiency of oxidative coupling reaction of polyphenols for hydrogel formation (Kawakita, 2012).	73
Figure 4.8	The gelation time of conjugate hydrogels with Col:Chit ratio of 4:1, 3:2, 1:1 and Chit at different concentration of H_2O_2 . The data represent the mean values with standard deviation from triplicate experiments. The boxed region on the figure (B) is highlighted by the magnifications (B-1).	74
Figure 4.9	Horseradish peroxidase (a) was irreversibly inactivated when exposed to high concentrations of H_2O_2 . Active enzyme intermediate compound (b) reacted with excess peroxide to	75

form inactive species, where iron was released (c) from HRP molecule as a result of heme destruction (Valderrama et al., 2002).

Figure 4.10	The gelation time of conjugate hydrogels with Col:Chit ratio of 4:1, 3:2, 1:1 and Chit at different temperature. The data represent the mean values with standard deviation from triplicate experiments. The boxed region on the figure (C) is highlighted by the magnifications (C-1).	76
Figure 4.11	Chitosan could provide additional amino groups (a) to function as binding sites for phenolic hydroxyl groups (Ma et al., 2003). Hence, higher composition of chitosan enhanced the hydrogel formation.	78
Figure 4.12	The efficiency of cell attachment on conjugate hydrogels on 1 st day and 5 th day relative to 2D cell attachment on 1 st day. The data represent the mean values with standard deviation from triplicate experiments. The statistically significant differences among the data sets were assessed by the student's <i>t</i> -test (* <i>p</i> < 0.01).	79
Figure 4.13	The cell growth rate on conjugate hydrogels after 5 days incubation. The data represent the mean values with standard deviation from triplicate experiments. The statistically significant differences among the data sets were assessed by the student's <i>t</i> -test (* <i>p</i> < 0.01).	82
Figure 4.14	The bloom strength of conjugate hydrogels with Col:Chit ratio of 3:2 at different concentration of HRP. The data represent the mean values with standard deviation from triplicate experiments.	84
Figure 4.15	The bloom strength of conjugate hydrogels at hydrogel formation using 3 unit/ml of HRP and 1 mM of H ₂ O ₂ . The data represent the mean values with standard deviation from triplicate experiments. The statistically significant differences among the data sets were assessed by the student's <i>t</i> -test (* <i>p</i> < 0.01).	85
Figure 4.16	The porosity of conjugate hydrogels, where hydrogel was formed using 3 unit/ml of HRP and 1 mM of H ₂ O ₂ . The data represent the mean values with standard deviation from triplicate experiments. The statistically significant differences among the data sets were assessed by the student's <i>t</i> -test (* <i>p</i> < 0.01, ** <i>p</i> < 0.05).	87

Figure 4.17	The FESEM image of Col-Chit-Ph hydrogel with Col:Chit ratio of 3:2.	89
Figure 4.18	The FESEM image of Col-Chit-Ph hydrogel with Col:Chit ratio of 4:1.	90
Figure 4.19	The FESEM image of Col-Chit-Ph hydrogel with Col:Chit ratio of 1:1.	91
Figure 4.20	The FESEM image of Chit conjugate hydrogel.	92
Figure 4.21	The percentage of swelling of conjugate hydrogels with Col:Chit ratio of 4:1, 3:2, 1:1 and Chit for period of 120 minutes. The data represent the mean values with standard deviation from triplicate experiments.	93
Figure 4.22	The percentage of degradation of conjugate hydrogels with Col:Chit ratio of 3:2, 1:1 and Chit at 1 st and 2 nd week. The data represent the mean values with standard deviation from triplicate experiments. The statistically significant differences among the data sets were assessed by the student's <i>t</i> -test (* <i>p</i> < 0.01, ** <i>p</i> < 0.05).	96

LIST OF PLATES

		Page
Plate 4.1	The image of conjugates at 37 °C immediately after addition of HRP and H ₂ O ₂ for samples with Col:Chit ratio of (a) 4:1, (b) 3:2 and (c) 1:1. Image of gelation at 5 minutes for the respective samples are shown in (e), (f) and (g). Chit-Ph sample was used as control (d, h).	67
Plate 4.2	The image of inverse tube gelation at 5 minutes after addition of HRP and H ₂ O ₂ to the conjugate samples. The samples are conjugates with Col:Chit ratio of 4:1, 3:2 and 1:1.	68
Plate 4.3	The degradation state of conjugate hydrogels with collagen to chitosan ratio of 3:2 (a, b, c, d), 1:1 (e, f, g, h) and Chit (i, j, k, l) at initial, 1 st , 2 nd and 3 rd week. Here, all hydrogels lost structure in the 3 rd week.	99

LIST OF ABBREVIATIONS

ρHP	3-(4-Hydroxyphenyl)-propionic acid
AA	Antibiotic-antimycotic
DCC	Dicyclohexylcarbodiimide
DIC	N,N'-diisopropylcarbodiimide
DPBS	Dulbecco's phosphate buffered saline
ECM	Extracellular matrix
EDC	1-ethyl-3-(3-dimethylaminopropyl) carbodiimide
EDTA	Ethylenediaminetetraacetic acid
F12: DMEM	F12: Dulbecco's Modified Eagles's Medium
FBS	Fetal bovine serum
FESEM	Field emission scanning electron microscope
HDF	Human dermal fibroblast
HEPES	4-(2-hydroxyethyl)-1-piperazineethanesulfonic acid
HLC	Human-like collagen
HRP	Horseradish peroxidase
MES	Morpholinoethanesulfonic acid
MSCs	Mesenchymal stem cells
MTT	3-(4,5-dimethylthiazol-2-yl)-2,5-diphenyltetrazolium bromide
PBS	Phosphate buffered saline
PCL	Poly(ε-caprolactone)
PGA	Poly(glycolic acid)
PEG	Poly(ethylene glycol)
PEGDA	Poly(ethylene-glycol)-diacrylate

PEGDMA	Poly(ethylene glycol)-dimethacrylate
PLA	Poly(lactic acid)
PLGA	Poly(lactic acid- <i>co</i> -glycolic acid)
PNIPAM	Poly(N-isopropylacrylamide)
SBF	Simulated body fluid
SDS	Sodium dodecyl sulphate
SDS-PAGE	Sodium dodecyl sulfate polyacrylamide gel electrophoresis
SMOs	Sulfamethazine oligomers
Sulfo-NHS	N-hydroxysulfosuccinimide
TEM	Transmission electron microscope
UV-Vis	Ultraviolet-visible
2D	Two dimensional
3D	Three dimensional

LIST OF SYMBOLS

A_{sample}	Absorbance value of cell attached to conjugate hydrogels
A_{2D}	Absorbance value of two dimensional polystyrene surfaces
M_1	Mass of hydrogel before immersion in ethanol
M_2	Mass of hydrogel after immersion in ethanol
P	Density of absolute ethanol
V	Volume of hydrogel
W_b	Water-swollen weight of hydrogel
W_a	Initial weight of hydrogel
W_1	Initial weight of hydrogel
W_2	Final weight of hydrogel

**SINTESIS IN SITU SECARA ENZIMATIK BAGI HIDROGEL KOLAGEN-
KITOSAN MENGGUNAKAN KOLAGEN DIPRARAWAT DENGAN
ULTRASONIK**

ABSTRAK

Beberapa tahun kebelakangan ini, hidrogel suntik telah menunjukkan potensi yang besar untuk aplikasi bioperubatan kerana mempunyai ciri-ciri yang jelas berbeza, iaitu penggelan *in situ*. Dalam kajian ini, rawatan ultrasonik diperkenalkan untuk merawat kolagen daripada tendon untuk mengurangkan saiz fibril dan mencegah agregasi fibril. Kolagen (Kol) yang diperawat dengan ultrasonik telah digabungkan dengan kitosan (Kit) untuk meningkatkan sifat fizikal hidrogel. Komposit hidrogel dibentuk oleh gabungan oksidatif kumpulan fenolik hidroksil (Ph) dalam rangkaian polimer dengan menggunakan peroksidase lobak kuda (HRP) dan hidrogen peroksida (H_2O_2). Kol-Kit-Ph yang terhasil dapat membentuk hidrogel yang cepat melalui tindak balas sambung silang yang dimangkin oleh peroksidase. Konsentrasi HRP dan H_2O_2 didapati mempengaruhi masa penggelan Kol-Kit-Ph. Selain itu, nisbah Kolagen kepada Kitosan (Kol:Kit) didapati mempengaruhi ciri fizikal, *in vitro* dan mekanikal hidrogel komposit dengan ketara. Hidrogel dengan komposisi chitosan yang lebih tinggi mempunyai penggelan yang lebih cepat, kekuatan mekanikal yang lebih tinggi, dan degradabiliti yang lebih rendah, tetapi menghasilkan keliangan matriks hidrogel yang lebih rendah. Keputusan yang diperolehi dalam kajian ini menunjukkan kepentingan nisbah kitosan kepada komposit hidrogel suntikan Kol-Kit-Ph. Keputusan yang paling ketara diperolehi dalam konjugat hidrogel dengan nisbah Kol:Khit 3:2, yang mempunyai kadar

pertumbuhan sel tertinggi berbanding yang lain selepas 5 hari inkubasi. Oleh itu, hidrogel ini mempunyai potensi untuk digunakan dalam bidang bioperubatan kerana ia stabil dari segi mekanikal dan menyokong fungsi selular.

IN SITU ENZYMATIC SYNTHESIS OF COLLAGEN-CHITOSAN HYDROGEL USING ULTRASONIC PRETREATED COLLAGEN

ABSTRACT

In recent years, injectable hydrogel has shown great potential for biomedical applications owing to its distinct properties of *in situ* gelation. In this research, ultrasonication was introduced to pretreat tendon collagen used in the project to reduce the size of fibrils and prevent fibril aggregation. The pretreated collagen (Col) was combined with chitosan (Chit) to improve the physical properties of hydrogels. Composite hydrogel was formed by oxidative coupling of the phenolic hydroxyl (Ph) groups in polymer chains using horseradish peroxidase (HRP) and hydrogen peroxide (H_2O_2). The resulting Col-Chit-Ph solutions were able to form rapid hydrogel via peroxidase-catalyzed crosslinking reaction. The concentration of HRP and H_2O_2 affected the gelation time of Col-Chit-Ph hydrogels. Besides, the Col to Chit (Col:Chit) ratio also significantly influenced the physical, *in vitro* and mechanical characteristics of composite hydrogels. The hydrogel with a higher composition of chitosan has faster gelation, higher mechanical strength, and lower degradability, but resulted in lower porosity of the hydrogel matrix. The results obtained in this study reveal the importance of the chitosan ratio to the Col-Chit-Ph injectable hydrogel composite. The most significant results were obtained in the conjugate hydrogel with Col:Chit ratio of 3:2, which has the highest cell growth rate compared to others after 5 days of incubations. Hence, this hydrogel has the potential for use in the biomedical fields as it is mechanically stable and supports cellular functions.

CHAPTER ONE

INTRODUCTION

1.1 Development of injectable hydrogels

Injectable hydrogel, which is also known as *in situ* forming hydrogel, has attracted growing interest in biomedical fields recently. Numerous studies on adapting injectable hydrogels as biomaterials have been reported owing to its ability to undergo an *in situ* solution to gel transition when administrated into the body (Liu et al., 2016). When compared to preformed hydrogels transplantation, injectable systems are more desirable as they allow accurate filling of irregular-shaped defects by simple injection of the hydrogel precursor solution to defect site. Injectable hydrogels can be fabricated by several crosslinking methods, mainly classified into physical and chemical crosslinking. These conventional crosslinking methods generally exhibit limitation of operational complexity, low stability, inefficiency coupling reactions and potential cytotoxic effects. Instead, enzymatic crosslinking method is considered as an effective route for development of injectable *in situ* forming hydrogels due to its high site specificity, rapid gelation and relatively mild reaction conditions that are suitable for living cells (Liu et al., 2017). Besides, undesirable side effects to cells can be prevented owing to the substrate specificity of the enzyme. In this study, an injectable enzymatically crosslinked hydrogels was synthesized via horseradish peroxidase (HRP) catalyzed crosslinking reaction in the presence of hydrogen peroxide (H₂O₂).

In addition to the crosslinking method, the biomaterials used for developing injectable hydrogels are of great importance (Heydarkhan-Hagvall et al., 2008). A

wide range of biomaterials, either naturally or synthetically-derived, have been exploited for biomedical uses. Naturally-derived biomaterials are the most common biomaterials used for synthesis of injectable hydrogels due to its intrinsic characteristic that promotes a better interaction with cells (Dhandayuthapani et al., 2011). The natural materials used as injectable hydrogels include collagen, gelatin, chitosan, fibrin, alginate, heparin, hyaluronic acid and chondroitin sulphate (Liu et al., 2017). Among these natural biomaterials, collagen is well-known for diverse biomedical applications owing to its biocompatibility, biodegradability and weak antigenic properties. It has been widely investigated for potential use as surgical suture, hemostatic agents, wound dressings and injectable biomaterials (Miller et al., 1964, Cameron, 1978, Ruszczak, 2003, Kuo et al., 2015).

In this study, collagen-based injectable hydrogel was prepared by integrating collagen with chitosan. Chitosan is a biomaterial known for being non-toxic, contains antibacterial properties and has structural similarity to glucosaminoglycans (GAGs) of the extracellular matrix. Previous studies confirmed that the combination of chitosan with collagen could improve the physical properties of injectable hydrogels (Chen et al., 2005). Nevertheless, there is no other research reported about the fabrication of this collagen (Col)-chitosan (Chit) composite hydrogel conjugated with phenolic hydroxyl (Ph) groups. The injectable Col-Chit conjugate hydrogels fabricated in this work may offer unique mechanical and biological properties for potential use in biomedical applications.

1.2 Problem Statement

Collagen has been considered as the most popular biomaterials in biomedical fields due to its excellent biocompatibility, biodegradability and weakly antigenic properties. The advantages of collagen have been evidenced by extensive investigation, mainly as wound dressings, tissue engineered scaffolds or matrices for drug delivery (Ruszczak, 2003, Lee et al., 2001, Wallace & Rosenblatt, 2003). In spite of the many advantages of collagen, this natural material has poor physical characteristic and rapid degradation rate that limit their practical use. Its mechanical strength is insufficient to maintain the structural stability of scaffolding materials, such as collagen hydrogels (Tangsadthakun et al., 2007). The composite of collagen with chitosan could overcome the limitations of hydrogels fabricated with collagen alone (Lee et al., 2001). However, collagen-chitosan composites do not exist together as blends in nature. The composite hydrogel from these two materials could resemble the main features of ECM, where collagen fibrils provide an excellent environment for cell activity while chitosan improves the mechanical properties of the hydrogel.

The collagen used in this study was extracted from ovine tendon, which is typically discarded as waste. Collagen extracted from ovine tendon is considered as cheap source of raw materials and large quantities of collagen can be isolated and purified for research purposes. However, compared to epidermal collagen fibrils which was proposed by Kuo et al. (2015) for the synthesis of injectable collagen-phenolic hydroxyl (collagen-Ph) hydrogel, tendon collagen fibrils were found to have limitations in terms of having large fibrils and aggregation of fibrils (Gathercole et al., 1987). The large collagen fibrils limit modifications that could be done to it, such as the conjugation of phenolic hydroxyl groups conducted in the current study.

Preliminary work on the present study showed that untreated ovine tendon collagen not only did not mix homogeneously with chitosan but also failed to gel *in situ*. Thus, an ultrasonic pretreatment was introduced to reduce the fibrils diameter and prevent collagen fibrils aggregation. Furthermore, the composite of ultrasonic pretreated collagen and chitosan, conjugated with phenolic hydroxyl (Ph) groups is novel for fabrication of *in situ* enzymatically crosslinked hydrogels. This ultrasonic pretreatment could be applied in biomedical applications when using collagen extracted from sources that will yield collagen with large fibrils.

1.3 Objectives

The primary aim of this study is to develop a novel *in situ* forming collagen-chitosan conjugates (Col-Chit-Ph) hydrogel through HRP-catalyzed crosslinking reaction.

The specific objectives are:

- 1) To study the effect of ultrasonication on the diameter and distribution of collagen fibrils
- 2) To study the effect of horseradish peroxidase and H₂O₂ concentrations on the *in situ* gelation of collagen-chitosan composite
- 3) To evaluate the physical, *in vitro* and mechanical characteristics of composite hydrogels at different Col:Chit ratio