Physical Aspects of Polymer Self-Assembly

P. R. Sundararajan



Physical Aspects of Polymer Self-Assembly

Physical Aspects of Polymer Self-Assembly

P. R. Sundararajan



Copyright © 2017 by John Wiley & Sons, Inc. All rights reserved

Published by John Wiley & Sons, Inc., Hoboken, New Jersey Published simultaneously in Canada

No part of this publication may be reproduced, stored in a retrieval system, or transmitted in any form or by any means, electronic, mechanical, photocopying, recording, scanning, or otherwise, except as permitted under Section 107 or 108 of the 1976 United States Copyright Act, without either the prior written permission of the Publisher, or authorization through payment of the appropriate per-copy fee to the Copyright Clearance Center, Inc., 222 Rosewood Drive, Danvers, MA 01923, (978) 750-8400, fax (978) 750-4470, or on the web at www.copyright.com. Requests to the Publisher for permission should be addressed to the Permissions Department, John Wiley & Sons, Inc., 111 River Street, Hoboken, NJ 07030, (201) 748-6011, fax (201) 748-6008, or online at http://www.wiley.com/go/permissions.

Limit of Liability/Disclaimer of Warranty: While the publisher and author have used their best efforts in preparing this book, they make no representations or warranties with respect to the accuracy or completeness of the contents of this book and specifically disclaim any implied warranties of merchantability or fitness for a particular purpose. No warranty may be created or extended by sales representatives or written sales materials. The advice and strategies contained herein may not be suitable for your situation. You should consult with a professional where appropriate. Neither the publisher nor author shall be liable for any loss of profit or any other commercial damages, including but not limited to special, incidental, consequential, or other damages.

For general information on our other products and services or for technical support, please contact our Customer Care Department within the United States at (800) 762-2974, outside the United States at (317) 572-3993 or fax (317) 572-4002.

Wiley also publishes its books in a variety of electronic formats. Some content that appears in print may not be available in electronic formats. For more information about Wiley products, visit our web site at www.wiley.com.

Library of Congress Cataloging-in-Publication Data

Names: Sundararajan, P. R., author. Title: Physical aspects of polymer self-assembly / P. R. Sundararajan. Description: Hoboken, New Jersey : John Wiley & Sons, 2017. | Includes bibliographical references and index. Identifiers: LCCN 2016036353 (print) | LCCN 2016049189 (ebook) |

ISBN 9781118543788 (cloth) | ISBN 9781118994337 (pdf) | ISBN 9781118994399 (epub) Subjects: LCSH: Self-assembly (Chemistry) | Polymers–Properties. Classification: LCC QD475 .S86 2017 (print) | LCC QD475 (ebook) | DDC 547/.28–dc23 LC record available at https://lccn.loc.gov/2016036353

Cover Illustrations Credits: Clockwise from bottom right: Fig 7.22 (d), reprinted with permission from Ref. 73, Chapter 7, Copyright (2012) Royal Society of Chemistry; Fig. 4.29 (b) reprinted with permission from Ref. 57, Chapter 4, Copyright (2013) Elsevier; Fig. 7.31 (c), reprinted with permission from Ref. 86, Chapter 7, Copyright (2015) Elsevier; Fig. 4.25 (a) Reprinted with permission from Ref. 40, Chapter 4, Copyright (2012) Elsevier.

Printed in the United States of America

Set in 10/12pt Warnock by SPi Global, Pondicherry, India

 $10 \quad 9 \quad 8 \quad 7 \quad 6 \quad 5 \quad 4 \quad 3 \quad 2 \quad 1$

To my wife Kumuda

Contents

Preface xi

- 1 Introduction 1
- 1.1 Polymer Tacticity 1
- 1.2 Big versus Small 5
- 1.3 Entanglement 5
- 1.4 Excluded Volume 8
- 1.5 Free Volume 10
- 1.6 Self-Assembly 10
- 1.7 Polymer Self-Assembly *12* References *13*

2 Molecular Forces 17

- 2.1 Van der Waals Interaction 17
- 2.2 Hydrogen Bond 21
- 2.3 C—H··· π Interaction 27
- 2.4 Halogen Bond 29
- 2.5 Other Hydrogen Bonds 30
- 2.6 Coulombic Interaction *31* References *33*

3 Features of Self-Assembly 37

- 3.1 Self-Sorting—Small Molecules 37
- 3.2 Polymer Self-Sorting 43
- 3.3 Concentration-Dependent Association 48
- 3.4 Polymer–Guest Molecule Recognition 49
- 3.5 Sergeant–Soldier Phenomenon 55
- 3.6 Majority Rules 61
- 3.7 Chain Folding 65

- viii Contents
 - 3.8 Foldamers 79
 - 3.9 Single Chain Polymer Crystals and Nanoparticles 91
 References 99
 Further Reading 104

4 Supramolecular Macromolecules and Polymers 105

- 4.1 Supramolecular Macromolecules 105
- 4.2 Supramolecular Polymers *110*
- 4.3 Modular Supramolecules 123
- 4.4 Solvent Influence 127
- 4.5 Comb Polymers 140 References 149 Further Reading 152

5 Block Copolymers 153

- 5.1 Theoretical Aspects 153
- 5.2 Diblock Copolymers 158
- 5.3 Organic/Inorganic Diblocks 165
- 5.4 Blends of Diblock Copolymers 170
- 5.5 Diblock/Homopolymer Blends 172
- 5.6 BCP/Small-Molecular Supramolecular Association 175
- 5.7 Triblock Copolymers 177
- 5.8 Some Applications of Gyroid Morphology 190
- 5.9 Graphoepitaxy 201
- 5.10 Porous Structures 211
- 5.11 Crystalline Block Copolymers 223
- 5.12 Nanotechnology 223 References 225 Further Reading 230

6 Rotaxanes and Polyrotaxanes 231

- 6.1 Definitions and Early Work 231
- 6.2 Cyclodextrins for Inclusion 237
- 6.3 Selective Threading 244
- 6.4 Micelles of Double-Hydrophilic Block Copolymers via Rotaxane Formation 249
- 6.5 Homopolymer Micelles 252
- 6.6 Linear and Cyclic PDMS 253
- 6.7 Abrasion Resistance 254
- 6.8 Beyond Linear Polymers and α -, β -, and γ -CDs 256
- 6.9 Insulated Molecular Wires 258
- 6.10 Molecular Switches and Machines 260

- 6.11 Supramolecular Oligomeric and Polymeric Rotaxanes 268
- 6.12 Rotaxane and Polyrotaxane-Based Muscles 270 References 277 Further Reading 280
- **7 Polymer Gels** 281
- 7.1 One-Dimensional Growth 281
- 7.2 Definitions and Classifications 283
- 7.3 Gels with Noncrystallizable Polymers 285
- 7.4 Gels with Crystallizable Polymers 295
- 7.5 Add a Sergeant to the Soldiers to Cause Gelation 300
- 7.6 π -Interaction-Mediated Gelation 308
- 7.7 Polymer Compatibilized Small Molecule/Polymer Gels 316
- 7.8 Monomer Self-Assembly and Polymer Gels 318
- 7.9 Poor Man's Rheology 321 References 324

8 Small-Molecule Self-Assembly in Polymer Matrices 329

- 8.1 Phase Separation in Charge Transport Polymer Layers 329
- 8.2 Glass Transition and Diffusion of Small Molecules 331
- 8.3 Subsurface Self-Assembly of Small Molecules in Polymer Matrices 333
- 8.4 Solvent Effect on Self-Assembly of Small Molecules in Polymer Matrices 338
- 8.5 Polymer-Compatibilized Small-Molecule Assembly in Polymer Matrices *343*
- 8.6 Polymerization-Induced Phase Separation and Reaction-Induced Phase Separation *344*
- 8.7 PIPS for LC Displays 345
- 8.8 PIPS with Supramolecular Assembly 347
- 8.9 PIPS for Porous Structures 347
- 8.10 Surfactant/Polymer Assembly 350 References 356

Index 359

Preface

Studies on molecular self-assembly has gained enormous momentum in the past two decades, driven by concurrent interest and developments in the areas of nanotechnology, molecular switches, shape memory devices, etc. Close to 130 000 publications have so far appeared in the literature on the topic of self-assembly and over 200 000 on the concept of self-assembly. Various disciplines of chemistry, biology, physics, and engineering have contributed to its emergence as a key research area. Novel synthetic methods, advances in the ability to manipulate molecules even at the atomic level, and device fabrication have been instrumental in its advancement. Amongst these, polymers have played a significant role and the self-assembly studies have explored various types of polymers, from everyday commodity plastics to high-performance polymers.

Several books and reviews have been published on the self-assembly of polymeric materials. Most of them have focussed on select themes such as supramolecular polymers. In this book, I have given an overview of various physical aspects of polymer self-assembly. Leaving the synthetic methods to the experts in that field, physical chemistry such as the morphology, etc., as it relates to polymer self-assembly is highlighted. This is an elaboration of a half-term graduate/fourth-year undergraduate course, "Macromolecular Nanotechnology," that I have been teaching for the past few years on the topic of polymer self-assembly as it relates to nanotechnology.

A brief introduction is given in Chapter 1 on the basic properties of polymers that distinguish them from small molecules as well as the basic definition of self-assembly. A look back at the literature on the emergence of the field of self-assembly, in terms of the number of publications from 1960 to 2015 is included.

As we emphasize noncovalent interactions as the trigger for self-assembly, I have given on overview of the force fields ("potential functions" as they used to be called) that were developed over the past decades to calculate the energies of interactions for van der Waals, hydrogen bonds, torsional contributions, and Coulombic interactions in Chapter 2. I myself have published several papers using these formulations, and was associated with the groups of G. N. Ramachandran (who devised the (Φ, Ψ) map) and Paul Flory during the decade that saw the development of these force fields. In addition to those, the halogen interactions and C—H··· π interactions also have been discussed, as these have been investigated in detail in recent years through crystallographic and nuclear magnetic resonance (NMR) studies.

Chapter 3 deals with the features that have been observed during the selfassembly of molecules and these include self-sorting; polymer-guest molecule assembly; the moieties that are used to functionalize polymers to induce self-assembly; sergeant-soldier phenomenon; chain folding; foldamers; and single-polymer, single-crystals, and single-polymer nanoparticles. Using these concepts, supramolecular polymers are discussed in Chapter 4. Since the International Union of Pure and Applied Chemistry (IUPAC) definition distinguishes between the terms polymers and macromolecules, examples of supramolecular assemblies that lead to polymers as well as macromolecules are presented in the chapter.

Block copolymer morphology is discussed in Chapter 5. This field is enormous with publications dating back to several decades, and several books and reviews have been published. I have tried to give a summary of the di- and triblock copolymer morphologies as well as those with organic/inorganic blocks. The gyroid morphology, grapho-epitaxy, and applications of block copolymer morphologies to nanoporous materials, metamaterials, and nano-reactors are discussed. The supramolecular assembly between linear polymers and cyclics that leads to rotaxanes is described in Chapter 6. A brief description of how these could be used for molecular switches, machines, and muscles is given. Although we consider liquid crystal as the fourth state of matter, one cannot ignore the gel state which has several applications. For the organo- or polymer gels, this state is a result of hydrophobic or solvo-phobic interactions. The gel morphologies of various synthetic polymers are discussed in Chapter 7.

Chapter 8 treats the self-assembly of small molecules in polymer matrices. Polymers such as polycarbonate are used as matrices to hold functional small molecules that are applicable to opto-electronic devices. Even the plasticizer technology uses small molecules in polymers. Hence, the interaction between the small molecules in a polymer matrix, whether they self-assemble or not, becomes important for device applications. In the chapter, I discuss the morphology of such composites when the small molecule possesses self-assembly attributes, such as spontaneous association driven by hydrogen bonds or π -interactions. The utilization of this attribute in techniques such as polymerization-induced phase separation and reaction-induced phase separation is illustrated. This then carries on to the application of these techniques for the fabrication of liquid crystal displays. Studies on polymer–surfactant interactions could not be ignored.

Although I became an academic late in my career, I benefited immensely from the contributions of my students and postdoctoral associates, and I thank them sincerely for their dedication. I thank Carleton University for providing me with a sabbatical break during which I completed parts of the book. On a personal note, I appreciate the support and encouragement from my wife Kumuda throughout our lives together. I am indebted to my brother Chellappa for supporting me during my university years. I thank my daughter Purnima, another nonmedical doctor in my family, for encouraging me to accept the invitation from Wiley to write the book.

> P. R. Sundararajan Carleton University Ottawa, Canada June 2016

1

Introduction

Polymers are ubiquitous in our daily lives. Natural polymers such as the DNA, RNA, and proteins have played a major role in the evolution of life itself. Cellulose, hemicelluloses, starch (amylose), and other naturally occurring polymers have been studied thoroughly, modified for useful applications and have been the key components of industrial advancement. Familiar to many is the chronological transition of the belief of these substances as colloids to the concept of "polymers." The "Rise of the Macromolecular Hypothesis" was discussed by Flory [1]. Supporting the Staudinger school of thought were, among others, the X-ray diffraction studies of cellulose by Meyer and Mark [2, 3]. Cellulose is perhaps the first polymer for which oriented X-ray fiber diffraction was recorded [2]. Synthetic polymers have also entered the scene around that time, with the synthesis of polystyrene [4] in 1839.

According to the International Union of Pure and Applied Chemistry (IUPAC) nomenclature [5], the terms polymer and macromolecule do not mean the same thing. A polymer is a substance composed of macromolecules. All macromolecules are not polymers.

1.1 Polymer Tacticity

As a polymer (Figure 1.1) is built up of many small molecular monomer units, the dimer (diad), trimer (triad), tetramer (tetrad), pentamer (pentad), and hexamer refer to two, three, four, five, and six monomers, respectively, linked together. Longer sequences of up to about 50-mers are called "oligomers." However, it is not uncommon in the studies on self-assembly to call such short chains polymers. Although natural or biopolymers such as poly(nucleic acids) (e.g., DNA), proteins and polysaccharides are also long chain molecules, the commonplace notion is that a polymer refers to the synthetic variety. Of these, vinyl polymers such as polyethylene (PE) and polystyrene are popularly known as plastics. The simplest of polymers is PE, with just a sequence of (CH_2) units (Figure 1.2). Polymerization of ethylene, vinyl fluoride, vinylidene



Figure 1.1 Schematics of a monomer, dimer, and a polymer.



Figure 1.2 Chemical structures of polyethylene and analogous fluorinated polymers. The dashed circles highlight the fluorine atoms.

fluoride, and tetrafluoroethylene lead to PE, poly(vinyl fluoride) (PVF), poly(vinylidene fluoride) (PVF2), and poly(tetrafluoroethylene), respectively. The latter is the well-known Teflon[®].

With bulkier substituents, polymers such as polystyrene, poly(methyl methacrylate), and poly(propylene) are obtained (Figure 1.3). Note that in the



Figure 1.3 Chemical structures of polystyrene, poly(methyl methacrylate), and polypropylene.

case of PE, PVF2, and PTFE, the substitution is symmetric, whereas with PVF, polystyrene, PMMA, and polypropylene, it is asymmetric. In the schematics shown in Figures 1.2 and 1.3, the bulkier substituent (R) is shown above the plane of the page. A general rendition is shown in Figure 1.4. In the figure [6], with the skeletal bonds in the all-*trans* conformation, the configuration with R above the page at the asymmetric carbon is designated as d and as l if it is below. If the substituents on two successive asymmetric carbons are in the same dd configuration, it is known as a "*meso*" (*m*) diad.

Perpetuation of such meso sequence would lead to an isotactic chain (Figure 1.4a). If the R groups are up and down the page, that is, *dl*, it is the racemic (*r*) diad (Figure 1.4b). The repetition of the racemic diad (*dl* sequence) would result in a syndiotactic polymer. Random occurrence of *m* and *r* results in an atactic polymer. The designation of d and l for the configuration at the asymmetric carbon is arbitrary. It follows the convention developed by Flory [7], which then led to the formulation of statistical weight matrices to calculate the statistical chain conformations. If the chain is rotated through 180° about a vertical axis such that the ends of the chain are reversed, all the dwould become *l* and vice versa. But the chain configuration would remain the same as long as the chain ends are indistinguishable. The *ll* would define the meso diad. With the diad configurations *m* and *r* defined earlier, a triad could have sequences of mm, rr, and mr (or rm). A tetrad could have sequences *mmm, mmr, rmr, mrm, rrm,* and *rrr,* of which only two of them would lead to stereoregular isotactic or syndiotactic chains. A pentad could have 10 such sequences, 8 of which will be heterotactic. Determining the distribution of such sequences in vinyl polymer chains that were prepared by various synthetic procedures was an active field, concurrent with advances in the NMR



Figure 1.4 (a)–(c) Schematic of the definition of tacticity for asymmetric chains. (Source: Sundararajan [6]. Reproduced with permission of Springer.)

techniques [8–11]. Although synthetic methods for stereoregular polymers have been developed, some of them such as isotactic polystyrene are of academic interest rather than of commercial use. Atactic polystyrene, in the form of, for example, Styrofoam, finds widespread applications. Likewise, PMMA in its atactic form, is used as a substitution for glass in the form of Plexiglass, as well as in microelectronic chips, etc. Studies on highly isotactic or syndiotactic polymers led to the understanding of aspects such as polymer crystallization and chain folding. In the studies of self-assembly of polymers, tacticity was seldom taken into consideration.

Some of the other polymers commonly used in studies of polymer self-assembly are polyesters, polyamides, polyurethanes, and polysiloxanes, the constituent units of which are shown in Figure 1.5. A summary of the synthetic procedures **Figure 1.5** Schematics of the segments of polyester, polyamide, polyurethane, and polysiloxane.

adopted for various types of polymers and their primary characterization properties was given by Sundararajan [6].

1.2 Big versus Small

As the small molecule "mono" mer units are joined together to build a "poly" mer, the properties change as the polymer increases in length. For example, ethane has boiling temperature of -89° and melts at -183°C. After growing by a few units, hexadecane melts at 18.5°C. With a further increase in chain length, triacontane [CH₃-(CH₂)₂₈-CH₃] melts at 65°C, and does not boil. Highmolecular-weight PE melts at 138°C. While the small molecules could melt and vaporize, polymer molecules melt and degrade rather than vaporizing. Most polymers show a glass-rubber transition (T_g) , whereas not all small molecules show a glass transition. Both could crystallize, but polymers should have a regular sequence of monomers (e.g., isotactic or syndiotactic) to be able to crystallize. Those with random sequence remain amorphous. The T_{g} is an important property of a polymer since it dictates the processing conditions for industrial applications. Small molecules such as D-glucose have a finite number of conformations, for example, the C1 chair form. However, amylose, which is a high-molecular-weight polymer of D-glucose, could have a large number of conformational sequences between contiguous D-glucose units due to rotations about the interunit C_1 –O– C_4 single bonds. The number of accessible conformations without steric overlap determines the "flexibility" of a polymer.

1.3 Entanglement

When a small molecule is dissolved in a solvent medium (lattice model) as shown pictorially in Figure 1.6a, both molecules can move and exchange lattice points just by diffusion and thermal motion. However, when a polymer is placed in a solvent (Figure 1.6b), coordinated movement of the monomer units

Figure 1.6 Schematic of (a) a small molecule and (b) a polymer in a solvent medium. The black circles denote the solvent molecules.

is necessary for the chain to diffuse. This results in loss of entropy of mixing. This would increase the viscosity of the solution compared to the small molecule/ solvent mixture. One of the most important properties of a polymer is the "entanglement" between its segments. A small molecule cannot entangle. As the polymer chain grows in length, due to coiling in solution or the melt, entanglement would set in. Most text books would mention a bowl of spaghetti as an example of entangled polymer chains. The polymer must be of a certain minimum length for entanglement to occur. For a bowl of cooked spaghetti to be an entangled stock, the length of the dry noodle should be about one foot. The average length of commercially sold dry spaghetti is 12-14 in., which assures the entanglement upon cooking. The critical molecular weight $M_{\rm c}$ for entanglement for polystyrene is about 37 000, while it is only about 5000 g/mol for polycarbonate [12]. Conformational analysis showed that polycarbonate chain can adopt flat helical as well as extended chain shapes with equal probability [13]. Thus, a low molecular weight is sufficient for entanglements to occur in the case of polycarbonate. M_c varies depending on the polymer structure and conformation. Another parameter is the entanglement molecular weight, M_e , which corresponds to the average molecular weight between entanglement points. The value of M_e is usually calculated from the plateau modulus G_N^0 using oscillatory shear experiments. The entanglement plays a significant role in the mechanical properties. Figure 1.7 shows the log-log plot of melt viscosity and molecular weight. It is seen that up to a certain molecular weight, the curve is linear, the region in which the viscosity scales with the first power of molecular weight. Beyond a certain molecular weight, the viscosity increases more sharply, with a slope of 3.4. The point at which the slope

Figure 1.7 Log–log plot of zero shear viscosities and molecular weight for a number of polymers. For clarity, the curves have been arbitrarily shifted along the ordinate. (Source: Graessley [14]. Reproduced with permission of Springer.)

changes from 1 to 3.4 is the one corresponding to M_c . The following relationship generally applies to most linear polymers:

$$\eta = KM \quad M < M_{\rm c} \tag{1.1}$$

$$\eta = K'M^{3.4} \quad M > M_{\rm c} \tag{1.2}$$

Here, K and K' are constants.

B 1 Introduction

1.4 Excluded Volume

In the conceptual framework of theoretical treatment of polymer chains, models such as freely jointed and freely rotating have been used. In the freely jointed or random walk model, a chain with a series of bonds each of length lcan adopt any (bond) angle between them, any dihedral angle and cross each other. There is no restriction on the contour of the chain except that the length of each step (bond) is fixed. Such a chain is "unperturbed" by any restrictions. In the freely rotating model, the bond lengths and bond angles are fixed, but the chain can assume any torsion angle between bonds. Now the chain is perturbed by imposing the condition that the bond angle is restricted to a certain value. In a real chain, the bonds cannot cross each other, that is, occupy the same space, which results in "excluded volume," as illustrated in Figure 1.8a. We find the concept of excluded volume in real life everywhere. If someone is sitting on a park bench or in a seat in a movie theater, that volume of space is "excluded" for others. In a hypothetical chain shown as in Figure 1.8a, the chain segments (bonds) are allowed to cross each other (indicated by *), as in the case of freely jointed model. Since the excluded volume would prevent such overlap, the chain would expand as in Figure 1.8b and the end-to-end distance r would increase. Another factor to consider is that the range of sterically accessible dihedral angles, illustrated in Figure 1.8c, between any two monomers would be restricted to various degrees depending on the type of polymer and the

Figure 1.8 (a) A random coil with long-range interaction (excluded volume overlap, denoted by *) between segments which are close in space but with large separation in the sequence along the chain. This would be the case in a freely jointed chain. (b) The chain expands to relieve the excluded volume overlap. The end-to-end distance *r* increases compared to that in (a). (c) Illustration of dihedral angles Φ and Ψ between contiguous units in a chain. (Source: (a) and (b) Tonelli [15]. Reproduced with permission of Wiley.)

interactions between contiguous monomers. These are short-range interactions which occur between contiguous neighbors, and are determined by the bond angles, torsion angles, and nonbonded forces such as van der Waals, hydrogen bonding, etc. Thus, the random coil of a real chain would be more expanded than the hypothetical free jointed or freely rotating models.

The role of excluded volume in the solution conformations of polymers has been discussed in detail by Flory [1]. As mentioned earlier, the long-range interaction gives rise to the excluded volume effect and causes chain expansion. The "long range" here does not mean in terms of the physical distance between the segments but the relative positions of the segments in the sequence along the chain, for example, the 5th and the 100th monomer unit, when they come close to each other. The average conformation of a randomly coiled chain in solution is governed by the short- and long-range interactions as well the polymer-solvent interaction. In a good solvent, the polymer-solvent interaction would be stronger than the mean of the energies between the polymer-polymer and solvent-solvent pairs. The chain would tend to expand to maximize the contacts between the polymer segments and the solvent molecules. In a poor solvent, the polymer would tend to adopt compact conformations to increase the number of contacts between the intrapolymer segments (subject to excluded volume effects) and to minimize the polymer-solvent interaction. In a particular solvent, at a certain temperature, the expansion due to excluded volume may be compensated exactly by the contraction due to the poor solvent. At this temperature, a balance occurs between the excluded volume (mutual volume exclusion of the segments), which expands the chain and the positive energy of mixing in the solvent which promotes first-neighbor contacts between the polymer segments resulting in a compact conformation. This temperature is known as the Flory Θ temperature. The chain would be unperturbed by long-range interactions and its conformation would be governed by short-range interactions between contiguous neighbors. By taking the rotations Φ and Ψ marked in Figure 1.8c to be discrete conformational states such as trans, gauche, and gauche minus (t-, g-, and g-rotational isomers, respectively), Flory [7] introduced the rotational isomericstate treatment of the statistical chain conformations in the unperturbed state (i.e., Θ condition). The Θ temperature depends on the solvent-polymer pair. Measurements and calculations of the Θ temperatures and chain dimensions for various polymers were a significant activity during the 1960s, extending to even the 1990s. The characteristic ratio of the unperturbed end-to-end distance of a chain with infinite molecular weight, defined as

$$C_{\infty} = \frac{\left\langle r^2 \right\rangle_0}{nl^2} \tag{1.3}$$

was related to the experimental measurements at the Θ temperature [7]. It was also during this period that experimental (neutron scattering, deuterated polymers, etc.) and theoretical work confirmed that the chain conformation in the amorphous,

10 1 Introduction

glassy state corresponded to that in the Θ condition. Properties such as the entanglement molecular weight (M_c), distance between entanglements (M_e), and viscoelastic properties have been correlated to the characteristic ratio [16–20]. A collection of the experimental results on the theta temperatures for various solvent/polymer pairs and the chain conformations was published [21] in 2007.

1.5 Free Volume

The excluded volume concept discussed earlier relates to the chain conformation and the physical properties associated with it. Another important factor is the "free volume," which is related to the glass transition temperature of a polymer. This is similar to the void space between spheres that are packed in a container. As the polymer coils pack themselves in space, intermolecular steric repulsions as well as thermal motions create free volume in a polymer matrix. The free volume would then depend on the temperature as well as the ease with which the chain can change its shape (conformation). For example, the rotational states of contiguous units of a poly(dimethyl siloxane) (PDMS) chain encounter very little energy barrier and the chain is hence highly flexible. As the temperature is lowered, the chain motion would cease at a particular temperature, which is the T_{g} . Due to its high conformational flexibility, the molecular notion in the case of PDMS does not freeze until a very low temperature of -125° C. For atactic polystyrene, the $T_{\rm g}$ is about 100°C; for poly(arylene sulfone), it is 250°C. Thus, the free volume above T_g depends on the conformational flexibility, and interchain interactions. Main chain aromatic polymers in which $\pi - \pi$ interaction is possible and those with interchain hydrogen bonds (e.g., polyamides) exhibit high glass transition temperatures. Other features that influence the $T_{\rm g}$ are long side chains, tacticity, etc. The molecular weight distribution would also affect the free volume. If the bulk sample has a large number of short chains in its midst, the number of chain ends would be significant. Since there must be a certain steric space between these chain ends, the free volume would increase, and the $T_{\rm g}$ would decrease. The low-molecular-weight fractions would act as internal plasticizers. The same would occur if the polymer is exposed to a solvent vapor or if a smallmolecule plasticizer is added. These would have a lubricating effect enabling chain movement and increase the free volume. The effect of free volume on the self-assembly of small molecules in polymer matrices is discussed in Chapter 8.

1.6 Self-Assembly

The research related to "self-assembly" spans a wide range of areas. It is believed to have originated with the studies on biological systems such as the DNA and RNA that led to an understanding that mutual recognition between molecular segments enables them to associate with one another. It is interesting to note the ever-increasing interest in this area, as shown in Table 1.1. These numbers were obtained from a search of the SciFinder Scholar (Chemical Abstracts Service of the American Chemical Society).

The search term was "self-assembly," with no other filter except the range of years. Thus these numbers include publications in all languages as well as patents, on not only molecular but also colloidal and other component selfassembly. While there were just a few articles in the 30-year period from 1960 to 1990, the number increased dramatically since then. It might be that it was during the late 1990s and the 2000s that the idea of using self-assembled systems for nanotechnology was gaining momentum.

Pelesko [22] quoted definitions of several authors as to the meaning of selfassembly. It is now generally defined as a process by which molecules or parts of molecules *spontaneously* form organized structures driven by specific *noncovalent* interactions between themselves, without an external stimulus. Further, the static self-assembly is a situation where the ordered state leads to equilibrium structures such as crystals. Although organized structures such as crystallization could occur in a large number of systems, the self-assembly is characterized by *spontaneous* and *reversible* organization of the molecular components. When the components are molecules, it is "molecular self-assembly." Whitesides [23, 24] presented scenarios of making useful devices at various length scales by self-assembly. Pelesko [22] discussed the self-organization of colloidal and other particle systems by the application of electrostatic force.

Publication years	Self-assen	nbly Concept o	of self-assembly
1960–1964	0	5	
1965–1969	43	65	
1970–1974	76	111	
1975–1979	204	280	
1980–1985	402	591	
1986-1990	491	838	
1991–1995	1612	3 4 4 1	
1996-2000	6167	12960	
2001-2005	19319	34351	
2006-2010	39639	63 411	
2011-2015	60011	87 474	
Total	127 964	203 527	

 Table 1.1
 Number of publications from SciFinder Scholar on "self-assembly" as entered and the "concept of self-assembly."

The self-assembly can thus be "directed" by specific external fields. Grzelczak et al. [25] reviewed the process and applications of directed self-assembly of nanoparticles. The term self-assembly has been used even in assemble-it-yourself furniture systems, where the assembly is modular [26, 27].

Although the majority of studies of self-assembly focus on functionalizing molecules with codes for hydrogen bonding, π -interaction or Coulombic interactions, other factors such as hydrophobic or solvo-phobic interactions also play a role in self-assembly. For example, phthalocyanines and porphyrins are insoluble in most organic solvents, but they could be made soluble in common solvents such as chloroform by peripheral substitution. Addition of a nonsolvent to such solutions in a controlled manner would trigger phase separation and the self-assembly via π -interaction, leading to nanowires and similar morphologies [28]. Even when a molecule is coded with, for example, hydrogen bonding, mutual steric and geometric registry must be favorable for self-assembly to occur.

1.7 Polymer Self-Assembly

As for the self-assembly of polymers, those with hydrogen bonding groups, such as polyamides, with aromatic interactions, for example, polyaramids, have been studied extensively in the past. As shown in Figure 1.5, the amide segment is similar to the amino acid moiety. Similar to the trend shown in Table 1.1, the research activity in the area of polymer self-assembly became intense only in the late 1990s. Table 1.2 shows the results of a search of the SciFinder Scholar. Although studies on hydrogen bonded polymers and similar systems were active before the 1990s, they do not appear significantly in the table, perhaps because the words "self-assembly" did not gain fame at that time in the area of synthetic polymers. In attempts to understand the molecular recognition between the nucleic acid base pairs, synthetic analogues were synthesized a few decades ago [29–39]. To this end, vinyl polymers of the nucleic acid bases, poly(vinyl adenine), poly(vinyl cytosine), poly(vinyl uracil), and poly(vinyl thymine), were synthesized and their interactions were studied since the 1970s.

Most articles on molecular self-assembly would point to the molecular recognition in biological molecules and suggest that Nature should be imitated when designing novel materials. To quote Ronald Breslow [40], "We learned the principle of wings from the birds but not the details of how to use them and power the flight. We take the principles of Nature, not the blueprint. The jumbo jet is not a scaled up version of the pigeon."

In considering self-assembly as it relates to polymers, the aspects are the self-assembly of polymers themselves and the self-assembly of individual units to create a polymer. In the former case, the polymer self-assembly could be

Publication years	Polymer self-assembly	Concept of polymer self-assembly
1960–1964		
1965–1969		
1970–1974		3
1975–1979		8
1980–1985		18
1986-1990		39
1991–1995	7	275
1996-2000	25	1204
2001-2005	93	3 370
2006-2010	182	6250
2011-2015	215	9191
	522	20358

 Table 1.2
 Number of publications from SciFinder Scholar on "polymer self-assembly" as entered and the "concept of polymer self-assembly"

driven by association elements such as hydrogen bonds. The self-association in the case of block copolymers would be driven by the incompatibility of the segments and to some extent by "self-recognition," "self-sorting." Using the principles of Nature, polymers functionalized with specific recognition units have been designed [41–48], and these led to various potential applications in areas such as nanotechnology. Using such methodologies to create folded structures, intramolecular and intermolecular association of chromophores with oligomeric or polymeric linkages by chain folding have created opportunities for optical applications [49–52]. We will discuss some of these in the following chapters.

References

- 1 P. J. Flory, Principles of Polymer Chemistry, 1969, Cornell University Press.
- 2 K. H. Meyer and H. Mark, Ber. Dtsch. Chem. Ges. A/B, 1928, 61, 593.
- 3 K. H. Meyer and H. Mark, Ber. Dtsch. Chem. Ges. A/B, 1928, 61, 1939.
- 4 E. Simon, Ann. Pharm., 1839, 31, 265.
- 5 R. C. Hiorns, R. J. Boucher, R. Duhlev, K.-H. Hellwich, P. Hodge, A. D. Jenkins, R. G. Jones, J. Kahovec, G. Moad, C. K. Ober, D. W. Smith, R. F. T. Stepto, J.-P. Vairon, and J. Vohlídal, *Pure Appl. Chem.*, 2012, 84, 2167–2169.

- 14 1 Introduction
 - 6 P. R. Sundararajan, in *Physical Properties of Polymers Handbook*, 2nd Ed., 2007, J. E. Mark, Ed., Chapter 1, Springer.
 - 7 P. J. Flory, *Statistical Mechanics of Chain Molecules*, **1969**, John Wiley & Sons, Inc., Chapter VI (Republished (**1989**) by Oxford University Press).
 - 8 F. A. Bovey, Polymer Conformation and Configuration, 1969, Academic Press.
 - 9 F. A. Bovey, P. Mirau, and H. S. Gutowsky, *Nuclear Magnetic Resonance Spectroscopy*, 2nd Ed., **1988**, Academic Press.
 - 10 A. E. Tonelli, *NMR Spectroscopy and Polymer Microstructure: The Conformational Connection*, 1989, Wiley-Interscience.
 - 11 A. E. Tonelli and J. L. White, in *Physical Properties of Polymers Handbook*, 2nd Ed., J. E. Mark, Ed., **2007**, Chapter 20, Springer.
 - 12 Z. Dobkowski, Rheol. Acta, 1995, 34, 578–585.
 - 13 P. R. Sundararajan, Macromolecules, 1987, 20, 1534-1539.
 - 14 W. W. Graessley, Adv. Polym. Sci., 1974, 16, 1.
 - 15 A. E. Tonelli, *Polymers from the Inside Out*, 2001, John Wiley & Sons, Inc., New York.
 - 16 S. M. Aharoni, Macromolecules, 1983, 16, 1722.
 - 17 T. A. Kavassalis and J. Noolandi, Macromolecules, 1988, 21, 2869.
 - 18 T. A. Kavassalis and J. Noolandi, Macromolecules, 1989, 22, 2709.
 - 19 R. P. Wool, Macromolecules, 1993, 26, 1564.
 - 20 L. J. Fetters, D. J. Lohse, D. Richter, T. A. Witten, and A. Zirkel, *Macromolecules*, 1994, 27, 4639.
 - P. R. Sundararajan, in *Physical Properties of Polymers Handbook*, 2007, J. E. Mark, Ed., Chapter 15, Springer.
 - 22 J. A. Pelesko, Self-Assembly, 2007, Chapman & Hall.
 - 23 G. Whitesides, Science, 2002, 295, 2418.
 - 24 G. Whitesides, Mater. Res. Soc. Bull., 2005, 30, 736.
 - 25 M. Grzelczak, J. Vermant, E. M. Furst, and L. M. Liz-Marzán, ACS Nano, 2010, 4, 3591–3605.
 - 26 M. Hackwood, G. Karmon, J. Adorian, Y. Tal, and M. Leczycki, Self-Assembly Furniture System, US Patent 5,244,271, 1993.
 - 27 C. Niziol, Self-Assembly Furniture, US Patent 4,421,366, 1983.
 - 28 J. Gao, C. Cheng, X. Zhou, Y. Li, X. Xu, X. Du, and H. Zhang, J. Colloid Interface Sci., 2010, 342, 225–228.
 - 29 E. Yashima, T. Tajima, N. Miyauchi, and M. Akashi, *Biopolymers*, 1992, 32, 811–817.
 - 30 L. Maggiora, S. Boguslawski, and M. P. Mertes, J. Med. Chem., 1977, 20, 1283–1287.
 - 31 J. Pitha, Cancer Res., 1976, 36, 1273–1277.
 - 32 F. H. Reynolds Jr., P. M. Pitha, R. Chuang, T.-C. Cheng, H. H. Kazazian, Jr., and D. Grunberger, *Mol. Pharmacol.*, 1975, 11, 708–715.