

Polyurethane Raw Materials

North America Isocyanates and Polyols



















Welcome to BASF's Polyurethane Raw Materials in North America



The basic polyurethane chemicals division of BASF provides manufacturers of polyurethane products with a broad catalog of raw materials, innovations, and technical expertise to help our customers advance their technologies in a diverse set of applications across various industries. With facilities in Geismar, LA and Wyandotte, MI, we supply aromatic isocyanates and an array of polyether polyols (conventional and graft) as well as polyester polyols to many of the major users of polyurethane raw materials, and through a comprehensive network of distributors. Our customers use these building blocks to formulate products in coatings, adhesives, sealants, elastomer (CASE) applications, as well as molded and slab-stock flexible foams, binders for engineered wood products (OSB, MDF, and PB), and polyisocyanurate insulation boards.



For more information, please visit our website at www.polyurethanes.basf.us.

Commitment to Customers

Continuously investing in our plants, supply chain, and technical expertise to better meet the needs of customers and support the safe handling of polyurethane chemicals.

With our long-lasting involvement in the polyurethane industry, BASF knows the requirements of the customers inside out. Our goals are simple: delivering the products that you need when you need them; finding the answers to your challenges; and ensuring the competitiveness of our offering.

To do so, we have built the best team of experts, backed by BASF resources around the globe, and made it available at your doorstep to help you make the most of polyurethane chemistry. We are also launching new products, investing in digital technologies, modernizing our supply chain, and expanding our plants. All with one goal in mind: being the supplier of choice for our customers.



Innovation

Improving performance and productivity. Opening new opportunities for polyurethane materials.

At BASF, we understand that innovation has always been a critical element for the growth and success of our customers. From TMI-based macromer technology, to liquid gel, and fast binder for engineered wood products, BASF has often pioneered solutions that contributed to the advancement of polyurethane technologies.

Today, our commitment to innovation is stronger than ever. Whether developing new products or inventing new processes, our technical team continues to explore the limits of isocyanate and polyol chemistries. Delivering those innovations with a robust level of technical support ensures fast and reliable implementation.



Quality

Meeting customers' expectations with cutting-edge technology and manufacturing expertise.

At BASF, we understand that it is essential for our customers to use ingredients in their formulations that meet their specific requirements each and every time. We strive to manufacture our isocyanates and polyols to consistent standards, whatever the application. By leveraging our state-of-the-art technologies, in-depth expertise, and investments in process engineering, our highly skilled staff ensures that quality, together with safety, is core to our operations.



Health and Safety

Relentless commitment to the safe handling of polyurethane chemicals.

At BASF, we commit significant resources and staff to promote the responsible use of our products along the entire value chain. We aim to ensure that each person transporting, storing or processing our isocyanates and polyols is fully aware of the risks and is properly trained for safe handling of these chemicals. Our health and safety activities begin in our laboratories and factories. Our commitment does not stop there. We offer training courses to familiarize customers and distributors with recommended procedures, both for normal operations and emergencies. We also provide personalized assistance to help with the introduction of new products, conversions to polyurethane technologies, or with other specific situations. Through our involvement in several industry associations, we are pooling our expertise on safe handling with other stakeholders, further enhancing the core knowledge and processes related to health and safety matters for the entire polyurethane industry.



Global Presence

Global presence with local expertise - We know what it means.

With BASF, you benefit from a partner with an established presence in all regions, operating world-class plants at our "Verbund" sites in North America, Europe, and Asia. For our customers, this means access to a global pool of technical experts and to the latest global innovations in polyure-thane chemicals. Since we know that a worldwide network means little without local support, our sales, customer care, and technical teams are available right here in North America to discuss your needs and provide solutions to help your business succeed.

Isocyanates

Lupranate® isocyanates from BASF are utilized across a large range of applications and industries. Products include monomeric and polymeric methylene diphenyl isocyanate (MDI), toluene diisocyanate (TDI), specialized blends, modified MDI, and MDI prepolymers.

Product	NCO (%)	Nominal Functionality	Viscosity @ 25°C (cps)	Storage Temperature (°C)
	to the 4,4'- and 2,4'- isomers of and stored as a liquid for up to fif		Pure 4,4'-MDI is a crystalline solid	at room temperature. At 45°C,
Lupranate M	33.5	2.0	Solid/Liquid	< 0 or 45
Lupranate MI	33.5	2.0	12	23 - 30
Lupranate MS	33.5	2.0	Solid/Liquid	< 0 or 45
Lupranate 253	33.0	2.0	16	30 - 40
Lupranate LP30	33.0	2.0	16	30 - 40
Lupranate LP27	32.4	2.0	17	30 - 35
Lupranate 227	32.1	2.0	15	20 - 35

Product	NCO (%)	Nominal Functionality	Viscosity @ 25°C (Cps)	Storage Temperature (°C)	
Carbodiimide Modified MDI BASF uses carbodiimide chemistr stable and clear at room tempera		e monomeric diphenylmethane diisocya	anate. The carbodiimide-modifi	ed MDIs are liquids that are	
Lupranate 81	29.5	2.1	40	20 - 35	
Lupranate MM103	29.5	2.2	40	25 - 35	
Lupranate 5143	29.2	2.2	40	22 - 30	
increases, the functionality and visco Lupranate M20	osity of the PMDI will increase 31.5	ates including 2-ring(MMDI), 3-ring, and he. PMDI is a brown, temperature-stable liq	uid.	20 - 30	
Lupranate M20	31.5	2.7	200	20 - 30	
Lupranate M70L	31.0	3.0	700	20 - 30	
MDI Blends Starting with a base of BASF Lup	ranate® PMDI and MMDI pr	oducts, the following line of isocyanate	blends and derivatives are creatives	ated. They offer quotem	
properties for your application ne	eds.			ateu. mey oner custom	
properties for your application ne	eds. 27.5	2.2	140	20 - 30	
properties for your application new		2.2			
properties for your application ned upranate 223 upranate 278	27.5		140	20 - 30	
	27.5 33.0	2.1	140 17	20 - 30 25 - 35	

Product	NCO (%)	Nominal Functionality	Viscosity @ 25°C (cps)	Storage Temperature (°C)
MDI Blends (cont.)				
Lupranate 5100	32.6	2.3	33	25 - 35
Lupranate 5350	32.6	2.3	29	20 - 35
Lupranate 5430	32.5	2.1	20	20 - 30
Lupranate 230	32.4	2.2	35	20 - 30
Lupranate 245	32.3	2.3	35	25 - 35
Lupranate TF2115	32.3	2.4	49	25 - 35
Lupranate 234	32.0	2.3	50	20 - 35
Lupranate 255	32.0	2.5	70	20 - 35
Lupranate 266	32.0	2.5	66	15 - 35
Lupranate 78	32.0	2.3	65	15 - 30
Lupranate M10	32.0	2.3	70	20 - 35
Lupranate 5400	31.8	2.4	66	15 - 35
Lupranate 5390	31.7	2.6	120	20 - 35

8 | Monomers North America

Product	NCO (%) Nominal Functionality		Viscosity @ 25°C (cps)	Storage Temperature (°C)
MDI Blends (cont.)				
Lupranate 277	31.0	2.8	350	20 - 30
Lupranate 5270	30.6	2.0	15	20 - 35
MDI Prepolymers A prepolymer results from the r	reaction of excess MMDI with a hy	droxyl terminated resin.		
Lupranate 233	25.4	2.3	175	20 - 30
Lupranate 5040	26.3	2.1	140	25 - 35
Lupranate 5090	23.0	2.1	650	20 - 30
Lupranate MP102	23.0	2.0	700	25 - 35
Lupranate 5050	21.5	2.1	335	25 - 35
Lupranate 5380	19.8	2.3	525	20 - 35
Lupranate 5030	18.9	2.0	1,130	25 - 35
Lupranate 5340	18.0	2.1	880	20 - 35
Lupranate 5370	16.5	ND	6,100	20 - 35

Product	NCO (%) Nominal Functionality		Viscosity @ 25°C (cps)	Storage Temperature (°C)	
MDI Prepolymers (cont.)					
Lupranate 275	15.9	2.1	560	25 - 35	
Lupranate 5080	15.9	2.0	330	20 - 30	
Lupranate 5060	15.5	2.0	1,000	25 - 35	
Lupranate 5230	14.1	2.0	1,450	20 - 30	
Lupranate 5070	13.0	2.0	3,360	25 - 35	
Lupranate 5020	9.5	2.0	2,500	25 - 35	
Lupranate 5310	8.0	2.0	2,700	20 - 35	
Aliphatic Prepolymers Aliphatic prepolymers are based	on 4,4'-HMDI. They offer improv	red UV resistance and high hardness	s when used in cast elastomer a	pplications.	
Lupranate 5570	25.8 - 27	2.0	450	30 - 40	
TDI and TDI Blends Lupranate® T80 is a mixture of 8	30% 2,4-isomer and 20% 2,6-iso	omer of toluene diisocyanate (TDI).			
Lupranate T80 Type I	48.2	2.0	3	16 - 32	
Lupranate T80 Type II	48.2	2.0	3	16 - 32	
Lupranate 8020	44.5	2.1	15	16 - 29	

Polyether Polyols

The Pluracol® polyol portfolio offers a diverse range of polyether polyols including conventional and graft polyols with the following typical values. The Pluracol graft series are polyether products containing dispersed particles of co-polymerized styrene and acrylonitrile, or SAN particles. These products offer property improvements for certain applications such as flexible foam and urethane elastomers.

Product	Nominal Functionality	OH Number (avg.)	Nominal Molecular Weight (g/mole)	Viscosity @ 25°C (cps)	Acid No. (max)	Na & K ppm (max)	Structure (*capped)	Typical Use
Diols								
Pluracol P410R	2	260	400	73	0.015	10	PO	CASE
Pluracol P710R	2	145	700	139	0.015	5	PO	CASE
Pluracol 1010	2	107	1,000	150	0.040	5	PO	CASE
Pluracol 2010	2	56	2,000	250	0.025	5	PO	CASE
Pluracol 1044	2	29	4,000	790	0.010	5	PO	CASE
Pluracol 1062	2	29	4,000	840	0.010	5	P0/E0*	Molded
Pluracol 628	2	25	3,850	1,500	0.010	5	P0/E0*	Molded

Product	Nominal Functionality	OH Number (avg.)	Nominal Molecular Weight (g/mole)	Viscosity @ 25°C (cps)	Acid No. (max)	Na & K ppm (max)	Structure (*capped)	Typical Use
Triols								
Pluracol 858	3	935	180	1,360	0.010	70	PO	Rigid
Pluracol 1158	3	920	183	3,400	0.100	130	E0	Rigid
Pluracol 1016	3	505	330	291	N/A	N/A	P0/E0*	Rigid
Pluracol TP440	3	398	400	600	0.030	20	P0	CASE
Pluracol GP430	3	398	400	360	0.010	10	P0	CASE
Pluracol GP730	3	230	700	270	0.045	10	PO	CASE
Pluracol 1070	3	170	1,000	262	0.015	12	P0/E0	Molded
Pluracol 2009	3	170	1,000	258	0.035	12	P0/E0*	Molded
Pluracol 1135i	3	112	1,500	305	0.010	5	P0	CASE
Pluracol 726	3	57.5	3,000	420	0.015	5	P0	CASE
Pluracol 2086	3	57	2,800	503	0.010	5	P0/E0*	Slab

Product	Nominal Functionality	OH Number (avg.)	Nominal Molecular Weight (g/mole)	Viscosity @ 25°C (cps)	Acid No. (max)	Na & K ppm (max)	Structure (*capped)	Typical Use
Triols (cont.)								
Pluracol 4156	3	56	3,000	582	N/A	N/A	PO/EO	Slab
Pluracol 1538	3	56	3,000	700	0.010	5	P0/E0*	Slab
Pluracol 2019/1	3	47	3,500	576	0.010	5	P0/E0	Slab
Pluracol 593	3	46	3,650	1,340	0.010	5	P0/E0*	Slab
Pluracol 816	3	35	4,800	900	0.010	5	P0/E0*	Molded
Pluracol 1421	3	35	4,800	900	0.030	5	P0/E0*	CASE
Pluracol 945	3	35	4,800	850	0.010	5	P0/E0*	Molded
Pluracol 2097	3	35	4,800	840	0.010	5	P0/E0*	Molded
Pluracol 1603	3	31	5,400	1,200	0.060	11	P0/E0*	Molded
Pluracol 2090	3	28	4,800	1,150	0.010	5	P0/E0*	Molded

Product	Nominal Functionality	OH Number (avg.)	Nominal Molecular Weight (g/mole)	Viscosity @ 25°C (cps)	Acid No. (max)	Na & K ppm (max)	Structure (*capped)	Typical Use
Triols (cont.)								
Pluracol 1026	3	27.5	6,000	1,329	0.010	5	P0/E0*	Molded
Pluracol 220	3	26.6	4,500	1,300	0.035	5	P0/E0*	CASE
Pluracol 2100	3	25	6,500	1,370	0.015	5	P0/E0*	Slab
Pluracol 380	3	25	6,500	1,370	0.010	5	P0/E0*	Molded
Quadrol +								
Quadrol® PM	4	770	292	56,000	N/A	N/A	PO	Rigid
Pluracol PEP450	4	555	400	2,000	0.060	15	P0	CASE
Pluracol 922	4	500	445	17,000	N/A	N/A	P0/E0	Rigid
Pluracol PEP550	4	450	500	1,600	0.060	15	P0	CASE
Pluracol 1578	4	395	550	18,600	N/A	15	P0/E0	Rigid
Pluracol 736	4	390	575	14,500	N/A	N/A	P0	Rigid

Product	Nominal Functionality	OH Number (avg.)	Nominal Molecular Weight (g/mole)	Viscosity @ 25°C (cps)	Acid No. (max)	Na & K ppm (max)	Structure (*capped)	Typical Use
Quadrol + (cont.)								
Pluracol SG-360	4	362.5	700	3,500	N/A	N/A	PO	Rigid
Pluracol 1168	4	300	740	1,800	N/A	N/A	P0/E0	Rigid
Pluracol SG-470	5.5	470	665	35,000	N/A	N/A	PO	Rigid
Product	Nominal Funct	tionality	OH Value	SAN So	olids (%)	Viscosity @ 25°C	Ту	pical Use
Graft Polyols								
Pluracol 1528FF	3		19	4	5	5,800		Molded
Pluracol 4600	3		29	4	5	4,200		Slab
Pluracol 4650	3		29	4	5	4,200		Slab
Pluracol 5132	3		22		2	3,240		Slab
Pluracol 5250	3		28	5	0	5,820		Slab

Polyester Polyols

The Lupraphen® polyol portfolio offers polyester polyols for CASE and footwear applications. These polyols are optimized for mechanical properties and hydrolysis resistance of the final product.

Product	Nominal Functionality	OH Number (avg.)	Nominal Molecular Weight (g/mole)	Viscosity @ 60°C (cps)	Acid No. (max)	Typical Use
Polyester Polyols						
Lupraphen 1602/1	2	44	2,500	1,425	0.500	CASE
Lupraphen 1606/1	2.5	52	2,700	20,500	1.400	CASE
Lupraphen 1608/1	2	55	2,000	1,075	0.900	CASE
Lupraphen 1608/2	2	55	2,000	1,075	0.300	CASE
Lupraphen 1609/1	2	55	2,000	1,285	0.700	CASE
Lupraphen 1612/1	2	55	2,000	1,100	0.700	CASE
Lupraphen 1613/1	2	55	2,000	1,025	0.700	CASE
Lupraphen 1801/1	2	110	1,000	255	1.000	CASE
Lupraphen 1802/1	2	110	1,000	333	0.700	CASE
Lupraphen 1803/1	2	110	1,000	355	0.700	CASE
Lupraphen 1804/1	2	150.5	750	190	0.700	CASE
Lupraphen 2605/1	2.8	59	2,600	20,500	1.400	CASE



About BASF

BASF Corporation, headquartered in Florham Park, New Jersey, is the North American affiliate of BASF SE, Ludwigshafen, Germany. BASF has more than 20,000 employees in North America and had sales of around \$20 billion in 2018. For more information about BASF's North American operations, visit www.basf.com.

At BASF, we create chemistry for a sustainable future. We combine economic success with environmental protection and social responsibility. The approximately 122,000 employees in the BASF Group work on contributing to the success of our customers in nearly all sectors and almost every country in the world. Our portfolio is organized into six segments: Chemicals, Materials, Industrial Solutions, Surface Technologies, Nutrition & Care and Agricultural Solutions. BASF generated sales of around €63 billion in 2018. BASF shares are traded on the stock exchanges in Frankfurt (BAS), London (BFA) and Zurich (BAS). Further information at www.basf.com.

BASF Corporation

Polyurethane Raw Materials 1609 Biddle Avenue Wyandotte, MI 48192 USA

tel: 877-297-3322 fax: 800-720-1132

e-mail: CMCustomerCare@basf.com website: www.polyurethanes.basf.us

THE DESCRIPTIONS, DESIGNS, DATA AND INFORMATION CONTAINED HEREIN ARE PRESENTED IN GOOD FAITH, AND ARE BASED ON BASF'S CURRENT KNOWLEDGE AND EXPERIENCE. THEY ARE PROVIDED FOR GUIDANCE ONLY, AND DO NOT CONSTITUTE THE AGREED CONTRACTUAL QUALITY OF THE PRODUCT OR A PART OF BASF'S TERMS AND CONDITIONS OF SALE. BECAUSE MANY FACTORS MAY AFFECT PROCESSING OR APPLICATION/USE OF THE PRODUCT, BASF RECOMMENDS THAT THE READER CARRY OUT ITS OWN INVESTIGATIONS AND TESTS TO DETERMINE THE SUITABILITY OF A PRODUCT FOR ITS PARTICULAR PURPOSE PRIOR TO USE. IT IS THE RESPONSIBILITY OF THE RECIPIENT OF PRODUCT TO ENSURE THAT ANY PROPRIETARY RIGHTS AND EXISTING LAWS AND LEGISLATION ARE OBSERVED. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH HEREIN, OR THAT THE PRODUCTS, DESCRIPTIONS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. ANY DESCRIPTIONS, DESIGNS, DATA AND INFORMATION GIVEN IN THIS PUBLICATION MAY CHANGE WITHOUT PRIOR INFORMATION. THE DESCRIPTIONS, DESIGNS, DATA, AND INFORMATION FURNISHED BY BASF HEREUNDER ARE GIVEN GRATIS AND BASF ASSUMES NO OBLIGATION OR LIABILITY FOR THE DESCRIPTIONS, DESIGNS, DATA OR INFORMATION GIVEN OR RESULTS OBTAINED, ALL SUCH BEING GIVEN AND ACCEPTED AT THE READER'S RISK.

= registered trademark of BASF Group.
 2019 BASF, Wyandotte, MI 48192. All rights reserved.
 BF-CMprod-19/09