

# **ANSI/AGMA 2003-D19**

(Revision of ANSI/AGMA 2003-C10)

# **American National Standard**

Rating the Pitting
Resistance and Bending
Strength of Generated
Straight Bevel, Zerol
Bevel and Spiral Bevel
Gear Teeth

# American National Standard

# Rating the Pitting Resistance and Bending Strength of Generated Straight Bevel, Zerol Bevel and Spiral Bevel Gear Teeth

ANSI/AGMA 2003-D19

[Revision of ANSI/AGMA 2003-C10]

Approval of an American National Standard requires verification by ANSI that the requirements for due process, consensus, and other criteria for approval have been met by the standards developer.

Consensus is established when, in the judgment of the ANSI Board of Standards Review, substantial agreement has been reached by directly and materially affected interests. Substantial agreement means much more than a simple majority, but not necessarily unanimity. Consensus requires that all views and objections be considered, and that a concerted effort be made toward their resolution.

The use of American National Standards is completely voluntary; their existence does not in any respect preclude anyone, whether he has approved the standards or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not conforming to the standards.

The American National Standards Institute does not develop standards and will in no circumstances give an interpretation of any American National Standard. Moreover, no person shall have the right or authority to issue an interpretation of an American National Standard in the name of the American National Standards Institute. Requests for interpretation of this standard should be addressed to the American Gear Manufacturers Association.

**CAUTION NOTICE:** AGMA technical publications are subject to constant improvement, revision, or withdrawal as dictated by experience. Any person who refers to any AGMA technical publication should be sure that the publication is the latest available from the Association on the subject matter.

[Tables or other self-supporting sections may be referenced. Citations should read: See ANSI/AGMA 2003-D19, Rating the Pitting Resistance and Bending Strength of Generated Straight Bevel, Zerol Bevel and Spiral Bevel Gear Teeth, published by the American Gear Manufacturers Association, 1001 N. Fairfax Street, Suite 500, Alexandria, Virginia 22314, http://www.agma.org.]

Approved May 14, 2019

#### **ABSTRACT**

This standard specifies a method for rating the pitting resistance and bending strength of generated straight bevel, zerol bevel and spiral bevel gear teeth. A detailed discussion of factors influencing gear survival and a calculation method are provided.

Published by

American Gear Manufacturers Association 1001 N. Fairfax Street, Suite 500, Alexandria, Virginia 22314

Copyright © 2019 by American Gear Manufacturers Association All rights reserved.

No part of this publication may be reproduced in any form, in an electronic retrieval system or otherwise, without prior written permission of the publisher.

Printed in the United States of America

ISBN: 978-1-64353-037-6

# Contents

| For | eword  | V  |  |  |
|-----|--|----|--|--|
| 1   | Scope  | 1  |  |  |
|     | 1.1 Rating formulas  | 1  |  |  |
|     | 1.2 Exceptions   | 1  |  |  |
| 2   | Nomenclature   | 2  |  |  |
|     | 2.1 Normative references   |    |  |  |
|     | 2.2 Symbols  |    |  |  |
| 3   | Applicability  | 5  |  |  |
| •   | 3.1 Rating practices   |    |  |  |
|     | 3.2 Non-uniform load   |    |  |  |
|     | 3.3 Testing  |    |  |  |
|     | 3.4 Manufacturing methods  |    |  |  |
|     | 3.5 Manufacturing tolerances   |    |  |  |
|     | 3.6 Contact pattern  |    |  |  |
|     | 3.7 Implied accuracy   |    |  |  |
|     | 3.8 Other considerations   |    |  |  |
| 4   | Criteria for gear tooth capacity   |    |  |  |
| 7   | 4.1 Relationship between macropitting resistance and bending strength          |    |  |  |
|     | 4.2 Macropitting   |    |  |  |
|     | 4.3 Micropitting   |    |  |  |
|     | 4.4 Subcase fatigue  |    |  |  |
|     | 4.5 Bending strength   |    |  |  |
| 5   | Fundamental rating formulas  |    |  |  |
| 0   | 5.1 Pitting resistance   |    |  |  |
|     | 5.2 Bending strength   |    |  |  |
| 6   | Pinion torque  |    |  |  |
|     | ·  |    |  |  |
| 7   | Overload factor, $K_o$ ( $K_A$ )   |    |  |  |
|     | 7.1 Items affecting external dynamic loads                                     |    |  |  |
|     | 7.2 Establishment of overload factors  |    |  |  |
| 8   | Safety factor, $S_{H}$ and $S_{F}$   | 13 |  |  |
| 9   | Service factors  | 14 |  |  |
|     | 9.1 Historical service factors   | 14 |  |  |
|     | 9.2 Use of service factors   | 14 |  |  |
| 10  | Dynamic factor, K <sub>v</sub>   | 15 |  |  |
|     | 10.1 Design effects  |    |  |  |
|     | 10.2 Manufacturing effects   |    |  |  |
|     | 10.3 Transmission error  |    |  |  |
|     | 10.4 Dynamic response  |    |  |  |
|     | 10.5 Resonance   |    |  |  |
|     | 10.6 Approximate dynamic factor, $K_{v}$                                       |    |  |  |
|     | 10.7 Other values  |    |  |  |
|     | 10.8 Unity dynamic factor  |    |  |  |
| 11  | Size factors, $C_s(Z_x)$ , $K_s(Y_x)$  |    |  |  |
|     |  |    |  |  |
|     | 11.1 Size factor for pitting resistance, $C_{\rm s}(Z_{\rm s})$                |    |  |  |
|     | 11.2 Size factor for bending strength, $K_s$ ( $Y_x$ )                         |    |  |  |
|     | Load distribution factor, $K_{\rm m}$ ( $K_{\rm H\beta}$ )                     |    |  |  |
| 13  | Crowning factor for pitting, $C_{xc}$ ( $Z_{xc}$ )                             |    |  |  |
|     | Lengthwise curvature factor for bending strength, $K_{x}\left(Y_{p}\right)$ 22 |    |  |  |
| 14  | Lengthwise curvature factor for bending strength, $K_{\chi}(T_{\beta})$        |    |  |  |

|  | 15.1         | Pitting resistance geometry factor, $I(Z_I)$   | 23       |  |  |
|--|--------------|--|----------|--|--|
|  | 15.2         | Bending strength geometry factor, $J(Y_J)$   | 23       |  |  |
| 16   | Stress       | cycle factors, $C_{L}$ ( $Z_{NT}$ ) and $K_{L}$ ( $Y_{NT}$ )   | 24       |  |  |
|  | 16.1         | Stress cycle factor for pitting resistance $C_{\rm L}$ ( $Z_{\rm NT}$ )  |          |  |  |
|  | 16.2         | Stress cycle factor for bending strength, $K_{\mathbf{L}}$ ( $Y_{\mathbf{NT}}$ )   |          |  |  |
|  | 16.3         | Localized yielding   |          |  |  |
| 17   |              | ess ratio factor for pitting resistance, $C_{H}\left(Z_{W}\right)$   |          |  |  |
|  | 17.1<br>17.2 | Through hardened gears Surface hardened/through hardened steels  | 26<br>27 |  |  |
|  | 17.3         | Equal hardness materials   |          |  |  |
| 18   | Temp         | erature factor, $K_{T}$ ( $K_{\theta}$ )   |          |  |  |
|  | 18.1         | High temperature operation   | 29       |  |  |
|  | 18.2         | Low temperature operation  |          |  |  |
| 19   |              | ility factors, $C_{R}\left(Z_{Z}\right)$ and $K_{R}\left(Y_{Z}\right)$   |          |  |  |
| 20   |              | coefficient for pitting resistance, $C_{\rm p}$ ( $Z_{\rm E}$ )  |          |  |  |
| 21   |              | able stress numbers  |          |  |  |
|  | 21.1<br>21.2 | Guide for case depth of surface hardened gears   |          |  |  |
|  | 21.2         | Allowable contact stress number, $s_{ac}$ ( $\sigma_{Hlim}$ )  Bending stress number (allowable), $s_{at}$ ( $\sigma_{Flim}$ ) |          |  |  |
|  | 21.4         | Metallurgical considerations   |          |  |  |
|  |              |  |          |  |  |
| An   | nexes        |  |          |  |  |
| Anr  | nex A        | (informative) Values for overload factor, $K_{\mathbf{o}}$ ( $K_{\mathbf{A}}$ )  | 42       |  |  |
| Anr  | nex B        | (informative) Miner's Rule   | 43       |  |  |
| Anr  | nex C        | (informative) Geometry factors, I and J  | 48       |  |  |
| Anr  | nex C (      | M) (informative) Geometry factors, $Z_{I}$ and $Y_{J}$   | 62       |  |  |
| Anr  | nex D        | (informative) Geometry factor figures  | 77       |  |  |
| Anr  | nex E        | (informative) Bevel gear sample calculations   | 96       |  |  |
| Anr  | nex F        | (informative) Bibliography   | 99       |  |  |
| Tal  | oles         |  |          |  |  |
|  |              | Symbols used in gear rating equations  | 3        |  |  |
|  |              | Reliability factors  |          |  |  |
|  |              | Allowable contact stress number, $s_{\sf ac}$ ( $\sigma_{\sf Hlim}$ ), for steel gears   |          |  |  |
|  |              | Allowable contact stress number, $s_{ac}$ ( $\sigma_{H lim}$ ), for iron gears   |          |  |  |
| Table 5 – Bending stress number (allowable), $s_{\rm at}$ ( $\sigma_{\rm Flim}$ ), for steel gears |              |  |          |  |  |
|  |              | Bending stress number (allowable), $s_{\rm at}$ ( $\sigma_{\rm F  lim}$ ), for iron gears                                      |          |  |  |
|  |              | Hardening process factors  |          |  |  |
|  |              | Major metallurgical factors affecting carburized and hardened gears <sup>1) 2) 3)</sup>  |          |  |  |
| Table 9 – Major metallurgical factors affecting nitrided gears <sup>1) 2) 3)</sup>                 |              |  |          |  |  |
|  |              | - Major metallurgical factors affecting through hardened gears <sup>1) 2) 3)</sup>   |          |  |  |
| Tak  | ole 11 -     | - Major metallurgical factors affecting flame or induction hardened gears <sup>1) 2) 3)</sup>                                  | 41       |  |  |

# **Figures** Figure 5 – Stress cycle factor for pitting resistance, $C_{\rm L}$ ( $Z_{\rm NT}$ ) (carburized case hardened steel bevel gears)......25 Figure 6 – Stress cycle factor for bending strength, $K_{\rm L}$ ( $Y_{\rm NT}$ ) (carburized case hardened steel bevel gears)......25 Figure 8 – Hardness ratio factor, $C_{\rm H}$ ( $Z_{\rm W}$ ), for surface hardened pinions......29 Figure 9 – Allowable contact stress number for through hardened steel gears, $s_{ac}$ ( $\sigma_{H lim}$ ) .......31 Figure 10 – Bending stress number (allowable) for through hardened steel gears, $s_{\rm at}(\sigma_{\rm F\,lim})$ ......33 Figure 11 – Typical minimum effective case depth for carburized gears, $h_e(h_c)$ ......35

#### **Foreword**

[The foreword, footnotes and annexes, if any, in this document are provided for informational purposes only and are not to be construed as a part of ANSI/AGMA Standard 2003-D19, *Rating the Pitting Resistance and Bending Strength of Generated Straight Bevel, Zerol Bevel and Spiral Bevel Gear Teeth.*]

This standard presents general formulas for rating pitting resistance and bending strength of generated straight bevel, zerol bevel and spiral bevel gear teeth, and supersedes the following previous standards:

AGMA 212.02, Standard for Surface Durability (Pitting) Formulas for Straight Bevel and Zerol Bevel Gear Teeth

AGMA 216.01, Standard for Surface Durability (Pitting) Formulas for Spiral Bevel Gear Teeth

AGMA 222.02, Standard for Rating the Strength of Straight Bevel and Zerol Bevel Gear Teeth

AGMA 223.01, Standard for Rating the Strength of Spiral Bevel Gear Teeth

The purpose of standard 2003-A86 was to establish a common base for rating various types of bevel gears for differing applications and to encourage the maximum practical degree of uniformity and consistency between rating practices within the gear industry.

The formulas presented in this standard contain numerous terms whose individual values can vary significantly depending on application, system effects, accuracy and manufacturing method. Proper evaluation of these terms is essential for realistic rating. The knowledge and judgment required to properly evaluate the various rating factors come primarily from years of accumulated experience in designing, testing, manufacturing and operating similar gear units. The detailed treatment of the general rating formulas for specific product applications is best accomplished by those experienced in the field.

ANSI/AGMA 2003-A86 consolidated and updated previous standards to facilitate application by elimination of redundant material, and also to stress the importance of checking both pitting resistance and bending strength aspects to insure a reliable and well balanced design.

The first draft of ANSI/AGMA 2003-A86 was made in May 1980. It was approved by the AGMA membership in June 1985. It was approved as an American National Standard on May 2, 1986, but was not published until early 1987. The edition contained editorial items which were discovered after publication and corrected by the members of the AGMA Gear Rating Committee in the spring of 1988.

AGMA 2003-B97 began as a proposal by the US Delegation to the International Standards Organization (ISO) in 1988 as an effort to reach a consensus. It contained revisions and updates which made it closer to ISO as follows:

- The calculations for dynamic factor and geometry factors appeared in a draft of ISO 10300;
- The table for load distribution factor was the same as appears in a draft of ISO 10300;
- The material grade requirements were similar to those of ISO 6336-5;
- Each symbol used in AGMA 2003-B97 had the ISO equivalent symbol adjacent to it in parentheses.

Several significant changes were introduced in AGMA 2003-B97:

- The introduction of material grade requirements to provide guidance in the selection of stress numbers;
- The replacement of the external dynamic factor;
- Replacing the internal dynamic factor with a new dynamic factor;
- Equations for size factor for bending and pitting resistance were introduced;
- An adjustment of the load distribution factor;
- Revision of the allowable stress numbers;
- Elimination of the stress correction factor;
- The life factor curve for pitting resistance was adjusted to compensate for revisions to previously mentioned factors:
- The fundamental contact stress formula was adjusted to remove the term accommodating light load conditions.

The term zerol or Zerol is used to define a spiral bevel gear with a zero spiral angle. Zerol is a registered trademark of the Gleason Works [4].

The earlier version of this standard, ANSI/AGMA 2003-C10, was a revision of its superseded version. The size factor for pitting resistance addressed in Clause 11 was updated to incorporate experience which was gained with use of the standard. Editorial changes were made to Equations 10M, C103M and Figure 3. All other material in the standard remained unchanged.

In addition to a general update to match current industry practices, ANSI/AGMA 2003-D19, which replaces ANSI/AGMA 2003-C10, also includes the following updates:

- a. extensively rewrote Clause 4 criteria for gear tooth capacity;
- b. adjusted constants in equations for more accurate imperial-to-metric results;
- c. added to section 21 explanation why bending stress numbers of bevel gears are lower compared to spur and helical gears;
- d. recalculated the sample problem with additional information.

The first draft of ANSI/AGMA 2003-D19 was made in June 2016. It was approved by the AGMA membership in March 2019. It was approved as an American National Standard on May 14, 2019.

Suggestions for improvement of this standard will be welcome. They should be sent to tech@agma.org.

This is a preview of "ANSI/AGMA 2003-D19". Click here to purchase the full version from the ANSI store.

# **PERSONNEL** of the AGMA Bevel Gearing Committee

| Chairman: Robert F. Wasilewski | Arrow Gear Company |
|--------------------------------|--------------------|
| Vice Chairman: George Lian     | Member Emeritus    |

# **ACTIVE MEMBERS**

| D. Bodily  | FLSmidth Inc.      |
|------------|--------------------|
| R. Calvert |                    |
| J. Kuker   |                    |
| J. Kolonko | Rexnord Gear Group |
| W. Tsung   |                    |
| C. Weyand  |                    |

#### **AMERICAN NATIONAL STANDARD**

**ANSI/AGMA 2003-D19** 

# American National Standard –

# Rating the Pitting Resistance and Bending Strength of Generated Straight Bevel, Zerol Bevel and Spiral Bevel Gear Teeth

## 1 Scope

## 1.1 Rating formulas

This standard provides a method by which different gear designs can be compared.

The formulas in this standard are intended to establish a uniformly acceptable method for calculating the pitting resistance and bending strength capacity of generated straight bevel, zerol bevel and spiral bevel gear teeth; curved and skewed tooth. They apply equally to tapered depth and uniform depth teeth.

The knowledge and judgment required to evaluate the various rating factors come from years of accumulated experience in designing, manufacturing and operating gear units. Empirical factors given in this standard are general in nature. AGMA application standards may use other empirical factors that are more closely suited to the particular field of application. This standard is intended for use by the experienced gear designer, capable of selecting reasonable values for the factors. It is not intended for use by the engineering public at large.

# 1.2 Exceptions

The rating formulas in this standard are not applicable to other types of gear tooth deterioration such as scuffing, wear, plastic yielding, scoring, case crushing and welding and are not applicable when vibratory conditions exceed the limits specified for the normal operation of the gears (see ANSI/AGMA 6000-B96, Specification for Measurement of Lateral Vibration on Gear Units).

The formulas of this standard are not applicable when any of the following conditions exist:

- bevel gears with offset, such as hypoids;
- straight and zerol bevel gears with transverse contact ratios,  $m_n$  ( $\varepsilon_a$ ) less than 1.0;
- bevel gears with modified contact ratios,  $m_o$  ( $\varepsilon_o$ ) less than 1.0;
- bevel gears which have a poor contact pattern;
- interference exists between tips of teeth and root fillets;
- teeth are pointed;
- backlash is zero;
- bevel teeth finished by forging, casting or sintering.

Design considerations to prevent fractures emanating from stress risers on the tooth profile, tip chipping and failures of the gear blank through the web or hub should be analyzed by general machine design methods.

NOTE: For the purposes of this document, pitting is meant as macropitting unless otherwise stated.

#### 1.2.1 Scuffing

Formulas for scuffing resistance on bevel gear teeth are not included in this standard. At the present time, there is insufficient agreement concerning the method for designing bevel gears to resist scuffing failure.