



AREVA

ASME NUCLEAR CODES AND STANDARDS

Supporting New Build and Nuclear Manufacturing in South Africa

Session 3: ASME Section III, Component Design and Construction, Including

Application to the AREVA EPR






Philippe MALOUINES
Regulations and Codes Advisor
ASME Inspector
AREVA NP-EIRA

- ▶ **AREVA welcomes you in Session 3**
- ▶ **1. Present situation: which Code for EPR components ?**
- ▶ **2. Principles of Code selection**
- ▶ **3. Origin of RCC-M rules and recent evolutions**
- ▶ **4. ASME vs RCC-M : puzzles and overlappings**
- ▶ **5. Conclusions**



1. Which code for AREVA EPR for NI, safety class 1 main component?

| | | | |
|----------------------------|-------------------|---|--|
| EPR Olkiluoto 3 Finland | RCC-M 2005 | Started, in progress  | Finnish regulation refers to ASME Sect.III or <i>other equivalent Code</i> |
| EPR Flamanville 3 | RCC-M 2007 | Started, in progress  | French regulation does not make mandatory any Code |
| EPR Taishan | RCC-M 2007 | Started  | Chinese regulation does not make mandatory any Code |
| EPR USA | ASME III | Pre-licencing phase | US regulation makes ASME consistent with any licence |

1. Which code for AREVA EPR: NI (SC2 & SC3 & NC), BOP, CI ?

| | | |
|----------------------------|---|--|
| EPR Olkiluoto 3 Finland | RCC-M 2005, ASME Sect. III , Sect. VIII, KTA, EN 13445, EN 13480,... | YVL:Finnish regulation, includes CE assessment for nuclear Not Classified (NC) equipment. |
| EPR Flamanville 3 | RCC-M 2007, ASME Sect. III and Sect. VIII, KTA, EN 13445, EN 13480,... | French regulation includes CE assessment for nuclear Not Classified (NC) equipment |
| EPR Taishan | RCC-M 2007 level 2 and 3, ASME Sect. III and Sect. VIII, EN 13445, EN 13480, Chinese standards | Chinese regulation does not make mandatory any Code |
| EPR USA | ASME Sect. III, Sect. VIII, | US regulation makes ASME consistent with any licence |

NI: Nuclear Island

CI: Conventional Island

BOP: Balance of Plant

CE: Stamp witnessing the conformity to European Regulations

2. Principles for Code selection

- ▶ Principles applied as a function of safety classification: Safety Report of the Owner is the base
- ▶ Needs
 - ◆ High level of Safety
 - ◆ High availability factor during 60 years
 - ◆ Reasonable equipment and maintenance costs
 - ◆ Low radiation exposure of workers
 - ◆ Standardization to benefit from experience
- ▶ Industrial context
 - ◆ Equipment requirements from Contractor Engineering departments
 - ◆ Consideration of Suppliers experience: market opening
 - ◆ Evolutionary Pressurized Water Reactor first developed in a French-German context. Today ready for US and deployment anywhere in the world.

2. Approach for specifying Equipment

▶ Global Safety Approach

- ◆ **Careful** selection of Materials
- ◆ Optimized System and Equipment design
- ◆ Low probability of Defect
- ◆ **Careful** Non-Destructive Examinations
- ◆ Implementation of QA System (Regulation RD 0034 in RSA)
- ◆ When needed (regulations), measures allowing a "break preclusion concept" to be used
- ◆ When needed (regulations), severe accidental conditions to be considered (Finland).


▶ Classification of Equipment

- ◆ As a function of Safety class (SC1, SC2, SC3)
- ◆ *As a function of Nuclear Pressure Equipment Regulations (« N1, N2, N3 » in the context of the French Regulation)*

As a result, equipment are classified in "Quality Classes" Q1, Q2, Q3

2. General strategy for EPR Codes and Standards selection: Nuclear Island, Balance of Plant, Conventional Island.


Classification



2. Consequences on Q2/Q3,NC Equipment Specifications

▶ **Necessity to adapt equipment specifications with**

- ◆ Provisions in addition to the code



▶ **Philosophy**

- ◆ Supplement with adequate provisions the applicable codes and/or standards
- ◆ Reach an equivalent global quality level

▶ **Compatibility conditions whenever several codes are used**

- Compatibility on dimensions
- Compatibility with hypotheses on general system design
- Consideration of fatigue risks
- Specification of applicable criteria levels
- Consideration of inspection liable to affect design
- Consistency of materials and range of approval of qualifications
- Pressure tests, Cleanliness...

2. Established conclusions for Nuclear Codes approach


Not only from AREVA' point of view...

Multinational Design Evaluation Programme
 Working Group on Component Manufacturing Oversight
 Issy-les-Moulineaux, France

**Comparison Between
 ASME Section III and RCC-M Codes
 for Component Construction**

Rick Swayne
 Reedy Engineering
 ASME Board on Nuclear Codes & Standards
 Chair, Task Group on Globalization

February 26, 2007



Conclusions

- ASME Section III and RCC-M Code are similar.
- ASME Section III and RCC-M have different approaches to ensuring compliance with technical requirements
- ASME Section III and RCC-M provide equivalent safety in operation.

3. Historical Aspects : origin of RCC rules

US regulations, codes and standards for the general design of systems and components

French and European rules, regulations and practices for the construction of components

PWR technology progressively adapted to French and European industrial and regulatory context

First RCC-M was picture of practices in 80's

Pragmatic approach: more than 60 NPP designed, manufactured, with rules set up in RCC

3. RCC-M vs ASME general organization

RCC-M Code

Section 1 Nuclear Island Components


- A General requirements
- B Class 1 components
- C Class 2 components
- D Class 3 components
- E Small components
- G Core support structures
- H Supports
- J Storage tanks
- P Containment penetrations
- Z Technical appendices

Section 2 Materials

Section 3 Examination methods

Section 4 Welding

Section 5 Fabrication



ASME Code

Section III



NCA

NB

NC

ND

None

NG

NF

NC/ND 3800-3900

NE

Appendices




Section II

Section V

Section IX (Qualifications)

Various parts of Sect. III

3. How are established RCC requirements: in Afcen



3. Main points of RCC-M approach and evolutions

- ▶ **RCC codes are Tools**
 - ◆ Integrating construction and operation experience
 - ◆ **Open to different regulatory contexts**
- ▶ **RCC-M is continuously evolving as a function of**
 - ◆ Contractor and Supplier experience and research,
 - ◆ Projects needs
 - ◆ Evolution of International standards: calculations,...
 - ◆ Regulatory evolutions
- ▶ **RCC-M 2007 edition integrates**
 - ◆ EPR project needs
 - ◆ Standards updating
 - ◆ Regulatory evolutions resulting from European PED and French ESPN Order: *example for materials requirements* ▶
- ▶ **Integration of appendices covering other regulatory contexts under consideration: *example*** ▶

No drastic changes
Continuous adaptations

4. RCC-M technical differences vs ASME III

| | Technical differences * |
|--|-------------------------|
| ▶ Design | |
| ♦ Mechanical resistance | 2,4,7,8 |
| ♦ Functional requirements out of scope | |
| ▶ Materials | |
| ♦ Materials selection | 3,5,6 |
| ♦ Procurement | |
| ♦ Part qualification | 1 |
| ▶ Manufacturing | |
| ♦ Fabrication and welding | 9,13 |
| ♦ Process and welders Qualifications | 10, |
| ▶ Examinations | |
| ♦ Stage | |
| ♦ Methods | 11 |
| ♦ Extent | 12 |
| ♦ Acceptance criteria | |
| ▶ Hydrostatic tests | 14 |
| ▶ Overpressure protection | |
| ♦ Issued in 2007 | |

* : source: MDEP ASME presentation


4. RCC-M technical scope vs ASME III: Technical differences

Equivalent but not identical! Reconciliation needed for the manufacturer

- 1 Material: ASME uses generic prequalification/ RCC-M uses prototype qualification (M140)
- 2 Material Stress Limits: ASME Section III, Class 2 and 3 allowable stresses are now up to 15% higher than those of the RCC-M Code, because Section III stress limits are now based on a design factor of 3.5 rather than 4
- 3 Material: RCC-M permits use of only very low carbon stainless steels with nitrogen limits. Determination of sensitivity to IGSCC, by corrosion testing, is required if the carbon content exceeds specified limits (0.03-0.04%). ASME Section III leaves material selection and IGSCC concerns to the Owner or Fabricator.
- 4 Material: RCC-M requires elevated-temperature tensile testing (base metal, weld metal, procedure qualifications) to confirm the elevated-temperature tensile and yield strengths for each heat/lot and welding procedure/ ASME relies on properties from representative heats to establish allowable stresses at elevated temperatures. Design factors compensate for unknowns and variations
- 5 Material: RCC-M requires impact testing with little regard for material composition or experience. It requires impact testing of materials that are exempted from testing by ASME Section III because of their inherent high toughness, such as austenitic stainless steel filler metal. These tests are not required by ASME Section III.
- 6 Material: RCC-M imposes a delta ferrite limit of 5-15%. The Section III limit is 5FN minimum. Section III does not have a maximum limit. High delta ferrite has not resulted in failure./ RCC-M requires corrosion testing if the carbon content exceeds 0.035%. ASME Section III does not require corrosion testing.
- 7 Design: Reinforced Openings, Class 1 Vessels - Same design approach, but RCC-M requires full stress analysis of openings, in addition to reinforcement calculations./ ASME Class 1 Piping - Same design approach, but RCC-M requires full stress analysis.
- 8 Design: Fatigue at Discontinuities - Same basic approach in both Codes, but RCC-M has add new detailed conditions of use of fatigue curves.
- 9 Welding qualification: RCC-M requires production weld test coupons. In most cases, one coupon per component, per WPS, per welder. ASME Section III does not require such coupons.
RCC-M welding procedure qualification for repair welds in castings must be performed using cast material. ASME Section III permits use of other product forms, such as plate. For ASME, procedure qualification product form has not been associated
- 10 Welding Qualification and Examination: RCC-M requires the welding procedure qualification test coupon to be examined in accordance with the production weld joint NDE requirements and to meet the applicable acceptance criteria. ASME Section III does not require this examination. ASME considers that examination of the production joint proves weld quality.
RCC-M permits no undercut. ASME Section III permits 1/32 in. (1 mm). ASME considers that undercut has not been associated with weld failure.
- 11 Examination: RCC-M requires liquid penetrant examination of all Class 1 weld preparation surfaces prior to welding. In addition, the root pass of all welds not requiring final volumetric examination (e.g., fillet or partial-penetration welds) is to be examined using the liquid penetrant method. These examinations are not required by ASME Section III. ASME considers that absence of such exams has not been associated with weld failure.
- 12 Examination: the RCC-M Code requires radiographic and surface examination of piping butt welds in all Classes. ASME Section III requires the same for Class 1, but less examination for Class 2 and 3 piping butt welds. ASME considers that higher design factor for Classes 2 and 3 compensates the reduced examination requirements.
- 13 Non-pressure-retaining Items: RCC-M specifies some requirements for non-pressure-retaining items, such as pump shafts and impellers, which are exempted from the ASME Section III requirements because they do not affect pressure boundary integrity. ASME considers that examination of these items have to be specified by the Owner or designer.
- 14 Hydrostatic Testing: RCC-M specifies higher hydrostatic test pressures than ASME Section III, especially for castings. Because the hydrostatic test does not exceed the material yield strength, the higher pressure adds no benefit. For cast components, RCC-M requires a hydrotest at 1.5 times design pressure times the ratio of the yield strength at the test temperature to the yield strength at the design temperature, up to 1.8 times design pressure. For forgings, the required test pressure is 1.25 times the yield strength ratio, not to exceed 1.5 times design pressure. The ASME Section III test pressure is 1.25 times design pressure. No failures have been attributed to a lower test pressure.
- 15 (...)


4. Fatigue analysis of crack-like discontinuities in RCC-M 2007

- Introduction of dedicated fatigue curves based on experiments (Appendix ZD 2300)



d chosen to minimize dispersion of Experimental results

- **Alternative ZD.3000 introduced:**
 - application of Neuber rule ($\Delta\sigma\Delta\varepsilon=cste$)
 - division by 1,5 before comparing to S-N CURVE (to take into account the fact that surface and size effects are integrated in the analysis)



4. ASME Organisational differences vs RCC-M or Industrial Codes or Standards

ASME:

Accreditation:

The ASME Sect. III standardized program for accreditation of manufacturers and fabricators provides great uniformity of acceptance of these organizations and therefore a great reliability on their assurance of product quality.

RCC-M does not have a generic standardized program for accreditation of manufacturers and fabricators, but relies on regulatory oversight of fabricators and technical qualification of the production workshop.

Authorized Inspection and Code Symbol Stamps:

ASME enhances reliability through use of the Authorized Nuclear Inspector (ANI or AI for Sect VIII).

Quality Assurance:

ASME Section III is similar to RCC-M. (NQA-1). ASME Section III is more technically-oriented than RCC-M and is based on US NRC requirements.

4. ASME III Organisational differences vs RCC-M or Industrial Codes or Standards

RCC-M or Industrial Codes or Standards :

European Members States, China, ...impose Third Parties for assessment of conformity and survey of manufacturing, through their regulation.

Accreditation:

RCC-M or European Standards (EN 13445...) do not required accreditation.

Only for Industrial Codes or Standards ,European Regulation (PED 97/23/EC), CE marking is the testimony of assessment under Third Party survey.

Authorized Inspection and Code Symbol Stamps:

RCC-M does not require Code Symbol Stamping.

Only for Industrial Codes or Standards CE marking is the testimony of assessment under Notified Body survey.


Quality Assurance:

RCC-M uses ISO-9000/2000 with additional requirement of IAEA 50-C-QA (GS-R-3 in 2009). RCC-M to require that the documentation package include shop travelers, which are not specifically addressed by ASME Sect. III and are not usually included in the final documentation package for Section III components

4. Third parties in EPR applied Regulation

| | | |
|---|---|---|
| <p>EPR Olkiluoto 3 Finland</p> | <p>RCC-M 2005, Level 1 level 2 and 3, ASME Sect. III and Sect.VIII, KTA, EN 13445, EN 13480,...</p> | <p>SC1&2: Finnish Nuclear Authority (STUK) SC3&4: Inspecta, Polartest, Bureau Veritas, EIRA « CE »: European Notified Bodies</p> |
| <p>EPR Flamanville 3</p> | <p>RCC-M 2007 level 2 and 3,ASME Sect. III and Sect.VIII, KTA, EN 13445, EN 13480,...</p> | <p>SC1: French Nuclear Authority (DEP or delegation). SC2, SC3: APAVE, AIB, Bureau Veritas, ASAP, HSB, CEIDRE « CE »:European Notified Bodies</p> |
| <p>EPR Taishan</p> | <p>RCC-M 2007 ,ASME Sect. III and Sect. VIII, EN 13445, EN 13480, Chinese standards</p> | <p>SC1: Chinese Nuclear Authority (NNSA), and EIRA SC2, SC3: NNSA, Third parties Non nuclear pressure equipment: third parties recognised by Chinese Authority</p> |
| <p>EPR USA</p> | <p>ASME Sect. III, Sect. VIII,</p> | <p>AIA</p> |

- ▶ **AREVA' needs for EPR can be satisfied both by ASME III or by RCC-M,**
- ▶ **Existing EPRs under construction follow RCC-M for the main safety class 1 components; for other safety class and non nuclear equipment , other codes are also used (ASME, KTA,...); however USEPR design is entirely based on ASME**
- ▶ **New non-mandatory appendix in RCC-M makes the Code « user friendly »: dedicated appendix for local regulation, like Europe, France, ...and U K, the latest one in progress.**
- ▶ **The first EPR to be built in RSA can take advantage of the opening of EPR to the Codes: all South African manufacturers having experience in ASME/ RCC-M/ KTA/ EN can be involved in a partnership for EPR construction.**






Thank you for your attention

philippe.malouines@areva.com




**Olkiluoto 3 site
In September 2008**

**Hydrostatic test
of RPV in Japan**



**Flamanville 3
site in
August 2008**

**RPV nozzle shell
of RPV in France**





广东台山核电站EPR方案



深圳中广核工程设计有限公司



Example: Materials and Procurement Regulatory requirements

- ▶ Section II updated according to recognized best practices and French regulation

| Equipment class | | N1 | N2 | N3 |
|---|---|--|---|---|
| A% Minimum elongation at fracture | Ferritic material Austenitic material Martensitic material Bolting | 20% 35% * 14% 12% with Z% ≥ 0,45 | 14% 25% 12% with Z% ≥ 0,45 | 14% |
| KV Minimum toughness | Ferritic material Austenitic material Martensitic material Bolting | 40 J at 0°C (60 J if Rm>600 MPa) 100 J at 20°C * 40 J at 0°C 40 J at 0°C | 27 J at 0°C 60 J at 20°C 40 J at 0°C | 27 J at 20°C |
| R_m Max. | | 800 MPa | - | - |

Note: *: 25% and 60 J for filler materials at procurement stage

- ▶ Limitation of Cobalt content



Example: Introduction of new appendices to be in compliance with European and French Regulation

- ▶ **On the correspondence between Regulatory provisions and RCC-M chapters**
 - ◆ **Appendix ZU and ZZ for European Pressure Equipment Directive (97/23/EC)**
 - ◆ **Appendix ZT and ZY for Nuclear Pressure Equipment French Order**

- ▶ **Content of Appendices**
 - **Content of Hazard analysis**
 - **Action by notified bodies and recognized third parties**
 - **Operating instructions**
 - **Identification of equipment**
 - **Equipment and Assemblies**
 - **Materials documents and quality system**
 - **Small components**
 - **Radiation protection**

