

**Supplement C—
Welder
Performance
Qualification
Sheet Metal Test
Requirements**



American Welding Society



Key Words — AWS Certified Welders, sheet metal welding, welders, welder certification, welder qualification

AWS QC7-93, Supplement C

Welder Performance Qualification Sheet Metal Test Requirements

Developed by
AWS Qualification and Certification Committee

Under the Direction of
AWS Education and Certification Council

Approved by
AWS Board of Directors
April 4, 1994

Abstract

This Supplement C to AWS Standard QC7, *Standard for AWS Certified Welder Program*, describes testing administered by Accredited Test Facilities to the requirements of AWS QC4-89, *Standard for Accreditation of Test Facilities for AWS Certified Welder Program*. The welder performance testing for this Supplement was developed using ANSI/AWS D9.1, *Sheet Metal Welding Code*, as reference.



American Welding Society

550 N.W. LeJeune Road, Miami, Florida 33126

Statement on Use of AWS Standards

All standards (codes, specifications, recommended practices, methods, classifications, and guides) of the American Welding Society are voluntary consensus standards that have been developed in accordance with the rules of the American National Standards Institute. When AWS standards are either incorporated in, or made part of, documents that are included in federal or state laws and regulations, or the regulations of other governmental bodies, their provisions carry the full legal authority of the statute. In such cases, any changes in those AWS standards must be approved by the governmental body having statutory jurisdiction before they can become a part of those laws and regulations. In all cases, these standards carry the full legal authority of the contract or other document that invokes the AWS standards. Where this contractual relationship exists, changes in or deviations from requirements of an AWS standard must be by agreement between the contracting parties.

International Standard Book Number: 0-87171-445-0

American Welding Society, 550 N.W. LeJeune Road, Miami, Florida 33126

© 1994 by American Welding Society. All rights reserved
Printed in the United States of America

Note: The primary purpose of AWS is to serve and benefit its members. To this end, AWS provides a forum for the exchange, consideration, and discussion of ideas and proposals that are relevant to the welding industry and the consensus of which forms the basis for these standards. By providing such a forum, AWS does not assume any duties to which a user of these standards may be required to adhere. By publishing this standard, the American Welding Society does not insure anyone using the information it contains against any liability arising from that use. Publication of a standard by the American Welding Society does not carry with it any right to make, use, or sell any patented items. Users of the information in this standard should make an independent, substantiating investigation of the validity of that information for their particular use and the patent status of any item referred to herein.

With regard to technical inquiries made concerning AWS standards, oral opinions on AWS standards may be rendered. However, such opinions represent only the personal opinions of the particular individuals giving them. These individuals do not speak on behalf of AWS, nor do these oral opinions constitute official or unofficial opinions or interpretations of AWS. In addition, oral opinions are informal and should not be used as a substitute for an official interpretation.

This standard is subject to revision at any time by the AWS Qualification and Certification Committee. It must be reviewed every five years and if not revised, it must be either reapproved or withdrawn. Comments (recommendations, additions, or deletions) and any pertinent data that may be of use in improving this standard are requested and should be addressed to AWS Headquarters. Such comments will receive careful consideration by the AWS Qualification and Certification Committee and the author of the comments will be informed of the Committee's response to the comments. Guests are invited to attend all meetings of the AWS Qualification and Certification Committee to express their comments verbally. Procedures for appeal of an adverse decision concerning all such comments are provided in the Rules of Operation of the Qualification and Certification Committee. A copy of these Rules can be obtained from the American Welding Society, 550 N.W. LeJeune Road, Miami, Florida 33126.

Personnel

AWS Committee on Qualification and Certification

<i>C. E. Pepper, Chairman</i>	Oak Ridge Nat'l Laboratory
<i>R. K. Wiswesser, 1st Vice Chairman</i>	Welder Training and Testing Institute
<i>J. F. Harris, 2nd Vice Chairman</i>	Centerior Energy
<i>L. P. Connor, Secretary</i>	American Welding Society
<i>E. M. Beck *</i>	Law Engineering Incorporated
<i>W. F. Behnke</i>	Ford Motor Company/Sterling Plant
<i>E. R. Bohnart</i>	Miller Electric Manufacturing Company
<i>H. Chapman</i>	Consultant
<i>H. F. Clark II</i>	Fluor Daniel, Incorporated
<i>A. L. Collin*</i>	Consulting Engineer
<i>P. R. Evans</i>	B&W Nuclear Technologies
<i>H. W. Goser</i>	Stupp Brothers Bridge and Iron Company
<i>W. L. Green*</i>	Retired, Ohio State University
<i>J. E. Greer</i>	Moraine Valley Community College
<i>M. L. Houle*</i>	Consultant
<i>W. H. Kennedy</i>	Canadian Welding Bureau
<i>R. E. Long</i>	Consultant
<i>S. P. Martin</i>	General Dynamics Land Systems
<i>R. D. Messer</i>	Exxon Chemical
<i>A. L. Petroski</i>	Valmet Paper Machinery
<i>R. R. Picard</i>	ASEA Brown Boveri
<i>S. L. Raymond</i>	National Training Fund/Sheet Metal Workers
<i>T. Schlafly *</i>	AISC
<i>S. W. Scott*</i>	Westinghouse Hanford Company
<i>R. M. Simons*</i>	Washington Public Supply System
<i>W. F. Urbick*</i>	Welding Management Consultants
<i>R. F. Waite</i>	Consultant
<i>F. G. DeLaurier, Ex-Officio</i>	American Welding Society
<i>L. G. Kvidahl, Ex-Officio</i>	American Welding Society President
<i>R. J. Dybas, Ex-Officio</i>	General Electric
<i>J. C. Papritan, Ex-Officio</i>	Ohio State University

*Advisor

AWS Subcommittee on Certification of Welders/Welding Operators

<i>R. K. Wiswesser, Chairman</i>	Welder Training and Testing Institute
<i>J. H. Balch</i>	National Pipeline Welding School
<i>H. Chapman</i>	Consultant
<i>H. F. Clark, II</i>	Fluor Daniel Incorporated
<i>A. L. Collin*</i>	Consulting Engineer
<i>D. H. Delk</i>	United States Air Force
<i>P. R. Evans</i>	B&W Nuclear Technologies
<i>H. W. Goser</i>	Stupp Brothers Bridge and Iron Company
<i>R. L. Harris*</i>	Consultant
<i>R. E. Long</i>	Consultant
<i>R. D. Messer</i>	Exxon Chemical
<i>J. S. Pawluk*</i>	Western Nevada Community College
<i>C. E. Pepper</i>	Oak Ridge National Laboratory
<i>A. L. Petroski</i>	Valmet Paper Machinery
<i>L. C. Pratt</i>	Ingalls Shipbuilding
<i>S. L. Raymond</i>	National Training Fund/Sheet Metal Workers
<i>M. L. Slaton*</i>	The Pritchard Corporation
<i>L. D. Smith</i>	Beloit Corporation/Paper Machinery Division
<i>W. E. Strate</i>	Strate Welding Supply Company
<i>W. F. Urbick</i>	Welding Management Consultants

*Advisor

Foreword

(This Foreword is not a part of Supplement C to AWS QC7-93, *Standard for AWS Certified Welders*, but is included only for information.)

The American Welding Society (AWS) Certified Welder Program is established to identify all elements necessary to implement a National Registry of Certified Welders. Four key elements are identified:

- (1) Welder performance qualification standards
- (2) Standard welding procedure specifications
- (3) Accredited performance qualification test facilities
- (4) AWS welder certification requirements

Supplement C, *Welder Performance Qualification Sheet Metal Test Requirements and AWS QC7-93, Standard for AWS Certified Welders*, contain the criteria for AWS Certified Welder Program and the AWS National Registry of Welders. Public listing or disclosure is at the option of the individual welder. It is expected that all four elements outlined above will allow the transfer of welder qualification from employer to employer. This potential transfer of welder qualification can affect financial savings to the welding industry.

The purpose of the QC7-93 is to document the ability of welders to deposit sound welds in accordance with standardized requirements and to impose sufficient controls on the documentation and maintenance of certification to allow transfer between employers without requalification, where allowed by Standard or Contract documents.

Supplement C shall be used in conjunction with AWS QC7-93. This Supplement C is not a standard unto itself and shall be considered only as a supplementary part of AWS QC7-93. The intent of this supplement is to provide welder performance test data to the industry that all employers may use without retesting each welder.

This supplement does not apply to employers that conduct welder qualification tests for their own employees in accordance with ANSI/AWS D9.1, *Sheet Metal Welding Code*. Supplement C to AWS QC7-93 specifies requirements intended to provide an *alternative* welders certification method to comply with the requirements of ANSI/AWS D9.1.

Table of Contents

	Page No.
<i>Personnel</i>	iii
<i>Foreword</i>	v
C1. Scope	1
C1.1 Program	1
C1.2 Exclusion	1
C1.3 Limitation	1
C1.4 Safety Precautions	1
C2. Definitions	1
C3. Responsibilities Regarding AWS Certified Welders	1
C3.1 Employer Responsibility	1
C3.2 Employer Obligation	1
C3.3 Qualification & Certification Department Responsibilities	2
C3.4 Test Facility Responsibilities	2
C4. Provisions for Testing	2
C4.1 Welding Procedure Specification (WPS)	2
C4.2 Test Facilities	2
C5. Certification Requisites	2
C5.1 Test Control	2
C5.2 Test Supervisor	2
C5.3 Test Facility	2
C6. Performance Test	2
C6.1 Identification	2
C6.2 Verification	2
C6.3 Safety Equipment	2
C6.4 Machine Adjustment	2
C6.5 Material Check	2
C6.6 Fit-Up	2
C6.7 Assembly Control	2
C6.8 Positioning	2
C6.9 Eye Correction	3
C6.10 Power Tools	3
C7. Examination Methods and Acceptance Standards	3
C8. Retests	3
C8.1 Immediate Retest	3
C8.2 Retest After Further Training or Practice	3
C9. Documentation of Welder Performance Qualification	3
C10. Period of Effectiveness	3

C11. Identification/Certification Documents	3
C12. Maintenance of Certification	3
C13. Renewal of Certification	3
C14. Revocation	3

Forms

QC-WF1C — Welder Qualification Test Record	4
QC-WF3A — Maintenance of Certification	5

List of Performance Test Descriptions

C-1 GMAW — 18 Gauge Coated Steel	6
C-2 GMAW — 18 Gauge Coated Steel	8
C-3 GMAW — 18 Gauge Coated Steel	10
C-4 GMAW — 10 Gauge Coated Steel	12
C-5 GMAW — 10 Gauge Coated Steel	14
C-6 GMAW — 10 Gauge Coated Steel	16
C-7 GMAW — 18 Gauge Stainless Steel	18
C-8 GMAW — 18 Gauge Stainless Steel	20
C-9 GMAW — 18 Gauge Stainless Steel	22
C-10 GMAW — 10 Gauge Stainless Steel	24
C-11 GMAW — 10 Gauge Stainless Steel	26
C-12 GMAW — 10 Gauge Stainless Steel	28

Supplement C

Welder Performance Qualification

Sheet Metal Test Requirements

C1. Scope

This Supplement C to AWS QC7-93, *Standard for AWS Certified Welders*, specifies requirements intended to provide an alternative welders certification method. The rules for performance qualification are defined in ANSI/AWS D9.1, *Sheet Metal Welding Code*. When the term certified welder is used it shall also denote "welding operator."

C1.1 Program. The administrative rules for the American Welding Society (AWS) Certified Welder Program and the requirements for maintenance of certification are provided in AWS QC7-93, *Standard for AWS Certified Welders*. Test facilities participating in the program are required to meet AWS QC4, *Standard for Accreditation of Test Facilities for AWS Certified Welder Program*.

C1.2 Exclusion. Neither AWS QC7-93 nor this Supplement C prevents or supersedes a Contractor from continuing to qualify welders in accordance with ANSI/AWS D9.1 or other standards. Employers may impose supplementary requirements in addition to this standard.

C1.3 Limitation. Welders participating in the AWS Certified Welder Program shall be limited to those welding essential variables defined in the applicable Performance Tests Descriptions.

C1.4 Safety Precautions. This document is not intended to address safety and health matters regarding the training of certified welders. This document only covers the rules of certification of welders to AWS QC7-93.

C2. Definitions

The terms used in this Supplement C are defined in AWS QC7-93 and ANSI/AWS A3.0, *Standard Welding Terms and Definitions*, except as follows:

Employer. The term is used collectively to mean contractor, fabricator, erector or manufacturer.

C3. Responsibilities Regarding AWS Certified Welders

C3.1 Employer Responsibility. The employers of AWS Certified Welders are responsible for the work performed by their employees. The employers may accept the AWS certification without additional testing or may add requirements as deemed necessary to meet their particular need.

C3.2 Employer Obligation. Companies who employ AWS certified welders should be fully aware of the provisions of the AWS QC7-93 standard and of this Supplement C.

C3.2.1 Employers should specifically note the extent of qualification as stated on the AWS welder certification card.

C3.2.2 The employer shall obtain a copy of the Performance Qualification Test Record from the AWS Qualification and Certification Department.

C3.2.3 The welders current status shall be checked with the Qualification and Certification Department.

C3.2.4 The employer shall maintain a record of performance for all welders during their periods of employment. The backup record to be filed with the employer's certification shall be the completed Performance Test Description and Limitation of Variables form prepared by the Accredited Test Facilities. A suggested certification record is shown in Form QC-WFC1, Welder Qualification Test Record.

C3.2.5 The Employer is responsible for all work performed by their employees; and therefore, should verify that the qualification(s) apply to each employee's work.

C3.2.6 The use of these qualifications may require the approval of the Engineer or Owner. The employer shall obtain such approval when required.

C3.3 Qualification and Certification Department Responsibilities. The Qualification and Certification Department shall complete the responsibilities defined in AWS QC7-93, 3.3.

C3.4 Test Facility Responsibilities. The Test Facility is responsible for safety and health matters during testing at that location in addition to other requirements stated herein.

C4. Provisions for Testing

C4.1 Welding Procedure Specification (WPS). The WPSs incorporated in this Supplement C shall be used to qualify welders to this standard. The WPSs in this supplement are for qualification of welders. Production welding procedures shall be provided by employers in accordance with AWS D9.1.

C4.2 Test Facilities. The Test Facilities for this AWS Welder Certification program shall comply with the requirements of AWS QC7-93, 4, Provisions for Testing. The Test Facility shall have been accredited according to AWS QC4, *Standard for Accreditation of Test Facilities for AWS Certified Welder Program*.

C5. Certification Requisites

C5.1 Test Control

C5.1.1 Performance qualification test coupons shall be welded in accordance with a written WPS and the Performance Test Description.

C5.1.2 Performance Test Descriptions include welding variables and define the limits of qualification for each test.

C5.2 Test Supervisor

C5.2.1 Qualification testing shall be performed under the direction of a person designated as the Test Super-

visor in accordance with AWS QC4, *Standard for Accreditation of Test Facilities for AWS Certified Welder Program*.

C5.2.2 The Test Supervisor shall be responsible for the performance qualification in accordance with this Supplement C.

C5.2.3 If during qualification testing, the Test Supervisor determines that the welder does not exhibit the skill to perform the test satisfactorily, the test may be terminated.

C5.2.4 The Test Supervisor may allow a welder to retest immediately or may require additional training or practice prior to retesting in accordance with C7, Retests.

C5.2.5 The Test Supervisor shall be responsible for enforcement of test shop safety rules, procedures, and cleanliness, as established by the Test Facility QA Manual.

C5.3 Test Facility. The Test Facility conducts the qualification tests and prepares the test reports. The American Welding Society issues the certification.

C6. Performance Test

C6.1 Identification. The applicant shall be assigned an identification letter, symbol or number, and this identifier shall be marked on the test materials and records.

C6.2 Verification. Prior to the initiation of welding, the applicant's photographic identification shall be verified by the Test Supervisor.

C6.3 Safety Equipment. The applicant shall use personal safety equipment applicable for the welding process. The safety requirements of the Accredited Test Facility shall conform to the requirements of ANSI/ASC Z49.1.

C6.4 Machine Adjustment. Before starting the qualification test, the welder shall adjust the machine settings to meet those of the WPS.

C6.5 Material Check. The base material and filler metal identifications shall be verified by the Test Supervisor prior to tack welding.

C6.6 Fit-Up. The applicant shall assemble the specified test assembly(ies) for welding in accordance with the WPS. The test assembly shall be verified by the Test Supervisor. The Test Supervisor shall inspect each test assembly prior to welding in accordance with AWS D9.1.

C6.7 Assembly Control. The Test Supervisor shall witness the placing of each test assembly in the specified welding position and shall mark the test assembly, or secure it, so that it remains in the specified position until welding has been completed.

C6.8 Positioning. All cleaning, grinding, chipping of slag or other in-process operations shall be performed

with the test assembly in the specified welding position. Evidence of removal of the test assembly or movement from the original location, except by accidental means (subject to concurrence by the Test Supervisor), shall be cause for test termination.

C6.9 Eye Correction. The Test Supervisor shall note the use of and type of eye correction on the Welder Qualification Test Record. The welder's certification card shall also reflect eye correction use.

C6.10 Power Tools. Any use, or lack of use, of power tools shall be noted on the Welding Qualification Test Record by the Test Supervisor.

C7. Examination Methods and Acceptance Standards

C7.1 All additional tests required by ANSI/AWS D9.1 shall be conducted under the supervision of the Test Supervisor.

C7.2 Visual Examination. The test plates shall meet the visual acceptance criteria for performance testing as defined in ANSI/AWS D9.1. The visual examination shall be performed by a current CWI without aid of magnification.

C8. Retests

If the welder performance test fails to meet the requirements a retest of each test failed may be allowed under the following conditions:

C8.1 Immediate Retest. No more than three immediate retests shall be permitted. The retest specimens shall meet all of the specified requirements.

C8.2 Retest after Further Training or Practice. A retest may be made, provided there is evidence that the welder has had further training or practice. A complete retest of the types and positions failed shall be made.

C9. Documentation of Welder Performance Qualification

The performance qualification data and results of the examination and testing shall be recorded on QC-WF1C. Records of applicants that meet the requirements shall be processed in accordance with AWS QC7-93.

C10. Period of Effectiveness

C10.1 The period of certification is twelve months. The period begins on the date of completion of the examina-

tion results and signature by the Test Supervisor. Thereafter, the certification shall be considered as remaining in effect indefinitely unless:

(1) the welder is not engaged in a given welding process for which the welder is certified for a period exceeding twelve months unless otherwise specified by ANSI/AWS D9.1, or

(2) there is some specific reason to question the welder's ability.

C10.2 Indefinite certification in accordance with C10 may be maintained by documenting the use of the welding process in accordance with C12, Maintenance of Certification.

C11. Identification/Certification Documents

The welder certification card is issued by AWS in accordance with AWS QC7-93.

C12. Maintenance of Certification

Welders may maintain their certification indefinitely by verifying the use of the welding process(es). The use of the process(es) shall be verified by the welder submitting completed forms required in AWS QC7-93, 11, Maintenance and Certification each year as a minimum. Such forms shall be postmarked prior to the expiration of certification. The certification expiration date is extended for a period of 12 months, as defined in ANSI/AWS D9.1 from the date of the last use of the process(es), as documented on Form QC-WF3A, received and accepted by the AWS Qualification and Certification Department.

After the certification period has expired, without the welder using the process, a single test need be made only in any thickness for each process in which the welder is qualified. Successful completion of such test restores all of the previous qualifications for the process tested.

C13. Renewal of Certification

Renewal of certifications shall be in accordance with AWS QC7-93, 12, Renewal of Certification.

C14. Revocation

The AWS Certification of a welder may be revoked in accordance with the administrative procedures defined in AWS QC7-93, 13, Revocation.

WELDER AND WELDING OPERATOR PERFORMANCE QUALIFICATION TEST RECORD

Qualification Test Performed

Name _____ WPS Number _____
 I.D. No. _____ Base Metal _____
 Date of Test _____ Gauge _____
 Test Position _____ Square groove (butt joint) _____
 Shield gas used _____ Code ANSI/AWS D9.1 _____
 Eye correction used _____ Yes _____ No Performance Test Description No. _____
 Power tools used _____ Yes _____ No

Essential Variables Qualified by Test

Type of base metal _____ Welding process _____
 Thickness _____ Min _____ Max Method of application _____
 _____ Manual _____ Semiautomatic
 _____ Automatic
 Uncoated Sheet _____ Yes _____ No Mode of transfer (GMAW) _____
 Coating material on sheet _____ Yes _____ No Welding Current _____ ac _____ dce _____ dcep
 Backing material _____ Shield gas used _____
 Filler metal specification _____ Positions qualified _____ Flat _____ Horizontal
 Filler Metal Classification _____ _____ Vertical _____ Overhead

Visual Inspection Results

Condition	Acceptable	Unacceptable
Complete fusion	_____	_____
Complete joint penetration	_____	_____
Maximum face and root reinforcement — 1/8 in.	_____	_____
No more than one visible pore per in. of weld	_____	_____
Maximum pore or inclusion size — 0.25 t where t = base metal thickness	_____	_____
No undercut exceeding 0.15 t for t less than or equal to 0.187 in.	_____	_____
No undercut exceeding 0.25 t for t greater than 0.187 in.	_____	_____
No cracks	_____	_____

Date Tested _____

Signed By _____
 Test Supervisor

Test Facility _____

AWS CWI No. _____

Test Facility No. _____

Date Signed _____

MAINTENANCE OF CERTIFICATION

Name _____ I.D. # _____

Enter date of last use of each of the following process(es):

SMAW _____ FCAW _____ GTAW _____

GMAW _____ SAW _____ Other _____

CERTIFICATION IS EXTENDED FROM DATE INDICATED ABOVE

Employer/Test Supervisor/Customer (circle one) Verification: We certify that the above named welder used the processes on the dates indicated.

Print Name _____ Title _____

Company Name _____ Phone _____

Signature _____ Date _____

WE RECOMMEND SENDING "U.S. MAIL, RETURN RECEIPT REQUESTED."

C6

**AWS QC7-93 Supplement C
Performance Test Description C-1
GMAW 18 Gauge Coated Steel**

Code: ANSI/AWS D9.1

Welding Process: Semiautomatic gas metal arc welding (GMAW) **Transfer Mode:** Short circuiting

Base Material: ASTM A526 CQ G90 or A527 LFG G90 **Coating Type:** Galvanized

Material Form: Sheet — 3" x 6" **Thickness:** 18 Gauge

Filler Metal: ANSI/AWS A5.18, Class ER-70S-X (F Number 6)

Weld Joint Detail: Square butt, root opening (R) = 0 – 1/2 t. Where t = base metal thickness

Backing: None

Welding Position(s): 4G

Vertical Welding Progression: Not applicable

Welding Procedure Specification (WPS) No.: QC7-93, C-1-O

Welding Technique: Single pass

Current: dcep

Shielding Gas: 75% Argon, 25% Carbon dioxide

Electrode Extension: 1/4 to 1/2 in.

Test Required: Visual inspection per ANSI/AWS D9.1

Limits of Welder Qualification

Code: ANSI/AWS D9.1

Welding Process: Gas metal arc welding (GMAW) — semiautomatic/automatic transfer mode — short circuiting

Base Metal: Galvanized or uncoated carbon steel (See ANSI/AWS D9.1)

Material Form: Sheet

Backing: With or without

Groove Weld Thickness: 16 Gauge and thinner

Fillet Weld Size: Unlimited

Pipe and Tubing: Not applicable

Filler Metal: ANSI/AWS A5.18, (F Number 6)

Current: dcep

Shielding Gas: 75% Argon, 25% Carbon dioxide

Positions: All groove and fillet

Vertical Welding Progression: Up or down

Welding Procedure Specification (WPS)


WPS Number C-1 Supported by PQR No.(s) WRC¹, 047A, 050A, 051B, 052B²
 WPS Rev. No. Original WPS Rev. Date January 1994

Code Reference ANSI/AWS D9.1, Sheet Metal Welding Code

Variables

Base metal ANSI/ASTM A526CQ G90 or A527LFQ G90, galvanized
 Metal thickness 18 Gauge (0.0516 in., 1.31 mm)
 Coating type Galvanized G90
 Joint preparation Shall be free of loose scale, rust, grease or foreign matter
 Backing material None
 Position of welding 4G Overhead Welding Progression: N/A
 Welding process GMAW
 Manual, semiautomatic, or automatic Semiautomatic
 Filler metal spec. ANSI/AWS A5.18
 Filler metal class ER70S-X (F Number 6)
 Electrical Characteristics dcep Electrode Extension 1/4 to 1/2 in.
 Mode of transfer Short circuit
 Shielding gas/combination 75% Argon, 25% Carbon dioxide
 Gas flow (CFH) 20-40 CFH

Joining Procedure

Filler Metal Size in.	Welding Power			Speed of Travel	Joint Detail
	Current Range Ampere	Wire Feed Speed (Reference) ipm	Voltage Range Volts		
0.035	50-130	100-230	15-17	As Required	 <p style="text-align: center;">18 ga. Root Opening</p> <p>Note: Root Opening = 0-1/2t</p>

¹Welding Research Council, 345 East 47th Street, New York, New York 10017.

²Also on file at AWS Headquarters (Qualification and Certification Dept.).

AWS QC7-93 Supplement C
Performance Test Description C-2
GMAW 18 Gauge Coated Steel

Code: ANSI/AWS D9.1

Welding Process: Semiautomatic gas metal arc welding (GMAW) **Transfer Mode:** Short circuiting

Base Material: ASTM A526 CQ G90 or A527 LFQ G90 **Coating Type:** Galvanized

Material Form: Sheet — 3" x 6" **Thickness:** 18 Gauge

Filler Metal: ANSI/AWS A5.18, Class ER-70S-X (F Number 6)

Weld Joint Detail: Square butt, root opening (R) = 0 – 1/2 t. Where t = base metal thickness

Backing: None

Welding Position(s): 3G

Vertical Welding Progression: Down

Welding Procedure Specification (WPS) No.: QC7-93, C-2-V

Welding Technique: Single pass

Current: dcep

Shielding Gas: 75% Argon, 25% Carbon dioxide

Electrode Extension: 1/4 to 1/2 in.

Test Required: Visual inspection per ANSI/AWS D9.1

Limits of Welder Qualification

Code: ANSI/AWS D9.1

Welding Process: Gas metal arc welding (GMAW) — semiautomatic/automatic transfer mode — short circuiting

Base Metal: Galvanized or uncoated carbon steel (See ANSI/AWS D9.1)

Material Form: Sheet

Backing: With or without

Groove Weld Thickness: 16 Gauge and thinner

Fillet Weld Size: Unlimited

Pipe and Tubing: Not applicable

Filler Metal: ANSI/AWS A5.18, (F Number 6)

Current: dcep

Shielding Gas: 75% Argon, 25% Carbon dioxide

Positions: Flat, horizontal and vertical groove and fillet

Vertical Welding Progression: Up or down

Welding Procedure Specification (WPS)


WPS Number C-2 Supported by PQR No.(s) WRC¹, 047A, 050A, 051B, 052B²
 WPS Rev. No. Original WPS Rev. Date January 1994

Code Reference ANSI/AWS D9.1, Sheet Metal Welding Code

Variables

Base metal ANSI/ASTM A526CQ G90 or A527LFQ G90, galvanized
 Metal thickness 18 Gauge (0.0516 in., 1.31 mm)
 Coating type Galvanized G90
 Joint preparation Shall be free of loose scale, rust, grease or foreign matter
 Backing material None
 Position of welding 3G Vertical Welding Progression: Down
 Welding process GMAW
 Manual, semiautomatic, or automatic Semiautomatic
 Filler metal spec. ANSI/AWS A5.18
 Filler metal class dcep
 Electrical Characteristics dcep Electrode Extension 1/4 to 1/2 in.
 Mode of transfer Short circuit
 Shielding gas/combination 75% Argon, 25% Carbon dioxide
 Gas flow (CFH) 20-40 CFH

Joining Procedure

Filler Metal Size in.	Welding Power			Speed of Travel	Joint Detail
	Current Range Ampere	Wire Feed Speed (Reference) ipm	Voltage Range Volts		
0.035	50-130	100-230	15-17	As Required	 <p>Note: Root Opening = 0-1/2t</p>

¹Welding Research Council, 345 East 47th Street, New York, New York 10017.

²Also on file at AWS Headquarters (Qualification and Certification Dept.).

AWS QC7-93 Supplement C
Performance Test Description C-3
GMAW Coated Steel

Code: ANSI/AWS D9.1

Welding Process: Semiautomatic gas metal arc welding (GMAW) **Transfer Mode:** Short circuiting

Base Material: ASTM A526 CQ G90 or A527 LFQ G90 **Coating Type:** Galvanized

Material Form: Sheet — 3" x 6"

Thickness: 18 Gauge

Filler Metal: ANSI/AWS A5.18, (F Number 6)

Weld Joint Detail: Square butt, root opening (R) = 0 – 1/2 t. Where t = base metal thickness

Backing: None

Welding Position(s): 1G

Vertical Welding Progression: Not applicable

Welding Procedure Specification (WPS) No.: QC7-93, C-3-F

Welding Technique: Single pass

Current: dcep

Shielding Gas: 75% Argon, 25% Carbon dioxide

Electrode Extension: 1/4 to 1/2 in.

Test Required: Visual inspection per ANSI/AWS D9.1

Limits of Welder Qualification

Code: ANSI/AWS D9.1

Welding Process: Gas metal arc welding (GMAW) — semiautomatic/automatic transfer mode — short circuiting

Base Metal: Galvanized or uncoated carbon steel (See ANSI/AWS D9.1)

Material Form: Sheet

Backing: With or without

Groove Weld Thickness: 16 Gauge and thinner

Fillet Weld Size: Unlimited

Pipe and Tubing: Not applicable

Filler Metal: ANSI/AWS A5.18, (F Number 6)

Current: dcep

Shielding Gas: 75% Argon, 25% Carbon dioxide

Positions: Flat groove and fillet

Vertical Welding Progression: Not applicable

Welding Procedure Specification (WPS)


WPS Number C-3 Supported by PQR No.(s) WRC', 047A, 050A, 051B, 052B'
 WPS Rev. No. Original WPS Rev. Date January 1994

Code Reference ANSI/AWS D9.1, Sheet Metal Welding Code

Variables

Base metal ANSI/ASTM A526CQ G90 or A527LFQ G90, galvanized
 Metal thickness 18 Gauge (0.0516 in., 1.31 mm)
 Coating type Galvanized G90
 Joint preparation Shall be free of loose scale, rust, grease or foreign matter
 Backing material None
 Position of welding 1G Flat Welding Progression: N/A
 Welding process GMAW
 Manual, semiautomatic, or automatic Semiautomatic
 Filler metal spec. ANSI/AWS A5.18
 Filler metal class ER70S-X
 Electrical Characteristics dcep Electrode Extension 1/4 to 1/2 in.
 Mode of transfer Short circuit
 Shielding gas/combination 75% Argon, 25% Carbon dioxide
 Gas flow (CFH) 20-40 CFH

Joining Procedure

Filler Metal Size in.	Welding Power			Speed of Travel	Joint Detail
	Current Range Ampere	Wire Feed Speed (Reference) ipm	Voltage Range Volts		
0.035	50-130	100-230	15-17	As Required	 <p>Note: Root Opening = 0-1/2t</p>

¹Welding Research Council, 345 East 47th Street, New York, New York 10017.

²Also on file at AWS Headquarters (Qualification and Certification Dept.).

AWS QC7-93 Supplement C
Performance Test Description C-4
GMAW Coated Steel

Code: ANSI/AWS D9.1

Welding Process: Semiautomatic gas metal arc welding (GMAW) **Transfer Mode:** Short circuiting

Base Material: ASTM A526 CQ G90 or A527 LFQ G90 **Coating Type:** Galvanized

Material Form: Sheet — 3" x 6" **Thickness:** 10 Gauge

Filler Metal: ANSI/AWS A5.18, Class ER-70S-X (F Number 6)

Weld Joint Detail: Square butt, root opening (R) = 0 – 1/2 t. Where t = base metal thickness

Backing: None

Welding Position(s): 4G

Vertical Welding Progression: Not applicable

Welding Procedure Specification (WPS) No.: QC7-93, C-4-0

Welding Technique: Single pass

Current: dcep

Shielding Gas: 75% Argon, 25% Carbon dioxide

Electrode Extension: 1/4 to 1/2 in.

Test Required: Visual inspection per ANSI/AWS D9.1

Limits of Welder Qualification

Code: ANSI/AWS D9.1

Welding Process: Gas metal arc welding (GMAW) — semiautomatic/automatic transfer mode — short circuiting

Base Metal: Galvanized or uncoated carbon steel (See ANSI/AWS D9.1)

Material Form: Sheet

Backing: With or without

Groove Weld Thickness: 16 Gauge to 0.276 in.

Fillet Weld Size: Unlimited

Pipe and Tubing: Not applicable

Filler Metal: ANSI/AWS A5.18, (F Number 6)

Current: dcep

Shielding Gas: 75% Argon, 25% Carbon dioxide

Positions: All groove and fillet

Vertical Welding Progression: Up or down

Welding Procedure Specification (WPS)


WPS Number C-4 Supported by PQR No.(s) WRC¹, 048A, 049A, 053A, 054B, 055B²
 WPS Rev. No. Original WPS Rev. Date January 1994

Code Reference ANSI/AWS D9.1, Sheet Metal Welding Code

Variables

Base metal ANSI/ASTM A526CQ G90 or A527LFQ G90, galvanized
 Metal thickness 10 Gauge (0.1382 in., 3.51 mm)
 Coating type Galvanized G90
 Joint preparation Shall be free of loose scale, rust, grease or foreign matter
 Backing material None
 Position of welding 4G Overhead Welding Progression: N/A
 Welding process GMAW
 Manual, semiautomatic, or automatic Semiautomatic
 Filler metal spec. ANSI/AWS A5.18
 Filler metal class ER70S-X
 Electrical Characteristics dcep Electrode Extension 1/4 to 1/2 in.
 Mode of transfer Short circuit
 Shielding gas/combination 75% Argon, 25% Carbon dioxide
 Gas flow (CFH) 20-40 CFH

Joining Procedure

Filler Metal Size in.	Welding Power			Speed of Travel	Joint Detail
	Current Range Ampere	Wire Feed Speed (Reference) ipm	Voltage Range Volts		
0.035	75-150	120-280	18-20	As Required	 <p>Note: Root Opening = 0-1/2t</p>

¹Welding Research Council, 345 East 47th Street, New York, New York 10017.

²Also on file at AWS Headquarters (Qualification and Certification Dept.).

AWS QC7-93 Supplement C
Performance Test Description C-5
GMAW Coated Steel

Code: ANSI/AWS D9.1

Welding Process: Semiautomatic gas metal arc welding (GMAW) **Transfer Mode:** Short circuiting

Base Material: ASTM A526 CQ G90 or A527 LFQ G90 **Coating Type:** Galvanized

Material Form: Sheet — 3" x 6" **Thickness:** 10 Gauge

Filler Metal: ANSI/AWS A5.18, Class ER-70S-X (F Number 6)

Weld Joint Detail: square butt, root opening (R) = 0 - 1/2 t. Where t = base metal thickness

Backing: None

Welding Position(s): 3G

Vertical Welding Progression: Down

Welding Procedure Specification (WPS) No.: QC7-93, C-5-V

Welding Technique: Single pass

Current: dcep

Shielding Gas: 75% Argon, 25% Carbon dioxide

Electrode Extension: 1/4 to 1/2 in.

Test Required: Visual inspection per ANSI/AWS D9.1

Limits of Welder Qualification

Code: ANSI/AWS D9.1

Welding Process: Gas metal arc welding (GMAW) — semiautomatic/Automatic transfer mode — short circuiting

Base Metal: Galvanized or uncoated carbon steel (See ANSI/AWS D9.1)

Material Form: Sheet

Backing: With or without

Groove Weld Thickness: 16 Gauge to 0.276 in.

Fillet Weld Size: Unlimited

Pipe and Tubing: Not applicable

Filler Metal: ANSI/AWS A5.18, (F Number 6)

Current: dcep

Shielding Gas: 75% Argon, 25% Carbon dioxide

Positions: Flat, horizontal and vertical groove and fillet

Vertical Welding Progression: Up or down

Welding Procedure Specification (WPS)


WPS Number C-5 Supported by PQR No.(s) WRC¹, 048A, 049A, 053A, 054B, 055B²
 WPS Rev. No. Original WPS Rev. Date January 1994

Code Reference ANSI/AWS D9.1, Sheet Metal Welding Code

Variables

Base metal ANSI/ASTM A526CQ G90 or A527LFQ G90, galvanized
 Metal thickness 10 Gauge (0.1382 in., 1.31 mm)
 Coating type Galvanized G90
 Joint preparation Shall be free of loose scale, rust, grease or foreign matter
 Backing material None
 Position of welding 3G Vertical Welding Progression: Down
 Welding process GMAW
 Manual, semiautomatic, or automatic Semiautomatic
 Filler metal spec. ANSI/AWS A5.18
 Filler metal class ER70S-X
 Electrical Characteristics dcep Electrode Extension 1/4 to 1/2 in.
 Mode of transfer Short circuit
 Shielding gas/combination 75% Argon, 25% Carbon dioxide
 Gas flow (CFH) 20-40 CFH

Joining Procedure

Filler Metal Size in.	Welding Power			Speed of Travel	Joint Detail
	Current Range Ampere	Wire Feed Speed (Reference) ipm	Voltage Range Volts		
0.035	75-150	120-280	18-20	As Required	 <p>Note: Root Opening = 0-1/2t</p>

¹Welding Research Council, 345 East 47th Street, New York, New York 10017.

²Also on file at AWS Headquarters (Qualification and Certification Dept.).

AWS QC7-93 Supplement C
Performance Test Description C-6
GMAW Coated Steel

Code: ANSI/AWS D9.1

Welding Process: Semiautomatic gas metal arc welding (GMAW) **Transfer Mode:** Short circuiting

Base Material: ASTM A526 CQ G90 or A527 LFQ G90 **Coating Type:** Galvanized

Material Form: Sheet — 3" x 6" **Thickness:** 10 Gauge

Filler Metal: ANSI/AWS A5.18, Class ER-70S-X (F Number 6)

Weld Joint Detail: square butt, root opening (R) = 0 – 1/2 t. Where t = base metal thickness

Backing: None

Welding Position(s): 1G

Vertical Welding Progression: Not applicable

Welding Procedure Specification (WPS) No.: QC7-93, C-6-F

Welding Technique: Single pass

Current: dcep

Shielding Gas: 75% Argon, 25% Carbon dioxide

Electrode Extension: 1/4 to 1/2 in.

Test Required: Visual inspection per ANSI/AWS D9.1

Limits of Welder Qualification

Code: ANSI/AWS D9.1

Welding Process: Gas Metal Arc Welding (GMAW) — semiautomatic/automatic transfer mode — short circuiting

Base Metal: Galvanized or uncoated carbon steel (See ANSI/AWS D9.1)

Material Form: Sheet

Backing: With or Without

Groove Weld Thickness: 16 Gauge to 0.276 in.

Fillet Weld Size: Unlimited

Pipe and Tubing: Not applicable

Filler Metal: ANSI/AWS A5.18, (F Number 6)

Current: dcep

Shielding Gas: 75% Argon, 25% Carbon dioxide

Positions: Flat groove and fillet

Vertical Welding Progression: Not applicable

Welding Procedure Specification (WPS)


WPS Number C-6 Supported by PQR No.(s) WRC¹, 048A, 049A, 053A, 054B, 055B²
 WPS Rev. No. Original WPS Rev. Date January 1994

Code Reference ANSI/AWS D9.1, Sheet Metal Welding Code

Variables

Base metal ANSI/ASTM A526CQ G90 or A527LFQ G90, galvanized
 Metal thickness 10 Gauge (0.1382 in., 3.51 mm)
 Coating type Galvanized G90
 Joint preparation Shall be free of loose scale, rust, grease or foreign matter
 Backing material None
 Position of welding 1G Flat Welding Progression: N/A
 Welding process GMAW
 Manual, semiautomatic, or automatic Semiautomatic
 Filler metal spec. ANSI/AWS A5.18
 Filler metal class ER70S-X
 Electrical Characteristics dcep Electrode Extension 1/4 to 1/2 in.
 Mode of transfer Short circuit
 Shielding gas/combination 75% Argon, 25% Carbon dioxide
 Gas flow (CFH) 20-40 CFH

Joining Procedure

Filler Metal Size in.	Welding Power			Speed of Travel	Joint Detail
	Current Range Ampere	Wire Feed Speed (Reference) ipm	Voltage Range Volts		
0.035	75-150	120-280	18-20	As Required	 <p>Note: Root Opening = 0-1/2t</p>

¹Welding Research Council, 345 East 47th Street, New York, New York 10017.

²Also on file at AWS Headquarters (Qualification and Certification Dept.).

AWS QC7-93 Supplement C
Performance Test Description C-7
GMAW Stainless Steel

Code: ANSI/AWS D9.1

Welding Process: Semiautomatic gas metal arc welding (GMAW) **Transfer Mode:** Short circuiting

Base Material: ASTM A167 or A240, Type 3xx **Coating Type:** None

Material Form: Sheet — 3" x 6" **Thickness:** 18 Gauge

Filler Metal: ANSI/AWS A5.9, Class ER-3xx (F Number 6)

Weld Joint Detail: Square butt, root opening (R) = 0 – 1/2 t. Where t = base metal thickness

Backing: None

Welding Position(s): 4G

Vertical Welding Progression: Not applicable

Welding Procedure Specification (WPS) No.: QC7-93, C-7-0

Welding Technique: Single pass

Current: dcep

Shielding Gas: 90% Helium, 7.5% Argon, 2.5% Carbon dioxide

Electrode Extension: 1/4 to 3/8 in.

Test Required: Visual inspection per ANSI/AWS D9.1

Limits of Welder Qualification

Code: ANSI/AWS D9.1

Welding Process: gas metal arc welding (GMAW) — semiautomatic/automatic transfer mode — short circuiting

Base Metal: Chromium and chromium nickel steel (uncoated) (See ANSI/AWS D9.1)

Material Form: Sheet **Backing:** With or without

Groove Weld Thickness: 16 Gauge and thinner **Fillet Weld Size:** Unlimited

Pipe and Tubing: Not applicable

Filler Metal: ANSI/AWS A5.9, (F Number 6)

Current: dcep

Shielding Gas: 90% Helium, 7.5% Argon, 2.5% Carbon dioxide

Positions: All groove and fillet

Vertical Welding Progression: Up or down

Welding Procedure Specification (WPS)

WPS Number C-7 Supported by PQR No.(s) WRC¹, 068A, 070A, 074A, 075B, 076A

WPS Rev. No. Original WPS Rev. Date January 1994

Code Reference ANSI/AWS D9.1, Sheet Metal Welding Code

Variables

Base metal ANSI/ASTM A167 or A240 type 3XX

Metal thickness 18 Gauge (0.0500 in., 1.27 mm)

Coating type None

Joint preparation Shall be free of loose scale, rust, grease or foreign matter

Backing material None

Position of welding 4G Overhead

Welding Progression: N/A

Welding process GMAW

Manual, semiautomatic, or automatic Semiautomatic

Filler metal spec. ANSI/AWS A5.9

Filler metal class ER-3XX

Electrical Characteristics dcep


Electrode Extension 1/4 to 3/8 in.

Mode of transfer Short circuit

Shielding gas/combination 90% Helium, 7.5% Argon, 2.5% Carbon dioxide

Gas flow (CFH) 20-40 CFH

Joining Procedure

Filler Metal Size in.	Welding Power			Speed of Travel	Joint Detail
	Current Range Ampere	Wire Feed Speed (Reference) ipm	Voltage Range Volts		
0.035	60-100	120-210	16-19	As Required	 <p>Note: Root Opening = 0-1/2t</p>

¹Welding Research Council, 345 East 47th Street, New York, New York 10017.

²Also on file at AWS Headquarters (Qualification and Certification Dept.).

AWS QC7-93 Supplement C
Performance Test Description C-8
GMAW Stainless Steel

Code: ANSI/AWS D9.1

Welding Process: Semiautomatic gas metal arc welding (GMAW) **Transfer Mode:** Short circuiting

Base Material: ASTM A167 or A240, Type 3XX **Coating Type:** None

Material Form: Sheet — 3" x 6" **Thickness:** 18 Gauge

Filler Metal: ANSI/AWS A5.9, Class ER-3XX (F Number 6)

Weld Joint Detail: Square butt, root opening (R) = 0 – 1/2 t. Where t = base metal thickness

Backing: None

Welding Position(s): 2G

Vertical Welding Progression: Down

Welding Procedure Specification (WPS) No.: QC7-93, C-8-V

Welding Technique: Single pass

Current: dcep

Shielding Gas: 90% Helium, 7.5% Argon, 2.5% Carbon dioxide

Electrode Extension: 1/4 to 3/8 in.

Test Required: Visual inspection per ANSI/AWS D9.1

Limits of Welder Qualification

Code: ANSI/AWS D9.1

Welding Process: gas metal arc welding (GMAW) — semiautomatic/automatic transfer mode — Short circuiting

Base Metal: Chromium and chromium nickel steel (See ANSI/AWS D9.1)

Material Form: Sheet

Backing: With or without

Groove Weld Thickness: 16 Gauge and thinner

Fillet Weld Size: Unlimited

Pipe and Tubing: Not applicable

Filler Metal: ANSI/AWS A5.9, (F Number 6)

Current: dcep

Shielding Gas: 90% Helium, 7.5% Argon, 2.5% Carbon dioxide

Positions: Flat, horizontal and vertical groove and fillet

Vertical Welding Progression: Up or Down

Welding Procedure Specification (WPS)


WPS Number C-8 Supported by PQR No.(s) WRC¹, 068A, 070A, 074A, 075A, 076A²
 WPS Rev. No. Original WPS Rev. Date January 1994

Code Reference ANSI/AWS D9.1, Sheet Metal Welding Code

Variables

Base metal ANSI/ASTM A167 or A240 Type 3XX
 Metal thickness 18 Gauge (0.0500 in., 1.27 mm)
 Coating type None
 Joint preparation Shall be free of loose scale, rust, grease or foreign matter
 Backing material None
 Position of welding 3G Vertical Welding Progression: Down
 Welding process GMAW
 Manual, semiautomatic, or automatic Semiautomatic
 Filler metal spec. ANSI/AWS A5.9
 Filler metal class ER-3XX
 Electrical Characteristics dcep Electrode Extension 1/4 to 3/8 in.
 Mode of transfer Short circuit
 Shielding gas/combination 90% Helium, 7.5% Argon, 2.5% Carbon dioxide
 Gas flow (CFH) 20-40 CFH

Joining Procedure

Filler Metal Size in.	Welding Power			Speed of Travel	Joint Detail
	Current Range Ampere	Wire Feed Speed (Reference) ipm	Voltage Range Volts		
0.035	60-100	120-210	16-19	As Required	 <p>Note: Root Opening = 0-1/2t</p>

¹Welding Research Council, 345 East 47th Street, New York, New York 10017.

²Also on file at AWS Headquarters (Qualification and Certification Dept.).

AWS QC7-93 Supplement C
Performance Test Description C-9
GMAW Stainless Steel

Code: ANSI/AWS D9.1

Welding Process: Semiautomatic gas metal arc welding (GMAW) **Transfer Mode:** Short circuiting

Base Material: ASTM A167 or A240 Type 3XX **Coating Type:** None

Material Form: Sheet — 3" x 6" **Thickness:** 18 Gauge

Filler Metal: ANSI/AWS A5.9, Class ER-3XX (F Number 6)

Weld Joint Detail: Square butt, root opening (R) = 0 – 1/2 t. Where t = base metal thickness

Backing: None

Welding Position(s): 1G

Vertical Welding Progression: Not applicable

Welding Procedure Specification (WPS) No.: QC7-93, C-9-F

Welding Technique: Single pass

Current: dcep

Shielding Gas: 90% Helium, 7.5% Argon, 2.5% Carbon dioxide

Electrode Extension: 1/4 to 3/8 in.

Test Required: Visual inspection per ANSI/AWS D9.1

Limits of Welder Qualification

Code: ANSI/AWS D9.1

Welding Process: gas metal arc welding (GMAW) — semiautomatic/automatic transfer mode — short circuiting

Base Metal: Chromium to chromium nickel steel (uncoated) (See ANSI/AWS D9.1)

Material Form: Sheet

Backing: With or without

Groove Weld Thickness: 16 Gauge and thinner

Fillet Weld Size: Unlimited

Pipe and Tubing: Not applicable

Filler Metal: ANSI/AWS A5.9, (F Number 6)

Current: dcep

Shielding Gas: 90% Helium, 7.5% Argon, 2.5% Carbon dioxide

Positions: Flat groove and fillet

Vertical Welding Progression: Not applicable

Welding Procedure Specification (WPS)


WPS Number C-9 Supported by PQR No.(s) WRC¹, 068A, 070A, 074A, 075A, 076A²
 WPS Rev. No. Original WPS Rev. Date January 1994

Code Reference ANSI/AWS D9.1, Sheet Metal Welding Code

Variables

Base metal ANSI/ASTM A167 or A240 Type 3XX
 Metal thickness 18 Gauge (0.0500 in., 1.27 mm)
 Coating type None
 Joint preparation Shall be free of loose scale, rust, grease or foreign matter
 Backing material None
 Position of welding 1G Flat Welding Progression: N/A
 Welding process GMAW
 Manual, semiautomatic, or automatic Semiautomatic
 Filler metal spec. ANSI/AWS A5.9
 Filler metal class ER-3XX
 Electrical Characteristics dcep Electrode Extension 1/4 to 3/8 in.
 Mode of transfer Short circuit
 Shielding gas/combination 90% Helium, 7.5% Argon, 2.5% Carbon dioxide
 Gas flow (CFH) 20-40 CFH

Joining Procedure

Filler Metal Size in.	Welding Power			Speed of Travel	Joint Detail
	Current Range Ampere	Wire Feed Speed (Reference) ipm	Voltage Range Volts		
0.035	60-100	120-210	16-19	As Required	 <p>Note: Root Opening = 0-1/2t</p>

¹Welding Research Council, 345 East 47th Street, New York, New York 10017.

²Also on file at AWS Headquarters (Qualification and Certification Dept.).

AWS QC7 Supplement C
Performance Test Description C-10
GMAW Stainless Steel

Code: ANSI/AWS D9.1

Welding Process: Semiautomatic gas metal arc welding (GMAW) **Transfer Mode:** Short circuiting

Base Material: ASTM A167 or A240 Type 3XX **Coating Type:** None

Material Form: Sheet — 3" x 6" **Thickness:** 10 Gauge

Filler Metal: ANSI/AWS A5.9, Class ER-3XX (F Number 6)

Weld Joint Detail: Square butt, root opening (R) = 0 - 1/2 t. Where t = base metal thickness

Backing: None

Welding Position(s): 4G

Vertical Welding Progression: Not applicable

Welding Procedure Specification (WPS) No.: QC7-93, C-10-O

Welding Technique: Single pass

Current: dcep

Shielding Gas: 90% Helium, 7.5% Argon, 2.5% Carbon dioxide

Electrode Extension: 1/4 to 3/8 in.

Test Required: Visual inspection per AWS D9.1

Limits of Welder Qualification

Code: ANSI/AWS D9.1

Welding Process: gas metal arc welding (GMAW) — semiautomatic/automatic transfer mode — short circuiting

Base Metal: Chromium and chromium nickel steel (See ANSI/AWS D9.1)

Material Form: Sheet

Backing: With or without

Groove Weld Thickness: 16 Gauge to 0.281 in.

Fillet Weld Size: Unlimited

Pipe and Tubing: Not applicable

Filler Metal: ANSI/AWS A5.9, (F Number 6)

Current: dcep

Shielding Gas: 90% Helium, 7.5% Argon, 2.5% Carbon dioxide

Positions: All groove and fillet

Vertical Welding Progression: Up or Down

Welding Procedure Specification (WPS)


WPS Number C-10 Supported by PQR No(s) WRC¹, 071B, 072B, 073A, 077A, 078A, 079A²
 WPS Rev. No. Original WPS Rev. Date January 1994

Code Reference ANSI/AWS D9.1, Sheet Metal Welding Code

Variables

Base metal ANSI/ASTM A167 or A240, Type 3XX
 Metal thickness 10 Gauge (0.1406 in., 2.57 mm)
 Coating type None
 Joint preparation Shall be free of loose scale, rust, grease or foreign matter
 Backing material None
 Position of welding 4G Overhead Welding Progression: N/A
 Welding process GMAW
 Manual, semiautomatic, or automatic Semiautomatic
 Filler metal spec. ANSI/AWS A5.9
 Filler metal class ER3XX
 Electrical Characteristics dcep Electrode Extension 1/4 to 3/8 in.
 Mode of transfer Short circuit
 Shielding gas/combination 90% Helium, 7.5% Argon, 2.5% Carbon dioxide
 Gas flow (CFH) 20-40 CFH

Joining Procedure

Filler Metal Size in.	Welding Power			Speed of Travel	Joint Detail
	Current Range Ampere	Wire Feed Speed (Reference) ipm	Voltage Range Volts		
0.035	100-150	210-330	16-29	As Required	 <p>Note: Root Opening = 0-1/2t</p>

¹Welding Research Council, 345 East 47th Street, New York, New York 10017.

²Also on file at AWS Headquarters (Qualification and Certification Dept.).

AWS QC7-93 Supplement C
Performance Test Description C-11
GMAW Stainless Steel

Code: ANSI/AWS D9.1

Welding Process: Semiautomatic gas metal arc welding (GMAW) **Transfer Mode:** Short circuiting

Base Material: ASTM A167 or A240 Type 3XX **Coating Type:** None

Material Form: Sheet — 3" x 6" **Thickness:** 10 Gauge

Filler Metal: ANSI/AWS A5.9, Class ER-3XX (F Number 6)

Weld Joint Detail: Square butt, root opening (R) = 0 – 1/2 t. Where t = base metal thickness

Backing: None

Welding Position(s): 3G

Vertical Welding Progression: Down

Welding Procedure Specification (WPS) No.: QC7-93, C-11-V

Welding Technique: Single pass

Current: dcep

Shielding Gas: 90% Helium, 7.5% Argon, 2.5% Carbon dioxide

Electrode Extension: 1/4 to 3/8 in.

Test Required: Visual inspection per AWS D9.1

Limits of Welder Qualification

Code: ANSI/AWS D9.1

Welding Process: gas metal arc welding (GMAW) — semiautomatic/automatic transfer mode — short circuiting

Base Metal: Chromium and chromium nickel steel (See ANSI/AWS D9.1)

Material Form: Sheet **Backing:** With or without

Groove Weld Thickness: 16 Gauge to 0.281 in. **Fillet Weld Size:** Unlimited

Pipe and Tubing: Not applicable

Filler Metal: ANSI/AWS A5.9, (F Number 6)

Current: dcep

Shielding Gas: 90% Helium, 7.5% Argon, 2.5% Carbon dioxide

Positions: Flat, horizontal and vertical groove and fillet

Vertical Welding Progression: Up or Down

Welding Procedure Specification (WPS)


WPS Number C-11 Supported by PQR No.(s) WRC¹, 071B, 072B, 073A, 077A, 078A, 079A²
 WPS Rev. No. Original WPS Rev. Date January 1994

Code Reference ANSI/AWS D9.1, Sheet Metal Welding Code

Variables

Base metal ANSI/ASTM A167 or A240, Type 3XX
 Metal thickness 10 Gauge (0.1406 in., 2.57 mm)
 Coating type None
 Joint preparation Shall be free of loose scale, rust, grease or foreign matter
 Backing material None
 Position of welding 3G Vertical Welding Progression: Down
 Welding process GMAW
 Manual, semiautomatic, or automatic Semiautomatic
 Filler metal spec. ANSI/AWS A5.9
 Filler metal class ER3XX
 Electrical Characteristics dcep Electrode Extension 1/4 to 3/8 in.
 Mode of transfer Short circuit
 Shielding gas/combination 90% Helium, 7.5% Argon, 2.5% Carbon dioxide
 Gas flow (CFH) 20-40 CFH

Joining Procedure

Filler Metal Size in.	Welding Power			Speed of Travel	Joint Detail
	Current Range Ampere	Wire Feed Speed (Reference) ipm	Voltage Range Volts		
0.035	100-150	210-330	16-20	As Required	 <p>Note: Root Opening = 0-1/2t</p>

¹Welding Research Council, 345 East 47th Street, New York, New York 10017.

²Also on file at AWS Headquarters (Qualification and Certification Dept.).

AWS QC7-93 Supplement C
Performance Test Description C-12
GMAW Stainless Steel

Code: ANSI/AWS D9.1

Welding Process: Semiautomatic gas metal arc welding (GMAW) **Transfer Mode:** Short circuiting

Base Material: ASTM A167 or A240 Type 3XX **Coating Type:** None

Material Form: Sheet — 3" x 6" **Thickness:** 10 Gauge

Filler Metal: ANSI/AWS A5.9, Class ER-3XX (F Number 6)

Weld Joint Detail: square butt, root opening (R) = 0 – 1/2 t. Where t = base metal thickness

Backing: None

Welding Position(s): 1G (Flat, See AWS D9.1, Fig 2 (A))

Vertical Welding Progression: Not applicable

Welding Procedure Specification (WPS) No.: QC7-93, C-12-F

Welding Technique: Single pass

Current: dcep

Shielding Gas: 90% Helium, 7.5% Argon, 2.5% Carbon dioxide

Electrode Extension: 1/4 to 3/8 in.

Test Required: Visual inspection per AWS D9.1

Limits of Welder Qualification

Code: ANSI/AWS D9.1

Welding Process: gas metal arc welding (GMAW) — semiautomatic/automatic transfer mode — short circuiting

Base Metal: Chromium and chromium nickel steel (See ANSI/AWS D9.1)

Material Form: Sheet **Backing:** With or without

Groove Weld Thickness: 16 Gauge to 0.281 **Fillet Weld Size:** Unlimited

Pipe and Tubing: Not applicable

Filler Metal: ANSI/AWS A5.9, (F Number 6)

Current: dcep

Shielding Gas: 90% Helium, 7.5% Argon, 2.5% Carbon dioxide

Positions: Flat groove and fillet

Vertical Welding Progression: Not applicable

Welding Procedure Specification (WPS)


WPS Number C-12 Supported by PQR No.(s) WRC¹, 071B, 072B, 073A, 077A, 078A, 079A²
 WPS Rev. No. Original WPS Rev. Date January 1994

Code Reference ANSI/AWS D9.1, Sheet Metal Welding Code

Variables

Base metal ANSI/ASTM A167 or A240, Type 3XX
 Metal thickness 10 Gauge (0.1406 in., 2.57 mm)
 Coating type None
 Joint preparation Shall be free of loose scale, rust, grease or foreign matter
 Backing material None
 Position of welding 1G Flat Welding Progression: N/A
 Welding process GMAW
 Manual, semiautomatic, or automatic Semiautomatic
 Filler metal spec. ANSI/AWS A5.9
 Filler metal class ER3XX
 Electrical Characteristics dcep Electrode Extension 1/4 to 3/8 in.
 Mode of transfer Short circuit
 Shielding gas/combination 90% Helium, 7.5% Argon, 2.5% Carbon dioxide
 Gas flow (CFH) 20-40 CFH

Joining Procedure

Filler Metal Size in.	Welding Power			Speed of Travel	Joint Detail
	Current Range Ampere	Wire Feed Speed (Reference) ipm	Voltage Range Volts		
0.035	100-150	210-330	16-20	As Required	 <p>Note: Root Opening = 0-1/2t</p>

¹Welding Research Council, 345 East 47th Street, New York, New York 10017

²Also on file at AWS Headquarters (Qualification and Certification Dept.).

